

PDL lab data file: P7265
 AREA: OKA CLAIMS
 MAPSHEET NO: 82E13W
 VENTURE: BC GEN EX
 GEOLOGIST: R PINSENT
 LAB PROJECT NO: 7265

PLEASE DISTRIBUTE RESULTS TO: R PINSENT ** LAB **
 B. HODGSON M. GAREAU

STANDARD ANALYSIS METHODS USED BY PDL GEOCHEM LAB ARE LISTED BELOW:
 ALL RESULTS EXPRESSED AS INDICATED IN UNITS COLUMN BELOW
 ANY EXCEPTIONS FOR THIS PROJECT ARE NOTED ABOVE

REMARKS: INTERNAL LAB STANDARDS HAVE BEEN INCLUDED FOR REFERENCE.
 SAMPLE NUMBERS FOLLOWED BY * ARE DUPLICATE ANALYSES.


	UNITS	WT. G	ATTACK USED	TIME	RANGE	METHOD
MO	PPM	0.5	C HCLC4/HNO3	4HRS	1-1000	ATOMIC ABSORPTION
CU	PPM	0.5	C HCLQ4/HNO3	4HRS	2-4000	ATOMIC ABSORPTION
ZN	PPM	0.5	C HCLQ4/HNO3	4HRS	2-3000	ATOMIC ABSORPTION
PB	PPM	0.5	C HCLQ4/HNO3	4HRS	2-3000	A.A. BACKGROUND COR.
CD	PPM	0.5	C HCLQ4/HNO3	4HRS	0.2-200	A.A. BACKGROUND COR.
NI	PPM	0.5	C HCLQ4/HNO3	4HRS	2-2000	ATOMIC ABSORPTION
CO	PPM	0.5	C HCLQ4/HNO3	4HRS	2-2000	ATOMIC ABSORPTION
AG1	PPM	0.5	C HCLQ4/HNO3	4HRS	0.2-20	A.A. BACKGROUND COR
AU	PPM	10.0	AQUA REGIA	3HRS	0.02-4.00	A.A. SOLVENT EXTRACT.
U	PPM	0.25	DIL HNO3	2HRS	1.0-1000	FLOURIMETRY SOLV. EX.
V	PPM	0.5	C HF/HCLQ4/HNO3/HCL	6HRS	5-1000	ATOMIC ABSORPTION
W	PPM	0.5	C HCLQ4/H3PO4	2HRS	2-1000	DC PLASMA.
F	PPM	0.25	NA2CO3/KNO3 FUSION	30MIN	40-4000	SPECIFIC ION ELECTODE
AS	PPM	0.5	C HCLQ4/HNO3	4HRS	2-1000	A.A. BACKGROUND COR.
SB	PPM	0.5	C HCL/HNO3	2HRS	2-1000	A.A. BACKGROUND COR.
BI	PPM	0.5	C HCLQ4/HNO3	4HRS	2-2000	A.A. BACKGROUND COR.
MN	PPM	0.5	C HCLQ4/HNO3	4HRS	2-3000	ATOMIC ABSORPTION
FE	%	0.5	C HF/HCLQ4/HNO3/HCL	6HRS	0.02-20%	ATOMIC ABSORPTION
HG	PPB	0.25	DIL HNO3/HCL	2HRS	5-2000PPB	A.A. COLD VAPOR GEN.
BA	%	0.25	C HF/HI/OXALIC	4HRS	0.02-20%	ATOMIC ABSORPTION
NA	%	0.5	C HF/HCLQ4/HNO3/HCL	6HRS	0.2 -20%	ATOMIC ABSORPTION
K	%	0.5	C HF/HCLQ4/HNO3/HCL	6HRS	0.2 -20%	ATOMIC ABSORPTION
CA	%	0.5	C HF/HCLQ4/HNO3/HCL	6HRS	0.02-20%	ATOMIC ABSORPTION
SR	PPM	0.5	C HF/HCLQ4/HNO3/HCL	6HRS	10-2000	ATOMIC ABSORPTION
MG	%	0.5	C HF/HCLQ4/HNO3/HCL	6HRS	0.2-20%	ATOMIC ABSORPTION
SN	PPM	1.0	NH4I FUSION	15MIN	5-500	A.A. SOLVENT EXTRACT.
LOI	%	1.0	ASH 600 DEG C	2HRS	0.02-99%	WEIGH RESDUE

PLACER GEOCHEM ASSAY SYSTEM: DATA FROM BC GEN EX OKA CLAIMS

DATE:

GRID	SAMPLE	PROJECT	CU	ZN	PB	CD	CO	AG	AU	AS	BI	FE
82E13W	OKA	69551	7265	0.72%	98	<2	1.3	170	2.6	16.5	40	204 17.7
82E13W	OKA	69552	7265	0.26%	2.86%	<2	350	41	2.7	1.3	650	12 39.4%
82E13W	OKA	69553	7265	260	182	<2	1.8	23	1.0	0.17	94	6 5.90
82E13W	OKA	69554	7265	128	215	<2	2.5	29	0.5	0.33	13	30 7.90
82E13W	OKA	69555	7265	49	37	2	0.3	25	1.7	4.7	17	202 7.54
82E13W	OKA	69556	7265	1360	1800	<2	11.4	30	6.0	3.9	0.56%	180 6.85%
82E13W	OKA	69557	7265	114	180	<2	2.0	21	0.3	0.07	66	2 4.90
82E13W	OKA	69557*	7265							0.08		
test	STD CU		7265	0.41%								
test	STD PB-ZN		7265		0.56%						0.09%	

END OF LISTING - 10 RECORDS PRINTED
 GCLIST RUN AT: 15:33:48



PLACER DEVELOPMENT LIMITED: GEOCHEM ASSAY SYSTEM

Following elements needed some values adjusted:

ELEMENT	NSS	LOW	HI	%	BLNK	NVAL
CU	0	0	0	2	0	7
ZN	0	0	0	1	0	7
PB	0	6	0	0	0	7
AS	0	0	0	1	0	7
FE	0	0	0	2	0	7

3 records skipped: tests, duplicate analyses

SUMMARY OF GEOCHEM DATA: BC GEN EX OKA CLAIMS

ITEM	# VALUES	MISSING	MINIMUM	MAXIMUM	AVERAGE	STD. DEV.
GRID	7	0	82E13W	82E13W		
SAMP	7	0	OKA	OKA		
PROJ	7	0	7265	7265		
AG	7	0	0.30	6.00	2.11	1.96
AS	7	0	13.00	5600.00	925.71	2073.61
AU	7	0	0.07	16.50	3.85	5.88
BI	7	0	2.00	204.00	90.86	98.42
CD	7	0	0.30	350.00	52.76	131.12
CO	7	0	21.00	170.00	48.43	54.01
CU	7	0	49.00	7200.00	1673.00	2612.68
FE	7	0	4.90	390000.00	65506.28	145347.14
PB	7	0	1.00	2.00	1.14	0.38
ZN	7	0	37.00	28600.00	4444.57	10669.61

END OF GCHSCAN: DATE: 87:11:26 time: 15:33:48 7 RECORDS PROCESSED