

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R. Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 2.

Venture: _____

Date: January 22/81 Page 1 of 7

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | | | | P P B | | % | | PPM | | | |
|-----------|-------------|------------|--|-----|----|-----|------|----|----|--------|----|----|----|---|-------|----|------|------|------|--|--|--|
| | | | F | As | Bi | Mn | Fe | Hg | Ba | L.O.I. | Sn | Na | Ca | K | | | | | | | | |
| | | | 16 17 20 21 25 26 30 31 35 36 40 41 45 46 50 51 55 56 60 61 80 | | | | | | | | | | | | | | | | | | | |
| A | 65001-65010 | 0222 | 400 | 14 | 12 | 158 | 0.98 | | | | | | | | | 5 | 1.95 | 0.37 | 2.00 | | | |
| | 65011-65020 | | 420 | 18 | 10 | 170 | 0.79 | | | | | | | | | 10 | 1.91 | 0.32 | 2.22 | | | |
| | 65021-65030 | | 420 | 3 | 9 | 174 | 0.81 | | | | | | | | | 5- | 2.17 | 0.39 | 2.30 | | | |
| | 65031-65038 | | 440 | 33 | 10 | 203 | 0.71 | | | | | | | | | 9 | 1.94 | 0.35 | 1.65 | | | |
| | 65039-65047 | | 560 | 2 | 7 | 119 | 0.99 | | | | | | | | | 5- | 2.17 | 0.59 | 2.32 | | | |
| | 65048-65054 | | 500 | 47 | 13 | 142 | 0.89 | | | | | | | | | 5- | 1.86 | 0.46 | 2.17 | | | |
| | 65055-65064 | | 500 | 6 | 11 | 136 | 0.90 | | | | | | | | | 5- | 2.33 | 0.60 | 2.18 | | | |
| | 65065-65074 | | 360 | 4 | 15 | 126 | 0.76 | | | | | | | | | 5- | 1.85 | 0.61 | 2.25 | | | |
| | 65075-65084 | | 460 | 2 | 9 | 127 | 0.79 | | | | | | | | | 5- | 2.13 | 0.39 | 2.09 | | | |
| | 65085-65095 | | 780 | 5 | 10 | 163 | 0.99 | | | | | | | | | 7 | 1.99 | 0.45 | 1.73 | | | |
| | 65096-65105 | | 840 | 4 | 13 | 167 | 1.02 | | | | | | | | | 5- | 2.33 | 0.69 | 2.29 | | | |
| | 65106-65115 | | 440 | 1- | 10 | 140 | 0.70 | | | | | | | | | 17 | 2.29 | 0.44 | 1.85 | | | |
| | 65116-65125 | | 400 | 27 | 8 | 174 | 0.75 | | | | | | | | | 17 | 2.11 | 0.38 | 1.95 | | | |
| | 65126-65133 | | 360 | 2 | 8 | 140 | 0.81 | | | | | | | | | 30 | 2.49 | 0.50 | 1.98 | | | |
| | 65134-65141 | | 480 | 3 | 10 | 126 | 0.88 | | | | | | | | | 5- | 2.16 | 0.44 | 1.86 | | | |
| | 65142-65152 | | 460 | 6 | 12 | 162 | 0.76 | | | | | | | | | 6 | 1.69 | 0.45 | 1.63 | | | |
| | 65153-65164 | | 640 | 5 | 11 | 143 | 0.75 | | | | | | | | | 5- | 2.10 | 0.40 | 2.38 | | | |
| | 65165-65167 | | 480 | 4 | 14 | 177 | 0.80 | | | | | | | | | 5- | 1.80 | 0.60 | 1.96 | | | |
| | 65168-65176 | | 1600 | 160 | 18 | 255 | 1.33 | | | | | | | | | 10 | 2.14 | 0.92 | 1.83 | | | |
| | 65177-65186 | | 700 | 3 | 11 | 137 | 0.83 | | | | | | | | | 5- | 2.42 | 0.40 | 2.15 | | | |
| | 65187-65196 | | 380 | 3 | 11 | 105 | 0.81 | | | | | | | | | 5- | 2.30 | 0.56 | 2.34 | | | |
| | 65197-65208 | | 1220 | 27 | 9 | 411 | 0.82 | | | | | | | | | 5- | 1.97 | 0.60 | 1.49 | | | |
| | 65209-65215 | | 580 | 69 | 11 | 710 | 0.88 | | | | | | | | | 5- | 1.92 | 0.21 | 1.80 | | | |
| | 65216-65225 | | 500 | 33 | 11 | 194 | 0.86 | | | | | | | | | 5- | 2.14 | 0.37 | 2.25 | | | |
| | 65226-65235 | | 500 | 81 | 10 | 253 | 0.83 | | | | | | | | | 5- | 1.78 | 0.41 | 2.33 | | | |

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R. Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 1.

Date: January 22/81 Page 2 of 7

Venture: _____

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | | | | | | | | | | | | | | | | | |
|-----------|-------------|------------|--------|-----|-----|-----|----|----|----|----|----|------|-------|------|----|----|----|----|----|----|----|----|----|----|----|----|----|-----|
| | | | Mo | Cu | Zn | Pb | Cd | Ni | Co | Ag | Au | U | V | W | | | | | | | | | | | | | | |
| 1 | 2 | 16 | 17 | 20 | 21 | 25 | 26 | 30 | 31 | 35 | 36 | 40 | 41 | 45 | 46 | 50 | 51 | 55 | 56 | 60 | 61 | 65 | 66 | 70 | 71 | 75 | 76 | 80 |
| A | 65236-65245 | 0222 | 400 | 10 | 70 | 37 | | | | 17 | 5 | 0.52 | 0.02- | 23 | | | | | | | | | | | | | | 63 |
| | 65246-65255 | | 390 | 13 | 220 | 147 | | | | 14 | 5 | 0.78 | 0.02- | 22 | | | | | | | | | | | | | | 29 |
| | 65256-65263 | | 100 | 15 | 43 | 25 | | | | 10 | 5 | 0.42 | 0.02- | 8.5 | | | | | | | | | | | | | | 113 |
| | 65264-65268 | | 200 | 47 | 89 | 176 | | | | 10 | 5 | 1.82 | 0.02- | 9.4 | | | | | | | | | | | | | | 79 |
| | 65269-65278 | | 140 | 11 | 16 | 8 | | | | 9 | 4 | 0.29 | 0.02- | 18.7 | | | | | | | | | | | | | | 81 |
| | 65279-65288 | | 150 | 8 | 17 | 7 | | | | 12 | 4 | 0.25 | 0.02- | 13.6 | | | | | | | | | | | | | | 64 |
| | 65289-65292 | | 49 | 11 | 20 | 8 | | | | 14 | 3 | 0.21 | 0.02- | 8.5 | | | | | | | | | | | | | | 70 |
| | 65293-65299 | | 90 | 25 | 40 | 16 | | | | 19 | 7 | 0.72 | 0.02- | 9.4 | | | | | | | | | | | | | | 77 |
| | 65300-65305 | | 280 | 9 | 21 | 6 | | | | 17 | 5 | 0.31 | 0.02- | 13.6 | | | | | | | | | | | | | | 180 |
| | 65306-65312 | | 320 | 8 | 19 | 5 | | | | 14 | 5 | 0.19 | 0.02- | 16.2 | | | | | | | | | | | | | | 119 |
| | 65313-65316 | | 110 | 6 | 36 | 6 | | | | 23 | 10 | 0.15 | 0.02- | 5- | | | | | | | | | | | | | | 141 |
| | 65317-65325 | | 270 | 8 | 15 | 12 | | | | 12 | 4 | 0.26 | 0.02- | 17.0 | | | | | | | | | | | | | | 98 |
| | 65326-65335 | | 460 | 8 | 13 | 7 | | | | 12 | 4 | 0.18 | 0.02- | 10.2 | | | | | | | | | | | | | | 51 |
| | 65336-65338 | | 20 | 14 | 34 | 12 | | | | 14 | 4 | 0.17 | 0.02- | 5- | | | | | | | | | | | | | | 11 |
| | 65339-65345 | | 26 | 18 | 34 | 6 | | | | 9 | 3 | 0.08 | 0.02- | 8.5 | | | | | | | | | | | | | | 10 |
| | 65346-65348 | | 160 | 10 | 11 | 11 | | | | 11 | 3 | 0.18 | 0.02- | 5- | | | | | | | | | | | | | | 30 |
| | 65349-65358 | | 350 | 11 | 15 | 7 | | | | 7 | 3 | 0.18 | 0.02- | 5.1 | | | | | | | | | | | | | | 43 |
| | 65359-65366 | | 0.084% | 11 | 17 | 8 | | | | 10 | 4 | 0.12 | 0.02- | 5.1 | | | | | | | | | | | | | | 46 |
| | 65367-65376 | | 310 | 10 | 16 | 10 | | | | 10 | 3 | 0.12 | 0.02- | 8.5 | | | | | | | | | | | | | | 123 |
| | 65377-65382 | | 250 | 9 | 51 | 44 | | | | 10 | 4 | 0.57 | 0.02- | 11.9 | | | | | | | | | | | | | | 56 |
| | 65383-65386 | | 120 | 10 | 6 | 6 | | | | 12 | 3 | 0.17 | 0.02- | 29 | | | | | | | | | | | | | | 55 |
| | 65387-65391 | | 100 | 76 | 52 | 61 | | | | 8 | 5 | 3.63 | 0.02- | 5- | | | | | | | | | | | | | | 37 |
| | 65392-65398 | | 35 | 51 | 224 | 64 | | | | 16 | 8 | 1.22 | 0.02- | 5- | | | | | | | | | | | | | | 22 |
| | 65399-65400 | | 33 | 39 | 61 | 29 | | | | 16 | 8 | 0.93 | 0.02- | 5- | | | | | | | | | | | | | | 18 |
| | 65401-65406 | | 74 | 171 | 770 | 540 | | | | 23 | 11 | 7 | 0.02- | 5- | | | | | | | | | | | | | | 150 |

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 2.

Venture: _____

Date: January 22/81 Page 2 of 7

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | | | | | PPB | % | | PPM | | | | |
|-----------|-------------|------------|-------|-----|----|------|------|----|----|--------|----|----|----|----|----|-----|----|----|-----|----|------|------|------|
| | | | F | As | Bi | Mn | Fe | Hg | Ba | L.O.I. | Sn | Na | Ca | K | | | | | | | | | |
| 1 | 2 | 16 | 17 | 20 | 21 | 25 | 26 | 30 | 31 | 35 | 36 | 40 | 41 | 45 | 46 | 50 | 51 | 55 | 56 | 60 | 61 | 80 | |
| A | 65236-65245 | 0222 | 780 | 250 | 12 | 1330 | 0.91 | | | | | | | | | | | | | 19 | 1.10 | 0.55 | 1.80 |
| | 65246-65255 | | 1020 | 360 | 12 | 2150 | 0.92 | | | | | | | | | | | | | 5- | 1.08 | 0.60 | 1.23 |
| | 65256-65263 | | 920 | 31 | 11 | 290 | 0.67 | | | | | | | | | | | | | 5 | 3.05 | 0.31 | 2.59 |
| | 65264-65268 | | 1040 | 280 | 22 | 324 | 0.77 | | | | | | | | | | | | | 9 | 2.27 | 0.34 | 2.82 |
| | 65269-65278 | | 540 | 13 | 11 | 166 | 0.77 | | | | | | | | | | | | | 5- | 2.19 | 0.35 | 2.33 |
| | 65279-65288 | | 580 | 6 | 8 | 155 | 0.75 | | | | | | | | | | | | | 5- | 2.40 | 0.36 | 2.22 |
| | 65289-65292 | | 640 | 9 | 9 | 86 | 0.72 | | | | | | | | | | | | | 8 | 2.19 | 0.28 | 2.40 |
| | 65293-65299 | | 3800 | 91 | 20 | 560 | 1.12 | | | | | | | | | | | | | 5- | 2.30 | 1.28 | 2.21 |
| | 65300-65305 | | 1160 | 3 | 11 | 171 | 1.11 | | | | | | | | | | | | | 8 | 2.44 | 0.70 | 2.12 |
| | 65306-65312 | | 840 | 4 | 10 | 155 | 1.06 | | | | | | | | | | | | | 5 | 2.88 | 0.64 | 2.99 |
| | 65313-65316 | | 2300 | 3 | 16 | 283 | 1.45 | | | | | | | | | | | | | 5 | 2.49 | 1.36 | 2.13 |
| | 65317-65325 | | 540 | 5 | 10 | 107 | 0.90 | | | | | | | | | | | | | 5- | 1.92 | 0.54 | 1.90 |
| | 65326-65335 | | 600 | 3 | 10 | 110 | 0.91 | | | | | | | | | | | | | 5 | 2.28 | 0.49 | 2.40 |
| | 65336-65338 | | 1080 | 20 | 11 | 67 | 1.05 | | | | | | | | | | | | | 5- | 1.40 | 0.73 | 2.23 |
| | 65339-65345 | | 840 | 12 | 6 | 75 | 0.90 | | | | | | | | | | | | | 9 | 1.85 | 0.26 | 2.43 |
| | 65346-65348 | | 880 | 5 | 7 | 70 | 0.53 | | | | | | | | | | | | | 5- | 2.04 | 0.37 | 2.19 |
| | 65349-65358 | | 2000 | 2 | 10 | 109 | 0.96 | | | | | | | | | | | | | 5- | 1.93 | 0.47 | 2.02 |
| | 65359-65366 | | 1480 | 3 | 10 | 128 | 1.07 | | | | | | | | | | | | | 5- | 1.72 | 0.46 | 1.74 |
| | 65367-65376 | | 1960 | 6 | 8 | 131 | 0.89 | | | | | | | | | | | | | 5- | 1.96 | 0.46 | 2.25 |
| | 65377-65382 | | 3800 | 40 | 9 | 193 | 0.85 | | | | | | | | | | | | | 21 | 1.94 | 0.47 | 2.10 |
| | 65383-65386 | | 900 | 5 | 6 | 62 | 0.61 | | | | | | | | | | | | | 5- | 1.69 | 0.34 | 1.93 |
| | 65387-65391 | | 2200 | 36 | 32 | 91 | 1.00 | | | | | | | | | | | | | 5- | 1.41 | 0.31 | 2.26 |
| | 65392-65398 | | 3400 | 13 | 14 | 318 | 1.33 | | | | | | | | | | | | | 11 | 1.29 | 0.68 | 1.71 |
| | 65399-65400 | | 2400 | 13 | 14 | 329 | 1.30 | | | | | | | | | | | | | 35 | 1.76 | 0.75 | 1.86 |
| | 65401-65406 | | 4000+ | 110 | 27 | 520 | 1.72 | | | | | | | | | | | | | 19 | 1.01 | 1.39 | 2.05 |

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 1.

Date: January 22/81 Page 3 of 7

Venture: _____

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | | | | | | | | | | | | | | | | | |
|-----------|-------------|------------|--------|-----|-----|-----|----|----|----|----|----|------|-------|------|----|----|----|----|----|----|----|----|----|----|----|----|----|-----|
| | | | Mo | Cu | Zn | Pb | Cd | Ni | Co | Ag | Au | U | V | W | | | | | | | | | | | | | | |
| 1 | 2 | 16 | 17 | 20 | 21 | 25 | 26 | 30 | 31 | 35 | 36 | 40 | 41 | 45 | 46 | 50 | 51 | 55 | 56 | 60 | 61 | 65 | 66 | 70 | 71 | 75 | 76 | 80 |
| A | 65407-65416 | 0222 | 62 | 49 | 61 | 49 | | | | 10 | 5 | 0.74 | 0.02- | 6.8 | | | | | | | | | | | | | | 40 |
| | 65417-65426 | | 150 | 37 | 52 | 42 | | | | 10 | 4 | 0.44 | 0.02- | 5.1 | | | | | | | | | | | | | | 48 |
| | 65427-65434 | | 220 | 53 | 127 | 223 | | | | 12 | 5 | 2.69 | 0.02- | 17.0 | | | | | | | | | | | | | | 41 |
| | 65435-65438 | | 360 | 108 | 80 | 24 | | | | 11 | 5 | 0.33 | 0.02- | 10.2 | | | | | | | | | | | | | | 72 |
| | 65439-65441 | | 670 | 46 | 66 | 26 | | | | 13 | 5 | 0.48 | 0.02- | 5- | | | | | | | | | | | | | | 48 |
| | 65442-65454 | | 280 | 13 | 49 | 32 | | | | 12 | 5 | 0.31 | 0.03 | 8.5 | | | | | | | | | | | | | | 9 |
| | 65455-65457 | | 170 | 16 | 26 | 27 | | | | 16 | 4 | 0.49 | 0.02- | 30 | | | | | | | | | | | | | | 10 |
| | 65458-65470 | | 220 | 8 | 15 | 8 | | | | 6 | 3 | 0.21 | 0.02- | 5- | | | | | | | | | | | | | | 145 |
| | 65471-65480 | | 460 | 6 | 13 | 7 | | | | 13 | 4 | 0.34 | 0.02- | 10.2 | | | | | | | | | | | | | | 114 |
| | 65481-65490 | | 350 | 4 | 14 | 7 | | | | 8 | 4 | 0.15 | 0.02- | 13.6 | | | | | | | | | | | | | | 76 |
| | 65491-65500 | | 340 | 9 | 15 | 10 | | | | 9 | 4 | 0.41 | 0.02- | 19.6 | | | | | | | | | | | | | | 32 |
| | 65501-65511 | | 220 | 7 | 11 | 6 | | | | 10 | 3 | 0.18 | 0.02- | 20 | | | | | | | | | | | | | | 49 |
| | 65512-65519 | | 210 | 16 | 44 | 14 | | | | 11 | 3 | 0.11 | 0.02- | 6.4 | | | | | | | | | | | | | | 71 |
| | 65520-65529 | | 260 | 13 | 24 | 9 | | | | 10 | 4 | 0.08 | 0.02- | 5- | | | | | | | | | | | | | | 39 |
| | 65530-65540 | | 480 | 15 | 26 | 18 | | | | 9 | 4 | 0.09 | 0.02- | 5- | | | | | | | | | | | | | | 115 |
| | 65541-65551 | | 340 | 15 | 17 | 9 | | | | 7 | 3 | 0.08 | 0.02- | 6.0 | | | | | | | | | | | | | | 66 |
| | 65552-65559 | | 330 | 15 | 21 | 9 | | | | 9 | 4 | 0.08 | 0.02- | 7.7 | | | | | | | | | | | | | | 230 |
| | 65560-65569 | | 130 | 14 | 24 | 9 | | | | 7 | 4 | 0.15 | 0.02- | 5- | | | | | | | | | | | | | | 80 |
| | 65570-65579 | | 0.115% | 24 | 47 | 29 | | | | 10 | 4 | 0.20 | 0.02- | 5.1 | | | | | | | | | | | | | | 82 |
| | 65580-65589 | | 480 | 13 | 30 | 9 | | | | 10 | 4 | 0.12 | 0.02- | 6.0 | | | | | | | | | | | | | | 100 |
| | 65590-65599 | | 320 | 6 | 20 | 5 | | | | 11 | 4 | 0.04 | 0.02- | 5- | | | | | | | | | | | | | | 65 |
| | 65600-65608 | | 160 | 4 | 14 | 3 | | | | 9 | 4 | 0.04 | 0.02- | 5- | | | | | | | | | | | | | | 38 |
| | 65609-65621 | | 80 | 4 | 18 | 3 | | | | 10 | 7 | 0.04 | 0.02- | 30 | | | | | | | | | | | | | | 24 |
| | 65622-65629 | | 190 | 15 | 19 | 5 | | | | 13 | 6 | 0.07 | 0.02- | 7.5 | | | | | | | | | | | | | | 9 |
| | 65630-65639 | | 430 | 10 | 17 | 3 | | | | 9 | 4 | 0.04 | 0.02- | 7.5 | | | | | | | | | | | | | | 11 |

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 2.

Venture: _____

Date: January 22/81 Page 3 of 7

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | P P B | | % | | | PPM | | | | | | |
|-----------|-------------|------------|-------|-----|----|-----|------|----|----|--------|----|-------|----|----|----|----|-----|----|----|----|------|------|------|
| | | | F | As | Bi | Mn | Fe | Hg | Ba | L.O.I. | Sn | Na | Ca | K | | | | | | | | | |
| 1 | 2 | 16 | 17 | 20 | 21 | 25 | 26 | 30 | 31 | 35 | 36 | 40 | 41 | 45 | 46 | 50 | 51 | 55 | 56 | 60 | 61 | 80 | |
| A | 65407-65416 | 0222 | 2600 | 71 | 12 | 203 | 0.96 | | | | | | | | | | | | | 11 | 1.40 | 0.49 | 2.65 |
| | 65417-65426 | | 1800 | 39 | 10 | 151 | 0.82 | | | | | | | | | | | | | 7 | 1.54 | 0.35 | 2.13 |
| | 65427-65434 | | 1800 | 180 | 15 | 323 | 1.05 | | | | | | | | | | | | | 11 | 1.07 | 0.43 | 1.82 |
| | 65435-65438 | | 1320 | 41 | 8 | 214 | 1.33 | | | | | | | | | | | | | 5- | 1.08 | 0.40 | 2.09 |
| | 65439-65441 | | 1000 | 88 | 9 | 182 | 1.13 | | | | | | | | | | | | | 32 | 0.83 | 0.46 | 2.65 |
| | 65442-65454 | | 1040 | 970 | 11 | 530 | 1.04 | | | | | | | | | | | | | 5- | 1.28 | 0.55 | 2.51 |
| | 65455-65457 | | 840 | 290 | 10 | 183 | 0.77 | | | | | | | | | | | | | 5- | 2.13 | 0.31 | 2.19 |
| | 65458-65470 | | 780 | 5 | 10 | 83 | 0.80 | | | | | | | | | | | | | 29 | 2.32 | 0.37 | 3.12 |
| | 65471-65480 | | 560 | 1 | 11 | 173 | 0.86 | | | | | | | | | | | | | 43 | 2.00 | 0.53 | 2.36 |
| | 65481-65490 | | 380 | 4 | 9 | 122 | 0.84 | | | | | | | | | | | | | 29 | 2.01 | 0.44 | 2.48 |
| | 65491-65500 | | 420 | 20 | 12 | 104 | 0.74 | | | | | | | | | | | | | 14 | 1.84 | 0.34 | 2.59 |
| | 65501-65511 | | 260 | 5 | 9 | 137 | 0.73 | | | | | | | | | | | | | 22 | 1.88 | 0.36 | 2.26 |
| | 65512-65519 | | 1140 | 3 | 10 | 97 | 1.01 | | | | | | | | | | | | | 12 | 1.80 | 0.44 | 2.34 |
| | 65520-65529 | | 840 | 4 | 12 | 94 | 0.97 | | | | | | | | | | | | | 15 | 1.98 | 0.49 | 2.49 |
| | 65530-65540 | | 880 | 25 | 9 | 114 | 1.00 | | | | | | | | | | | | | 6 | 2.01 | 0.50 | 2.68 |
| | 65541-65551 | | 540 | 3 | 8 | 77 | 0.78 | | | | | | | | | | | | | 14 | 1.90 | 0.30 | 2.38 |
| | 65552-65559 | | 500 | 2 | 9 | 102 | 0.93 | | | | | | | | | | | | | 7 | 1.67 | 0.30 | 2.32 |
| | 65560-65569 | | 600 | 4 | 12 | 122 | 1.10 | | | | | | | | | | | | | 6 | 1.72 | 0.45 | 2.13 |
| | 65570-65579 | | 580 | 16 | 9 | 97 | 0.85 | | | | | | | | | | | | | 11 | 1.90 | 0.41 | 2.52 |
| | 65580-65589 | | 560 | 4 | 13 | 142 | 0.99 | | | | | | | | | | | | | 19 | 1.86 | 0.77 | 3.01 |
| | 65590-65599 | | 280 | 2 | 10 | 106 | 1.00 | | | | | | | | | | | | | 34 | 1.71 | 0.49 | 2.55 |
| | 65600-65608 | | 230 | 1 | 11 | 91 | 0.99 | | | | | | | | | | | | | 10 | 1.87 | 0.53 | 2.59 |
| | 65609-65621 | | 420 | 2 | 15 | 138 | 0.92 | | | | | | | | | | | | | 6 | 2.24 | 0.52 | 2.08 |
| | 65622-65629 | | 800 | 9 | 14 | 122 | 1.12 | | | | | | | | | | | | | 6 | 1.65 | 0.53 | 2.49 |
| | 65630-65639 | | 660 | 3 | 13 | 106 | 0.95 | | | | | | | | | | | | | 7 | 1.90 | 0.61 | 2.84 |

Area : Adanac

PLACER DEVELOPMENT LIMITED

Geologist : R Pinsent

Map Sheet No. : _____

Geochemistry Analysis Sheet No. 1.

Date : January 22/81 Page 4 of 7

Venture : _____

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | | | | | | | |
|-----------|-------------|------------|--|----|-----|----|----|----|----|------|-------|------|---|-----|--|--|--|--|
| | | | Mo | Cu | Zn | Pb | Cd | Ni | Co | Ag | Au | U | V | W | | | | |
| | | | 16 17 20 21 25 26 30 31 35 36 40 41 45 46 50 51 55 56 60 61 65 66 70 71 75 76 80 | | | | | | | | | | | | | | | |
| A | 65640-65649 | 0222 | 850 | 14 | 17 | 6 | | 11 | 4 | 0.06 | 0.02- | 5.3 | | 48 | | | | |
| | 65650-65659 | | 390 | 12 | 20 | 3 | | 9 | 3 | 0.05 | 0.02- | 6.8 | | 52 | | | | |
| | 65660-65669 | | 340 | 9 | 17 | 9 | | 8 | 5 | 0.06 | 0.02- | 9.0 | | 23 | | | | |
| | 65670-65674 | | 220 | 7 | 16 | 4 | | 9 | 4 | 0.20 | 0.02- | 7.5 | | 65 | | | | |
| | 65675-65681 | | 160 | 17 | 24 | 9 | | 8 | 4 | 0.20 | 0.02- | 6.0 | | 24 | | | | |
| | 65682-65691 | | 250 | 14 | 30 | 24 | | 9 | 4 | 0.53 | 0.02- | 5- | | NSS | | | | |
| | 65692-65698 | | 420 | 13 | 38 | 25 | | 10 | 4 | 0.81 | 0.02- | 3.8 | | 24 | | | | |
| | 65699-65708 | | 430 | 8 | 19 | 17 | | 8 | 4 | 0.63 | 0.02- | 9.8 | | 43 | | | | |
| | 65709-65718 | | 180 | 8 | 10 | 12 | | 8 | 3 | 0.41 | 0.03 | 15.8 | | 54 | | | | |
| | 65719-65728 | | 110 | 6 | 38 | 32 | | 9 | 4 | 0.30 | 0.02- | 13.5 | | 30 | | | | |
| | 65729-65735 | | 120 | 4 | 22 | 13 | | 9 | 6 | 0.10 | 0.02- | 12.8 | | 21 | | | | |
| | 65736-65738 | | 70 | 11 | 20 | 4 | | 15 | 10 | 0.25 | 0.02- | 9.8 | | 105 | | | | |
| | 65739-65749 | | 360 | 12 | 10 | 3 | | 10 | 6 | 0.35 | 0.02- | 11.3 | | 37 | | | | |
| | 65750-65759 | | 400 | 16 | 17 | 4 | | 8 | 8 | 0.24 | 0.02- | 15.8 | | 58 | | | | |
| | 65760-65769 | | 280 | 21 | 18 | 12 | | 8 | 7 | 0.46 | 0.02- | 17.3 | | 34 | | | | |
| | 65770-65779 | | 460 | 19 | 21 | 25 | | 15 | 6 | 0.72 | 0.02- | 19.5 | | 164 | | | | |
| | 65780-65788 | | 380 | 13 | 18 | 18 | | 11 | 6 | 0.48 | 0.02- | 20.5 | | 118 | | | | |
| | 65789-65796 | | 43 | 12 | 21 | 10 | | 12 | 5 | 0.10 | 0.02- | 5- | | 82 | | | | |
| | 65797-65806 | | 130 | 16 | 43 | 12 | | 12 | 6 | 0.11 | 0.02- | 5- | | 131 | | | | |
| | 65807-65816 | | 300 | 9 | 30 | 15 | | 10 | 6 | 0.35 | 0.02- | 5- | | 105 | | | | |
| | 65817-65824 | | 130 | 8 | 161 | 49 | | 12 | 8 | 0.57 | 0.02- | 12.8 | | 50 | | | | |
| | 65825-65834 | | 120 | 7 | 71 | 44 | | 10 | 6 | 0.35 | 0.02- | 10.5 | | 34 | | | | |
| | 65835-65844 | | 130 | 6 | 64 | 20 | | 13 | 7 | 0.39 | 0.02- | 15.0 | | 56 | | | | |
| | 65845-65849 | | 150 | 8 | 39 | 6 | | 12 | 7 | 0.17 | 0.02- | 15.0 | | 37 | | | | |
| | 65850-65856 | | 400 | 20 | 29 | 20 | | 14 | 11 | 0.25 | 0.02- | 15.0 | | 22 | | | | |

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R. Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 2.

Date: January 22/81 Page 4 of 7

Venture: _____

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | | | | | | P P B | | % | | | PPM | | | |
|-----------|-------------|------------|-------|----|----|-----|------|----|----|--------|----|----|----|----|----|----|-------|----|----|------|------|------|----|--|--|
| | | | F | As | Bi | Mn | Fe | Hg | Ba | L.O.I. | Sn | Na | Ca | K | | | | | | | | | | | |
| | | | 16 | 17 | 20 | 21 | 23 | 24 | 30 | 31 | 35 | 36 | 40 | 41 | 43 | 44 | 50 | 51 | 53 | 56 | 60 | 61 | 80 | | |
| A | 65640-65649 | 0222 | 500 | 3 | 13 | 111 | 0.94 | | | | | | | | | | | | 8 | 1.89 | 0.65 | 2.63 | | | |
| | 65650-65659 | | 580 | 1 | 13 | 100 | 1.02 | | | | | | | | | | | | 7 | 1.96 | 0.60 | 2.72 | | | |
| | 65660-65669 | | 480 | 84 | 14 | 134 | 0.85 | | | | | | | | | | | | 5 | 1.86 | 0.57 | 2.73 | | | |
| | 65670-65674 | | 380 | 4 | 11 | 105 | 0.82 | | | | | | | | | | | | 6 | 1.86 | 0.53 | 2.49 | | | |
| | 65675-65681 | | 580 | 20 | 11 | 86 | 0.83 | | | | | | | | | | | | 16 | 1.87 | 0.28 | 1.99 | | | |
| | 65682-65691 | | 600 | 3 | 14 | 137 | 0.81 | | | | | | | | | | | | 9 | 1.93 | 0.33 | 2.60 | | | |
| | 65692-65698 | | 560 | 13 | 17 | 162 | 0.83 | | | | | | | | | | | | 11 | 1.69 | 0.54 | 2.68 | | | |
| | 65699-65708 | | 480 | 6 | 15 | 138 | 0.51 | | | | | | | | | | | | 7 | 1.42 | 0.32 | 1.71 | | | |
| | 65709-65718 | | 600 | 4 | 16 | 149 | 0.62 | | | | | | | | | | | | 17 | 1.68 | 0.43 | 2.22 | | | |
| | 65719-65728 | | 380 | 73 | 12 | 157 | 0.70 | | | | | | | | | | | | 5 | 1.81 | 0.40 | 2.00 | | | |
| | 65729-65735 | | 440 | 3 | 12 | 147 | 0.69 | | | | | | | | | | | | 10 | 1.78 | 0.55 | 2.44 | | | |
| | 65736-65738 | | 920 | 2 | 18 | 165 | 1.45 | | | | | | | | | | | | 5- | 2.21 | 0.99 | 2.19 | | | |
| | 65739-65749 | | 840 | 4 | 15 | 88 | 0.86 | | | | | | | | | | | | 5- | 2.01 | 0.31 | 2.75 | | | |
| | 65750-65759 | | 720 | 4 | 15 | 154 | 0.80 | | | | | | | | | | | | 5- | 1.98 | 0.39 | 2.43 | | | |
| | 65760-65769 | | 600 | 7 | 21 | 156 | 0.77 | | | | | | | | | | | | 10 | 2.00 | 0.39 | 2.35 | | | |
| | 65770-65779 | | 460 | 1 | 25 | 161 | 0.87 | | | | | | | | | | | | 14 | 1.91 | 0.44 | 2.43 | | | |
| | 65780-65788 | | 600 | 14 | 23 | 163 | 0.83 | | | | | | | | | | | | 5- | 2.00 | 0.40 | 2.09 | | | |
| | 65789-65796 | | 280 | 10 | 10 | 121 | 1.04 | | | | | | | | | | | | 5- | 1.73 | 0.44 | 2.32 | | | |
| | 65797-65806 | | 520 | 11 | 13 | 155 | 0.97 | | | | | | | | | | | | 5- | 1.72 | 0.53 | 2.66 | | | |
| | 65807-65816 | | 680 | 6 | 14 | 130 | 0.76 | | | | | | | | | | | | 6 | 1.67 | 0.44 | 2.33 | | | |
| | 65817-65824 | | 740 | 38 | 15 | 296 | 0.44 | | | | | | | | | | | | 5 | 0.93 | 0.41 | 1.43 | | | |
| | 65825-65834 | | 600 | 79 | 12 | 206 | 0.66 | | | | | | | | | | | | 15 | 1.87 | 0.40 | 2.28 | | | |
| | 65835-65844 | | 620 | 2 | 12 | 200 | 1.03 | | | | | | | | | | | | 14 | 2.51 | 0.61 | 2.76 | | | |
| | 65845-65849 | | 540 | 4 | 13 | 164 | 0.77 | | | | | | | | | | | | 9 | 1.85 | 0.44 | 1.94 | | | |
| | 65850-65856 | | 1240 | 6 | 14 | 143 | 1.38 | | | | | | | | | | | | 7 | 1.58 | 0.92 | 1.70 | | | |

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 1.

Date: January 22/81 Page 5 of 7

Venture: _____

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | | | | | |
|-----------|-------------|------------|--|----|-----|-----|----|----|----|------|-------|------|---|----|--|--|
| | | | Mo | Cu | Zn | Pb | Cd | Ni | Co | Ag | Au | U | V | W | | |
| | | | 16 17 20 21 25 26 30 31 35 36 40 41 45 46 50 51 55 56 60 61 65 66 70 71 75 76 80 | | | | | | | | | | | | | |
| A | 65857-65866 | 0222 | 450 | 18 | 33 | 21 | | 12 | 6 | 0.44 | 0.02- | 13.5 | | 17 | | |
| | 65867-65878 | | 330 | 15 | 30 | 20 | | 13 | 7 | 0.19 | 0.02- | 12.8 | | 18 | | |
| | 65879-65882 | | 800 | 37 | 490 | 470 | | 11 | 6 | 2.57 | 0.02- | 21 | | 70 | | |
| | 65883-65893 | | 630 | 9 | 67 | 43 | | 12 | 8 | 0.84 | 0.02- | 7.5 | | 45 | | |
| | 65894-65900 | | 19 | 6 | 35 | 5 | | 10 | 5 | 0.04 | 0.02- | 7.5 | | 15 | | |
| | 65901-65910 | | 37 | 6 | 46 | 10 | | 9 | 6 | 0.09 | 0.02- | 5- | | 44 | | |
| | 65911065920 | | 100 | 6 | 25 | 7 | | 10 | 6 | 0.09 | 0.02- | 5- | | 20 | | |
| | 65921-65932 | | 420 | 6 | 33 | 15 | | 13 | 6 | 0.25 | 0.02- | 9.0 | | 21 | | |
| | 65933-65944 | | 280 | 6 | 33 | 6 | | 9 | 7 | 0.05 | 0.02- | 24 | | 18 | | |
| | 65945-65956 | | 140 | 8 | 21 | 7 | | 10 | 4 | 0.04 | 0.02- | 22 | | 12 | | |
| | 65957-65966 | | 310 | 18 | 24 | 16 | | 12 | 4 | 0.13 | 0.02- | 16.6 | | 5- | | |
| | 66051-66059 | | 130 | 13 | 50 | 63 | | 16 | 9 | 1.27 | 0.02- | 21 | | 33 | | |
| | 66060-66072 | | 260 | 17 | 50 | 81 | | 11 | 8 | 1.72 | 0.02- | 15.0 | | 18 | | |
| | 66073-66077 | | 130 | 11 | 26 | 16 | | 11 | 6 | 0.42 | 0.02- | 19.0 | | 34 | | |
| | 66078-66087 | | 170 | 11 | 30 | 17 | | 11 | 5 | 0.46 | 0.02- | 21 | | 50 | | |
| | 66088-66097 | | 230 | 14 | 36 | 15 | | 14 | 8 | 0.47 | 0.02- | 27 | | 59 | | |
| | 66098-66107 | | 260 | 25 | 39 | 7 | | 15 | 8 | 0.48 | 0.02- | 25 | | 67 | | |
| | 66108-66113 | | 140 | 30 | 113 | 34 | | 13 | 7 | 1.35 | 0.02- | 23 | | 66 | | |
| | 65967-65979 | | 120 | 13 | 18 | 7 | | 14 | 7 | 0.05 | 0.02- | 15.0 | | 10 | | |
| | 65980-65990 | | 190 | 11 | 17 | 6 | | 14 | 6 | 0.04 | 0.02- | 12.6 | | 16 | | |
| | 65991-66001 | | 600 | 14 | 20 | 5 | | 10 | 5 | 0.37 | 0.02- | 16.6 | | 14 | | |
| | 66002-66012 | | 190 | 20 | 18 | 9 | | 10 | 8 | 0.30 | 0.02- | 9.5 | | 6 | | |
| | 66013-66022 | | 270 | 10 | 15 | 6 | | 11 | 5 | 0.12 | 0.02- | 5- | | 11 | | |
| | 66023-66032 | | 850 | 13 | 24 | 10 | | 13 | 7 | 0.28 | 0.02- | 5- | | 14 | | |
| | 66033-66044 | | 440 | 17 | 23 | 10 | | 16 | 7 | 0.43 | 0.02- | 9.5 | | 14 | | |

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R. Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 2.

Date: January 22/81 Page 5 of 7

Venture: _____

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | PPB | % | | PPM | | | | | | | | | | | | | |
|-----------|-------------|------------|-------|-----|----|-----|------|----|----|--------|----|----|------|------|------|----|----|----|----|----|----|----|--|
| | | | F | As | Bi | Mn | Fe | Hg | Ba | L.O.I. | Sn | Na | Ca | K | | | | | | | | | |
| 1 | 2 | 16 | 17 | 20 | 21 | 23 | 26 | 30 | 31 | 35 | 36 | 40 | 41 | 45 | 46 | 50 | 51 | 53 | 54 | 60 | 61 | 80 | |
| A | 65857-65866 | 0222 | 2200 | 40 | 12 | 133 | 0.63 | | | | | 5- | 1.27 | 0.27 | 1.94 | | | | | | | | |
| | 65867-65878 | | 1280 | 81 | 14 | 213 | 0.73 | | | | | 5 | 0.95 | 0.55 | 1.87 | | | | | | | | |
| | 65879-65882 | | 1320 | 610 | 22 | 286 | 0.41 | | | | | 5- | 1.10 | 0.26 | 2.30 | | | | | | | | |
| | 65883-65893 | | 2400 | 12 | 22 | 275 | 0.39 | | | | | 5- | 1.03 | 0.27 | 1.13 | | | | | | | | |
| | 65894-65900 | | 2400 | 9 | 13 | 133 | 0.79 | | | | | 21 | 1.98 | 0.34 | 2.14 | | | | | | | | |
| | 65901-65910 | | 2800 | 2 | 11 | 102 | 0.71 | | | | | 9 | 1.90 | 0.34 | 2.13 | | | | | | | | |
| | 65911065920 | | 2200 | 5 | 13 | 119 | 0.56 | | | | | 5- | 1.59 | 0.26 | 2.20 | | | | | | | | |
| | 65921-65932 | | 1800 | 2 | 12 | 114 | 0.79 | | | | | 20 | 1.90 | 0.38 | 2.55 | | | | | | | | |
| | 65933-65944 | | 2000 | 7 | 10 | 89 | 0.68 | | | | | 8 | 1.77 | 0.27 | 1.24 | | | | | | | | |
| | 65945-65956 | | 2200 | 6 | 12 | 86 | 0.75 | | | | | 5- | 1.98 | 0.36 | 2.10 | | | | | | | | |
| | 65957-65966 | | 1320 | 20 | 16 | 257 | 0.73 | | | | | 5- | 1.49 | 0.83 | 1.85 | | | | | | | | |
| | 66051-66059 | | 2400 | 47 | 21 | 198 | 0.82 | | | | | 5- | 1.75 | 0.39 | 1.65 | | | | | | | | |
| | 66060-66072 | | 2000 | 19 | 20 | 284 | 0.79 | | | | | 5- | 2.35 | 0.45 | 2.20 | | | | | | | | |
| | 66073-66077 | | 880 | 7 | 12 | 207 | 0.82 | | | | | 7 | 1.88 | 0.38 | 1.55 | | | | | | | | |
| | 66078-66087 | | 880 | 2 | 13 | 205 | 0.61 | | | | | 5- | 2.28 | 0.33 | 2.42 | | | | | | | | |
| | 66088-66097 | | 880 | 9 | 17 | 229 | 0.56 | | | | | 5 | 2.21 | 0.22 | 2.77 | | | | | | | | |
| | 66098-66107 | | 840 | 2 | 18 | 199 | 0.86 | | | | | 5 | 2.10 | 0.35 | 2.10 | | | | | | | | |
| | 66108-66113 | | 920 | 6 | 19 | 210 | 0.91 | | | | | 5- | 2.33 | 0.34 | 1.97 | | | | | | | | |
| | 65967-65979 | | 1320 | 5 | 13 | 84 | 0.83 | | | | | 5- | 2.12 | 0.34 | 2.45 | | | | | | | | |
| | 65980-65990 | | 2200 | 4 | 12 | 92 | 0.90 | | | | | 5- | 2.38 | 0.44 | 2.68 | | | | | | | | |
| | 65991-66001 | | 2200 | 6 | 11 | 67 | 0.80 | | | | | 5- | 2.36 | 0.35 | 2.30 | | | | | | | | |
| | 66002-66012 | | 840 | 12 | 11 | 100 | 0.88 | | | | | 5- | 1.74 | 0.57 | 2.36 | | | | | | | | |
| | 66013-66022 | | 440 | 6 | 13 | 134 | 0.76 | | | | | 5- | 1.71 | 0.60 | 2.88 | | | | | | | | |
| | 66023-66032 | | 500 | 9 | 13 | 193 | 0.86 | | | | | 5- | 1.72 | 0.49 | 2.58 | | | | | | | | |
| | 66033-66044 | | 520 | 3 | 15 | 145 | 0.88 | | | | | 8 | 1.88 | 0.62 | 2.74 | | | | | | | | |

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 2.

Venture: _____

Date: January 22/81 Page 6 of 7

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | | | | | P P B | | % | | PPM | | | |
|-----------|-------------|------------|-------|-----|----|-----|------|----|----|--------|----|----|----|----|----|-------|----|----|----|-----|------|------|------|
| | | | F | As | Bi | Mn | Fe | Hg | Ba | L.O.I. | Sn | Na | Ca | K | | | | | | | | | |
| 1 | 2 | 16 | 17 | 20 | 21 | 25 | 26 | 30 | 31 | 35 | 36 | 40 | 41 | 45 | 46 | 50 | 51 | 55 | 56 | 60 | 61 | 80 | |
| A | 66114-66122 | 0222 | 3400 | 24 | 15 | 72 | 0.81 | | | | | | | | | | | | | 5- | 1.51 | 0.45 | 1.95 |
| | 66123-66132 | | 3600 | 18 | 17 | 138 | 0.65 | | | | | | | | | | | | | 24 | 1.69 | 0.31 | 2.42 |
| | 66133-66142 | | 2600 | 110 | 16 | 307 | 0.67 | | | | | | | | | | | | | 5- | 1.74 | 0.24 | 2.13 |
| | 66143-66152 | | 3800 | 61 | 14 | 387 | 0.73 | | | | | | | | | | | | | 5- | 1.74 | 0.28 | 2.75 |
| | 66153-66158 | | 2800 | 11 | 17 | 108 | 0.63 | | | | | | | | | | | | | 5- | 2.05 | 0.32 | 2.73 |
| | 66159-66170 | | 2800 | 250 | 20 | 325 | 0.80 | | | | | | | | | | | | | 5- | 1.25 | 0.53 | 2.50 |
| | 66171-66177 | | 1320 | 14 | 20 | 341 | 0.93 | | | | | | | | | | | | | 5- | 1.48 | 0.75 | 2.19 |
| | 66178-66187 | | 1020 | 12 | 21 | 190 | 0.86 | | | | | | | | | | | | | 5- | 2.29 | 0.38 | 2.32 |
| | 66188-66195 | | 2800 | 21 | 14 | 200 | 0.62 | | | | | | | | | | | | | 5- | 2.07 | 0.22 | 2.82 |
| | 66196-66205 | | 2400 | 24 | 13 | 149 | 0.71 | | | | | | | | | | | | | 5- | 1.40 | 0.27 | 2.73 |
| | 66206-66212 | | 2600 | 580 | 16 | 326 | 0.75 | | | | | | | | | | | | | 5- | 1.21 | 0.37 | 2.84 |
| | 66213-66215 | | 920 | 13 | 18 | 239 | 0.76 | | | | | | | | | | | | | 5- | 1.59 | 0.46 | 2.39 |
| | 66217-66255 | | 2000 | 6 | 12 | 88 | 0.80 | | | | | | | | | | | | | 5- | 1.92 | 0.32 | 1.96 |
| | 66256-66264 | | 2000 | 4 | 14 | 84 | 0.75 | | | | | | | | | | | | | 5- | 2.20 | 0.29 | 2.64 |
| | 66265-66275 | | 1960 | 4 | 15 | 75 | 1.10 | | | | | | | | | | | | | 5- | 2.00 | 0.55 | 2.30 |
| | 66276-66285 | | 1880 | 3 | 14 | 70 | 0.81 | | | | | | | | | | | | | 5- | 1.79 | 0.38 | 2.52 |
| | 66285-66295 | | 1020 | 3 | 20 | 126 | 1.20 | | | | | | | | | | | | | 5- | 1.60 | 0.95 | 2.40 |
| | 66295-66305 | | 960 | 3 | 15 | 111 | 1.02 | | | | | | | | | | | | | 5- | 1.94 | 0.65 | 2.62 |
| | 66306-66315 | | 700 | 2 | 15 | 97 | 0.85 | | | | | | | | | | | | | 5- | 2.18 | 0.43 | 2.08 |
| | 66226-66235 | | 1960 | 6 | 13 | 92 | 5.50 | | | | | | | | | | | | | 5- | 2.20 | 0.55 | 1.70 |
| | 66236-66245 | | 2200 | 4 | 12 | 77 | 4.50 | | | | | | | | | | | | | 5- | 2.10 | 0.45 | 2.10 |
| | 66246-66250 | | 2200 | 4 | 10 | 86 | 0.70 | | | | | | | | | | | | | 5- | 2.20 | 0.32 | 1.80 |
| | 66326-66331 | | 2400 | 4 | 9 | 68 | 2.90 | | | | | | | | | | | | | 5- | 2.30 | 0.29 | 1.50 |
| | 66332-66341 | | 2400 | 4 | 9 | 76 | 0.70 | | | | | | | | | | | | | 5- | 2.30 | 0.34 | 2.10 |
| | 66342-66351 | | 2400 | 6 | 8 | 94 | 0.70 | | | | | | | | | | | | | 5- | 1.90 | 0.39 | 2.10 |

Area: Adanac

PLACER DEVELOPMENT LIMITED

Geologist: R Pinsent

Map Sheet No.: _____

Geochemistry Analysis Sheet No. 1.

Venture: _____

Date: January 22/81 Page 7 of 7

| Card Type | SAMPLE No. | Lab. Proj. | P P M | | | | | | | | | | | | | |
|-----------|-------------|-------------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|----|--|--|
| | | | Mo | Cu | Zn | Pb | Cd | Ni | Co | Ag | Au | U | V | W | | |
| 1 | 2 | 16 17 20 21 | 25 26 | 30 31 | 35 36 | 40 41 | 45 46 | 50 51 | 55 56 | 60 61 | 65 66 | 70 71 | 75 76 | 80 | | |
| A | 66352-66361 | 0222 | 4000 | 6 | 20 | 6 | | 13 | 4 | 0.04 | 0.02- | 21 | | 16 | | |
| | 66362-66371 | | 330 | 10 | 44 | 23 | | 13 | 6 | 0.15 | 0.02- | 15.8 | | 23 | | |
| | 66372-66381 | | 630 | 18 | 31 | 13 | | 15 | 5 | 0.21 | 0.02- | 19.8 | | 23 | | |
| | 66382-66391 | | 950 | 15 | 44 | 15 | | 16 | 5 | 0.17 | 0.02- | 16.6 | | 23 | | |
| | 66392-66401 | | 530 | 6 | 22 | 10 | | 14 | 7 | 0.09 | 0.02- | 22 | | 36 | | |
| | 66402-66414 | | 730 | 8 | 18 | 10 | | 12 | 5 | 0.10 | 0.02- | 17.4 | | 13 | | |
| | 66415-66424 | | 12 | 10 | 35 | 12 | | 13 | 7 | 0.12 | 0.02- | 17.4 | | 11 | | |
| | 66425-66433 | | 12 | 15 | 142 | 64 | | 12 | 8 | 0.53 | 0.02- | 11.9 | | 9 | | |
| | 66434-66442 | | 11 | 5 | 168 | 81 | | 14 | 7 | 0.57 | 0.03 | 12.6 | | 24 | | |
| | 66443-66452 | | 32 | 47 | 24 | 9 | | 15 | 7 | 0.19 | 0.02- | 23.7 | | 28 | | |
| | 66453-66462 | | 20 | 17 | 24 | 5 | | 12 | 6 | 0.11 | 0.02- | 19.0 | | 16 | | |
| | 66463-66466 | | 29 | 27 | 31 | 8 | | 9 | 7 | 0.27 | 0.02- | 12.6 | | 26 | | |
| | 66467-66478 | | 24 | 21 | 19 | 5 | | 19 | 5 | 0.15 | 0.02- | 19.0 | | 19 | | |
| | 66549-66482 | | 68 | 19 | 26 | 19 | | 13 | 8 | 0.42 | 0.02- | 11.1 | | 30 | | |
| | 66483-66492 | | 770 | 26 | 12 | 20 | | 13 | 5 | 0.42 | 0.02- | 9.5 | | 34 | | |
| | 66493-66500 | | 51 | 15 | 21 | 7 | | 12 | 5 | 0.15 | 0.02- | 11.1 | | 34 | | |
| | 66501-66510 | | 4 | 8 | 23 | 8 | | 10 | 4 | 0.14 | 0.02- | 14.2 | | 15 | | |
| | 66511-66520 | | 5 | 11 | 17 | 5 | | 8 | 6 | 0.18 | 0.02- | 17.4 | | 23 | | |
| | 66521-66530 | | 12 | 8 | 27 | 7 | | 12 | 3 | 0.16 | 0.02- | 15.8 | | 14 | | |
| | 66531-66540 | | 15 | 14 | 51 | 50 | | 12 | 7 | 0.25 | 0.02- | 15.8 | | 40 | | |
| | 66541-66548 | | 19 | 12 | 36 | 18 | | 11 | 7 | 0.23 | 0.02- | 22 | | 50 | | |
| | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | |

GEOCHEMICAL DATA LISTING: LINA RANGE R. PINSENT
 FILE: P1011-B

DATE: 81-03-30

AREA: LINA RANGE
 MAPSHEET NO: 104 N
 VENTURE: *
 GEOLOGIST: R. PINSENT
 LAB PROJECT NO: 1011

REMARKS: PLEASE DISTRIBUTE RESULTS TO: R. PINSENT P. BRADSHAW
 S. TENNANT T. DOUGLAS
 J. HYLANDS

STANDARD ANALYSIS METHODS USED BY PDL GEOCHEM LAB ARE LISTED BELOW:
 ALL RESULTS EXPRESSED AS INDICATED IN UNITS COLUMN BELOW
 ANY EXCEPTIONS FOR THIS PROJECT ARE NOTED ABOVE

| | UNITS | WT.G | ATTACK | USED | TIME | RANGE | METHOD |
|-----|-------|------|-------------|-------------------|-------|-----------|------------------------|
| MO | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 1-1000 | ATOMIC ABSORPTION |
| CU | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-4000 | ATOMIC ABSORPTION |
| ZN | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-3000 | ATOMIC ABSORPTION |
| PB | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-3000 | A.A. BACKGROUND COR. |
| CD | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 0.2-200 | A.A. BACKGROUND COR. |
| NI | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-2000 | ATOMIC ABSORPTION |
| CO | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-2000 | ATOMIC ABSORPTION |
| AG1 | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 0.2-20 | A.A. BACKGROUND COR |
| AG2 | PPM | 0.5 | C | HN03 | 2HRS | 0.02-4.00 | A.A. SOLVENT EXTRACT |
| AU | PPM | 3.0 | C | HBR/BR | 12HRS | 0.02-4.00 | A.A. SOLVENT EXTRACT |
| U | PPM | 0.25 | DIL | HN03 | 2HRS | 0.5-1000 | FLUORIMETRY SOLV. EX. |
| V | PPM | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 5-1000 | ATOMIC ABSORPTION |
| W | PPM | 1.0 | C | HF/HN03/HCL/H2S04 | 4HRS | 5-500 | A.A. SOLVENT EXTRACT. |
| F | PPM | 0.25 | NA2CO3/KNO3 | FUSION | 30MIN | 40-4000 | SPECIFIC ION ELECTODE |
| AS | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-1000 | A.A. HYDRIDE GENERATOR |
| BI | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-2000 | ATOMIC ABSORPTION |
| MN | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-3000 | ATOMIC ABSORPTION |
| FE | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.02-20% | ATOMIC ABSORPTION |
| HG | PPB | 0.5 | DIL | HN03 | 2HRS | 5-2000PPB | A.A. COLD VAPOR GEN. |
| BA | % | 0.5 | C | HF/HI/OXALIC | 4HRS | 0.02-20% | ATOMIC ABSORPTION |
| NA | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.2 -20% | ATOMIC ABSORPTION |
| K | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.2 -20% | ATOMIC ABSORPTION |
| CA | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.02-20% | ATOMIC ABSORPTION |
| SR | PPM | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 10-2000 | ATOMIC ABSORPTION |
| MG | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.2-20% | ATOMIC ABSORPTION |
| SN | PPM | 1.0 | NH4I | FUSION | 15MIN | 2-500 | A.A. SOLVENT EXTRACT. |
| LOI | % | 1.0 | ASH | 600 DEG C | 2HRS | 0.02-99% | WEIGH RESDUE |

| NTS | SAMPLE | PROJECT | MO | CU | ZN | PB | NI | CO | AG | AU | U | W | F | BI | MN | FE | SN |
|---------------|--------|---------|-----|-----|-----|----|----|------|-------|-------|------|------|------|-----|-----|-----|----|
| Ruby Mt. | 62348 | | 14 | 2 | 29 | 6 | 8 | 3 | 0.13 | <0.02 | 11.9 | 6 | 920 | 5 | 54 | 0.7 | <5 |
| | 62349 | | 18 | 9 | 97 | 34 | 7 | 2 | 0.85 | <0.02 | <0.5 | <5 | 176 | 3 | 280 | 0.5 | 8 |
| | 62521 | | 13 | 6 | 39 | 14 | 15 | 8 | 0.16 | <0.02 | 0.7 | <5 | 300 | 18 | 278 | 1.7 | <5 |
| | 62522 | | 10 | 6 | 41 | 4 | 13 | 9 | 0.15 | <0.02 | 0.7 | 7 | 220 | 12 | 253 | 2.0 | <5 |
| | 62523 | | 23 | 22 | 23 | 1 | 12 | 8 | 1.25 | <0.02 | 1.1 | <5 | 280 | 19 | 113 | 3.2 | <5 |
| | 62524 | | 12 | 6 | 17 | 5 | 11 | 4 | 0.24 | 0.40 | <0.5 | <5 | 196 | 8 | 106 | 0.8 | 6 |
| | 62525 | | 26 | 6 | 5 | 6 | 14 | 2 | 0.17 | <0.02 | <0.5 | <5 | 20 | 3 | 36 | 0.6 | <5 |
| Volcanic Cr. | 69501 | | 7 | 6 | 62 | 48 | 35 | 21 | 0.16 | <0.02 | 3.7 | <5 | 196 | 24 | 208 | 6.0 | <5 |
| | 69502 | | 2 | 9 | 80 | 74 | 20 | 12 | 0.41 | <0.02 | <0.5 | 6 | 300 | 19 | 141 | 6.0 | <5 |
| | 69503 | | 3 | 159 | 62 | 18 | 16 | 10 | 0.42 | 0.02 | <0.5 | <5 | 460 | 10 | 74 | 2.8 | <5 |
| | 69504 | 0.19% | 20 | 54 | 9 | 31 | 19 | 0.13 | 0.02 | <0.5 | 5 | 1580 | 18 | 276 | 7.0 | <5 | |
| | 69505 | | 41 | 53 | 41 | 23 | 8 | 6 | 0.73 | <0.02 | 5.2 | <5 | 136 | 8 | 81 | 0.5 | <5 |
| | 69506 | | 17 | 106 | 113 | 10 | 36 | 28 | 0.44 | <0.02 | 5.2 | <5 | 400 | 54 | 585 | 5.0 | <5 |
| | 69507 | | 10 | 77 | 61 | 14 | 17 | 15 | 0.22 | <0.02 | 4.5 | 5 | 500 | 33 | 282 | 5.0 | <5 |
| | 69508 | | 18 | 42 | 32 | 10 | 7 | 7 | 0.29 | <0.02 | 3.4 | 12 | 140 | 9 | 119 | 0.9 | <5 |
| | 69509 | | 110 | 77 | 65 | 10 | 17 | 22 | 0.23 | <0.02 | 0.7 | <5 | 920 | 24 | 404 | 6.0 | <5 |
| | 69510 | 0.52% | 238 | 61 | 21 | 14 | 24 | 1.14 | <0.02 | <0.5 | 22 | 1180 | 25 | 480 | 5.0 | 7 | |
| | 69511 | | 16 | 29 | 103 | 11 | 27 | 33 | 0.12 | <0.02 | 3.0 | <5 | 600 | 30 | 314 | 8.0 | <5 |
| | 69512 | | 18 | 18 | 64 | 21 | 13 | 21 | 0.13 | <0.02 | 1.1 | <5 | 300 | 21 | 340 | 5.0 | <5 |
| Fire Mt. | 69513 | | 29 | 23 | 84 | 11 | 15 | 12 | 0.19 | <0.02 | 0.9 | 27 | 720 | 15 | 47 | 1.8 | 9 |
| | 69514 | | 110 | 37 | 28 | 20 | 16 | 3 | 0.33 | <0.02 | <5 | 9 | 800 | 7 | 24 | 0.7 | <5 |
| | 69515 | | 78 | 13 | 27 | 9 | 22 | 4 | 0.13 | <0.02 | <5 | 6 | 1200 | 6 | 41 | 0.6 | <5 |
| | 69516 | | 3 | 375 | 13 | 8 | 46 | 18 | 0.26 | 0.02 | <5 | <5 | 100 | 18 | 156 | 6.0 | <5 |
| | 69517 | | 3 | 162 | 9 | 16 | 23 | 10 | 0.19 | 0.02 | <5 | <5 | 58 | 24 | 255 | 3.3 | <5 |
| | 69518 | | 2 | 118 | 10 | 7 | 44 | 19 | 0.14 | <0.02 | <5 | <5 | 68 | 19 | 168 | 5.0 | 5 |
| | 69519 | 0.18% | 8 | 3 | 7 | 14 | 2 | 0.11 | <0.02 | <5 | 8 | 460 | 8 | 52 | 0.5 | 12 | |
| | 69520 | | 63 | 12 | 2 | 25 | 12 | 3 | 0.31 | <0.02 | <5 | 11 | 860 | 6 | 33 | 0.4 | 6 |
| | 69521 | 0.08% | 7 | 13 | 9 | 17 | 3 | 0.06 | <0.02 | <5 | <5 | 220 | 7 | 39 | 0.5 | <5 | |
| Steamboat Mt. | 69522 | | 12 | 35 | 24 | 11 | 14 | 5 | 0.07 | <0.02 | <5 | <5 | 250 | 13 | 123 | 1.3 | <5 |
| | 69523 | | 15 | 135 | 56 | 36 | 15 | 9 | 0.64 | <0.02 | <5 | 10 | 200 | 15 | 211 | 1.4 | <5 |
| | 69524 | | 11 | 27 | 31 | 23 | 13 | 6 | 0.15 | <0.02 | <5 | <5 | 180 | 13 | 253 | 1.6 | <5 |
| | 69525 | 0.06% | 22 | 81 | 36 | 16 | 10 | 0.26 | <0.02 | <5 | <5 | 180 | 22 | 470 | 1.9 | <5 | |
| | 69526 | 0.40% | 8 | 19 | 17 | 13 | 5 | 0.11 | <0.02 | <5 | 9 | 260 | 8 | 97 | 0.7 | <5 | |
| | 69527 | | 33 | 7 | 19 | 13 | 11 | 6 | 0.09 | <0.02 | <5 | 7 | 180 | 11 | 146 | 1.1 | 6 |
| | 69528 | | 23 | 86 | 30 | 14 | 15 | 5 | 0.17 | <0.02 | <5 | <5 | 220 | 14 | 134 | 1.9 | <5 |
| | 69529 | | 7 | 30 | 12 | 6 | 9 | 4 | 0.11 | <0.02 | 8.0 | <5 | 320 | 11 | 51 | 1.7 | <5 |
| | 69530 | | 11 | 75 | 33 | 14 | 29 | 9 | 0.08 | <0.02 | <5 | <5 | 540 | 18 | 148 | 2.4 | <5 |
| | 69531 | | 9 | 25 | 15 | 10 | 11 | 9 | 0.11 | <0.02 | <5 | <5 | 215 | 13 | 95 | 2.2 | <5 |
| | 69532 | | 6 | 22 | 9 | 10 | 9 | 5 | 0.09 | <0.02 | <5 | 6 | 156 | 13 | 74 | 1.9 | <5 |
| | 69533 | | 8 | 44 | 21 | 15 | 13 | 6 | 0.21 | <0.02 | <5 | 60 | 100 | 12 | 196 | 1.6 | <5 |
| | 69534 | | 4 | 123 | 20 | 13 | 33 | 9 | 0.13 | <0.02 | <5 | 28 | 280 | 20 | 122 | 3.1 | <5 |
| | 69535 | | 3 | 163 | 20 | 10 | 58 | 15 | 0.23 | <0.02 | <5 | 13 | 900 | 24 | 192 | 3.9 | <5 |

END OF LISTING - 42 RECORDS PRINTED
 GCLIST RUN AT: 11:43:30 CPU USED: 1.38 SECONDS

GEOCHEMICAL DATA LISTING: CLOUD R. PINSENT
 FILE: P1008-B

DATE: 81-03-30

AREA: CLOUD
 MAPSHEET NO: 105 D
 VENTURE: *
 GEOLOGIST: R. PINSENT
 LAB PROJECT NO: 1008

REMARKS: PLEASE DISTRIBUTE RESULTS TO: R. PINSENT / P. BRADSHAW
 S. TENNANT ✓ T. DOUGLAS
 J. HYLANDS

STANDARD ANALYSIS METHODS USED BY PDL GEOCHEM LAB ARE LISTED BELOW:
 ALL RESULTS EXPRESSED AS INDICATED IN UNITS COLUMN BELOW
 ANY EXCEPTIONS FOR THIS PROJECT ARE NOTED ABOVE

| | UNITS | WT.G | ATTACK | USED | TIME | RANGE | METHOD |
|-----|-------|------|-------------|-------------------|-------|-----------|------------------------|
| MO | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 1-1000 | ATOMIC ABSORPTION |
| CU | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-4000 | ATOMIC ABSORPTION |
| ZN | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-3000 | ATOMIC ABSORPTION |
| PB | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-3000 | A.A. BACKGROUND COR. |
| CD | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 0.2-200 | A.A. BACKGROUND COR. |
| NI | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-2000 | ATOMIC ABSORPTION |
| CO | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-2000 | ATOMIC ABSORPTION |
| AG1 | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 0.2-20 | A.A. BACKGROUND COR |
| AG2 | PPM | 0.5 | C | HN03 | 2HRS | 0.02-4.00 | A.A. SOLVENT EXTRACT |
| AU | PPM | 3.0 | C | HBR/BR | 12HRS | 0.02-4.00 | A.A. SOLVENT EXTRACT |
| U | PPM | 0.25 | DIL | HN03 | 2HRS | 0.5-1000 | FLUORIMETRY SOLV. EX. |
| V | PPM | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 5-1000 | ATOMIC ABSORPTION |
| W | PPM | 1.0 | C | HF/HN03/HCL/H2SO4 | 4HRS | 5-500 | A.A. SOLVENT EXTRACT. |
| F | PPM | 0.25 | NA2CO3/KN03 | FUSION | 30MIN | 40-4000 | SPECIFIC ION ELECTODE |
| AS | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-1000 | A.A. HYDRIDE GENERATOR |
| BI | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-2000 | ATOMIC ABSORPTION |
| MN | PPM | 0.5 | C | HCL04/HN03 | 4HRS | 2-3000 | ATOMIC ABSORPTION |
| FE | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.02-20% | ATOMIC ABSORPTION |
| HG | PPB | 0.5 | DIL | HN03 | 2HRS | 5-2000PPB | A.A. COLD VAPOR GEN. |
| BA | % | 0.5 | C | HF/HI/OXALIC | 4HRS | 0.02-20% | ATOMIC ABSORPTION |
| NA | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.2 -20% | ATOMIC ABSORPTION |
| K | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.2 -20% | ATOMIC ABSORPTION |
| CA | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.02-20% | ATOMIC ABSORPTION |
| SR | PPM | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 10-2000 | ATOMIC ABSORPTION |
| MG | % | 0.5 | C | HF/HCL04/HN03/HCL | 6HRS | 0.2-20% | ATOMIC ABSORPTION |
| SN | PPM | 1.0 | NH4I | FUSION | 15MIN | 2-500 | A.A. SOLVENT EXTRACT. |
| LOI | % | 1.0 | ASH | 600 DEG C | 2HRS | 0.02-99% | WEIGH RESDUE |

| NTS | SAMPLE | PROJECT | MO | CU | ZN | PB | NI | CO | AG | AU | U | W | F | BI | MN | FE | SN |
|-------|--------|---------|-------|----|----|----|----|----|------|-------|-----|----|-----|----|-----|-----|----|
| Cloud | 62345 | 1008 | 0.36% | 16 | 28 | 10 | 11 | 4 | 0.20 | <0.02 | 5.5 | <5 | 240 | 12 | 291 | 1.2 | 9 |
| | 62346 | 1008 | 48 | 3 | 24 | 16 | 14 | 4 | 0.09 | <0.02 | 9.5 | <5 | 200 | 11 | 234 | 1.1 | <5 |
| | 62347 | 1008 | 0.23% | 7 | 13 | 89 | 11 | 3 | 2.48 | <0.02 | <5 | <5 | 120 | 55 | 37 | 0.6 | 6 |

END OF LISTING - 3 RECORDS PRINTED
 GCLIST RUN AT: 09:21:00 CPU USED: .54 SECONDS

GEOCHEMICAL DATA LISTING: RED CLAIMS R. PINSENT
 FILE: P1010-B

DATE: 81-03-30

AREA: RED CLAIMS
 MAPSHEET NO: 104 N
 VENTURE: *
 GEOLOGIST: R. PINSENT
 LAB PROJECT NO: 1010

REMARKS: PLEASE DISTRIBUTE RESULTS TO: R. PINSENT / P. BRADSHAW
 S. TENNANT / T. DOUGLAS
 J. HYLANDS

STANDARD ANALYSIS METHODS USED BY PDL GEOCHEM LAB ARE LISTED BELOW:
 ALL RESULTS EXPRESSED AS INDICATED IN UNITS COLUMN BELOW
 ANY EXCEPTIONS FOR THIS PROJECT ARE NOTED ABOVE

| | UNITS | WT.G | ATTACK USED | TIME | RANGE | METHOD |
|-----|-------|------|---------------------|-------|-----------|------------------------|
| MO | PPM | 0.5 | C HCL04/HN03 | 4HRS | 1-1000 | ATOMIC ABSORPTION |
| CU | PPM | 0.5 | C HCL04/HN03 | 4HRS | 2-4000 | ATOMIC ABSORPTION |
| ZN | PPM | 0.5 | C HCL04/HN03 | 4HRS | 2-3000 | ATOMIC ABSORPTION |
| PB | PPM | 0.5 | C HCL04/HN03 | 4HRS | 2-3000 | A.A. BACKGROUND COR. |
| CD | PPM | 0.5 | C HCL04/HN03 | 4HRS | 0.2-200 | A.A. BACKGROUND COR. |
| NI | PPM | 0.5 | C HCL04/HN03 | 4HRS | 2-2000 | ATOMIC ABSORPTION |
| CO | PPM | 0.5 | C HCL04/HN03 | 4HRS | 2-2000 | ATOMIC ABSORPTION |
| AG1 | PPM | 0.5 | C HCL04/HN03 | 4HRS | 0.2-20 | A.A. BACKGROUND COR |
| AG2 | PPM | 0.5 | C HN03 | 2HRS | 0.02-4.00 | A.A. SOLVENT EXTRACT |
| AU | PPM | 3.0 | C HBR/BR | 12HRS | 0.02-4.00 | A.A. SOLVENT EXTRACT |
| U | PPM | 0.25 | DIL HN03 | 2HRS | 0.5-1000 | FLUORIMETRY SOLV. EX. |
| V | PPM | 0.5 | C HF/HCL04/HN03/HCL | 6HRS | 5-1000 | ATOMIC ABSORPTION |
| W | PPM | 1.0 | C HF/HN03/HCL/H2S04 | 4HRS | 5-500 | A.A. SOLVENT EXTRACT. |
| F | PPM | 0.25 | NA2C03/KN03 FUSION | 30MIN | 40-4000 | SPECIFIC ION ELECTODE |
| AS | PPM | 0.5 | C HCL04/HN03 | 4HRS | 2-1000 | A.A. HYDRIDE GENERATOR |
| BI | PPM | 0.5 | C HCL04/HN03 | 4HRS | 2-2000 | ATOMIC ABSORPTION |
| MN | PPM | 0.5 | C HCL04/HN03 | 4HRS | 2-3000 | ATOMIC ABSORPTION |
| FE | % | 0.5 | C HF/HCL04/HN03/HCL | 6HRS | 0.02-20% | ATOMIC ABSORPTION |
| HG | PPB | 0.5 | DIL HN03 | 2HRS | 5-2000PPB | A.A. COLD VAPOR GEN. |
| BA | % | 0.5 | C HF/HI/OXALIC | 4HRS | 0.02-20% | ATOMIC ABSORPTION |
| NA | % | 0.5 | C HF/HCL04/HN03/HCL | 6HRS | 0.2-20% | ATOMIC ABSORPTION |
| K | % | 0.5 | C HF/HCL04/HN03/HCL | 6HRS | 0.2-20% | ATOMIC ABSORPTION |
| CA | % | 0.5 | C HF/HCL04/HN03/HCL | 6HRS | 0.02-20% | ATOMIC ABSORPTION |
| SR | PPM | 0.5 | C HF/HCL04/HN03/HCL | 6HRS | 10-2000 | ATOMIC ABSORPTION |
| MG | % | 0.5 | C HF/HCL04/HN03/HCL | 6HRS | 0.2-20% | ATOMIC ABSORPTION |
| SN | PPM | 1.0 | NH4I FUSION | 15MIN | 2-500 | A.A. SOLVENT EXTRACT. |
| LOI | % | 1.0 | ASH 600 DEG C | 2HRS | 0.02-99% | WEIGH RESDUE |

| NTS | SAMPLE | PROJECT | MO | CU | ZN | PB | NI | CO | AG | AU | U | W | F | BI | MN | FE | SN |
|-----|--------|---------|-------|-----|-----|-----|----|----|------|-------|------|-----|------|----|------|-----|----|
| | 62502 | 1010 | 86 | 15 | 179 | 62 | 13 | 12 | 0.34 | <0.02 | <5 | <5 | 360 | 14 | 293 | 0.7 | 12 |
| | 62503 | 1010 | 180 | 16 | 208 | 73 | 11 | 8 | 0.34 | <0.02 | <5 | 7 | 380 | 16 | 244 | 0.8 | <5 |
| | 62504 | 1010 | 24 | 1 | 125 | 53 | 9 | 7 | 0.36 | <0.02 | 5.5 | 51 | 420 | 16 | 378 | 1.1 | 7 |
| | 62505 | 1010 | 76 | 1 | 340 | 460 | 14 | 11 | 0.45 | <0.02 | 1.9 | 11 | 320 | 14 | 252 | 1.2 | 9 |
| | 62506 | 1010 | 0.79% | 15 | 112 | 38 | 10 | 7 | 0.32 | 0.02 | 14.9 | 23 | 340 | 10 | 297 | 0.7 | <5 |
| | 62507 | 1010 | 70 | 70 | 82 | 990 | 12 | 10 | 7 | 0.02 | 6.7 | 24 | 300 | 15 | 42 | 1.3 | 8 |
| | 62508 | 1010 | 0.06% | 37 | 440 | 270 | 14 | 7 | 1.48 | 0.03 | 1.1 | 22 | 560 | 8 | 600 | 0.9 | 7 |
| | 62509 | 1010 | 0.08% | 56 | 900 | 510 | 15 | 10 | 3.20 | <0.02 | 4.1 | 21 | 500 | 13 | 740 | 1.4 | 5 |
| | 62510 | 1010 | 320 | 21 | 80 | 43 | 13 | 5 | 1.21 | <0.02 | 6.0 | 18 | 220 | 13 | 291 | 0.6 | <5 |
| | 62511 | 1010 | 14 | 56 | 40 | 144 | 12 | 6 | 1.27 | <0.02 | 3.0 | 34 | 160 | 12 | 203 | 1.3 | <5 |
| | 62512 | 1010 | 16 | 46 | 220 | 252 | 19 | 14 | 3.57 | <0.02 | 4.5 | 200 | 1220 | 32 | 1040 | 2.0 | 8 |
| | 62513 | 1010 | 230 | 111 | 213 | 116 | 14 | 6 | 3.42 | <0.02 | 3.7 | 7 | 420 | 9 | 64 | 1.2 | 7 |
| | 62514 | 1010 | 17 | 158 | 86 | 19 | 12 | 8 | 0.55 | <0.02 | 4.5 | <5 | 220 | 6 | 230 | 1.7 | 15 |
| | 62515 | 1010 | 11 | 40 | 44 | 51 | 10 | 6 | 0.53 | <0.02 | 5.2 | 6 | 1240 | 11 | 169 | 1.0 | 10 |
| | 62516 | 1010 | 0.31% | 14 | 123 | 217 | 9 | 4 | 0.72 | <0.02 | 1.1 | 12 | 260 | 6 | 379 | 0.5 | <5 |
| | 62517 | 1010 | 29 | 16 | 188 | 23 | 10 | 4 | 0.66 | <0.02 | 22 | <5 | 220 | 8 | 125 | 0.5 | 17 |
| | 62518 | 1010 | 69 | 23 | 200 | 255 | 15 | 7 | 0.36 | <0.02 | 1.1 | 28 | 340 | 14 | 298 | 1.1 | 11 |
| | 62519 | 1010 | 33 | 35 | 114 | 60 | 12 | 8 | 0.29 | <0.02 | <0.5 | 13 | 300 | 8 | 259 | 1.1 | 7 |
| | 62520 | 1010 | 150 | 17 | 125 | 130 | 12 | 5 | 0.99 | <0.02 | <0.5 | 15 | 400 | 9 | 112 | 0.6 | 6 |

END OF LISTING - 19 RECORDS PRINTED
 GCLIST RUN AT: 09:59:09 CPU USED: 1.03 SECONDS

*Red
M.H.*