



862492

TEL. (604) 763-1815
(604) 860-8525

Equity Silver Mines Ltd.
R. Pease Oct. 3, 1984

C.F. MINERAL RESEARCH LIMITED
263 LAKE AVENUE
KELOWNA, BRITISH COLUMBIA
CANADA V1Y 5W6

C.F.M. 84-108

14

SAMPLE NO.	NET WEIGHT (gms)	Grains of Scheelite? Blue-white S.W. & 'dead' L.W. Fluorescence	Possible Powellite? Yellow S.W. & 'dead' L.W. Fluorescence	SAMPLE NO.	NET WEIGHT (gms)	Grains of Scheelite? Blue-white S.W. & 'dead' L.W. Fluorescence	Possible Powellite? Yellow S.W. & 'dead' L.W. Fluorescence
01479				01480			
-35+150 IM	1.55			-35+150 IM	1.11		
IP	27.49			IP	18.50		
IN	22.23			IN	77.14		
HM	15.31			HM	5.39		
HP	133.23			HP	134.28	—	
HN	6.96	—		HN	6.01	—	
-150 IM	0.20			-150 IM	0.15		
IP	1.25			IP	1.78		
IN	2.61			IN	4.52		
HM	3.53			HM	0.38		
HP	11.89			HP	4.29		
HN	4.71			HN	0.81		
ORIG. WT. KG.	14.8			ORIG. WT. KG.	14.8		

* Net weight of sample by C.F. Minerals = Gross wt. - Tare of container



C.F. MINERAL RESEARCH LIMITED
263 LAKE AVENUE
KELOWNA, BRITISH COLUMBIA
CANADA V1Y 5W6

TEL. (604) 763-1815
(604) 860-8525

3/4

SAMPLE NO.	NET WEIGHT (gms)	Grains of Scheelite? Blue-white S.W. & 'dead' L.W. Fluorescence	Possible Powellite? Yellow S.W. & 'dead' L.W. Fluorescence	SAMPLE NO.	NET WEIGHT (gms)	Grains of Scheelite? Blue-white S.W. & 'dead' L.W. Fluorescence	Possible Powellite? Yellow S.W. & 'dead' L.W. Fluorescence
01483				01484			
-35+150 IM	0.92			-35+150 IM	0.46		
IP	57.50			IP	34.20		
IN	60.11			IN	40.02		
HM	13.64			HM	3.55		
HP	260.16			HP	95.12		
HN	17.92	-		HN	1.90	-	
-150 IM	0.15			-150 IM	0.09		
IP	3.43			IP	3.84		
IN	7.82			IN	14.94		
HM	5.26			HM	0.73		
HP	24.27			HP	5.44		
HN	8.05			HN	1.61		
ORIG. WT. KG.	16.5			ORIG. WT. KG.	15.4		

* Net weight of sample by C.F. Minerals = Gross wt. - Tare of container

