

P L A C E R D O M E I N C (V A N C O U V E R L A B O R A T O R Y)

GEOCHEMICAL DATA LISTING: V232 SPRING

DATE: 88:12:07

PDL lab data file: P8436

AREA: SPRING
 MAPSHEET NO: 92H16
 VENTURE: V232
 GEOLOGIST: R PEASE
 LAB PROJECT NO: 8436

PLEASE DISTRIBUTE RESULTS TO: RP BB LAB

REMARKS:

"AU1 RESULTS REPORTED IN PPB"
 "SAMPLES FROM BOXES 9 TO 16"

STANDARD ANALYSIS METHODS USED BY PDL GEOCHEM LAB ARE LISTED BELOW:
 ALL RESULTS EXPRESSED AS INDICATED IN UNITS COLUMN BELOW
 ANY EXCEPTIONS FOR THIS PROJECT ARE NOTED ABOVE

REMARKS: INTERNAL LAB STANDARDS HAVE BEEN INCLUDED FOR REFERENCE.
 SAMPLE NUMBERS FOLLOWED BY * ARE DUPLICATE ANALYSES.

	UNITS	WT.G	ATTACK USED	TIME	RANGE	METHOD
MO	PPM	0.5	HCL04/HN03	4HRS	1-1000	ATOMIC ABSORPTION
CU	PPM	0.5	HCL04/HN03	4HRS	2-4000	ATOMIC ABSORPTION
ZN	PPM	0.5	HCL04/HN03	4HRS	2-3000	ATOMIC ABSORPTION
PB	PPM	0.5	HCL04/HN03	4HRS	2-3000	A.A. BACKGROUND COR.
CD	PPM	0.5	HCL04/HN03	4HRS	0.2-200	A.A. BACKGROUND COR.
NI	PPM	0.5	HCL04/HN03	4HRS	2-2000	ATOMIC ABSORPTION
CO	PPM	0.5	HCL04/HN03	4HRS	2-2000	ATOMIC ABSORPTION
AG	PPM	0.5	HCL04/HN03	4HRS	0.2-20	A.A. BACKGROUND COR
AU	PPM	10.0	AQUA REGIA	3HRS	0.01-4.00	A.A. SOLVENT EXTRACT.
AU1	PPB	10.0	AQUA REGIA	3HRS	5-4000	A.A. SOLVENT EXTRACT.
U	PPM	0.25	DIL HN03	2HRS	1.0-1000	FLUORIMETRY SOLV. EX.
V	PPM	0.5	HF/HCL04/HN03/HCL	6HRS	5-1000	ATOMIC ABSORPTION
W	PPM	0.5	HCL04/H3PO4	2HRS	2-1000	DC PLASMA
F	PPM	0.25	NA2CO3/KNO3 FUSION	30MIN	40-4000	SPECIFIC ION ELECTRODE
AS	PPM	0.5	AQUA REGIA	3HRS	2-2000	DC PLASMA
SB	PPM	0.5	HCL/HN03	3HRS	2-2000	DC PLASMA
BI	PPM	0.5	HCL04/HN03	4HRS	2-2000	A.A. BACKGROUND COR.
MN	PPM	0.5	HCL04/HN03	4HRS	2-2000	ATOMIC ABSORPTION
FE	%	0.5	HF/HCL04/HN03/HCL	6HRS	0.02-20%	DC PLASMA
HG	PPB	0.25	DIL HN03/HCL	2HRS	5-2000PPB	A.A. COLD VAPOR GEN.
BA	%	0.25	HF/HI/OXALIC	4HRS	0.02-20%	ATOMIC ABSORPTION
NA	%	0.5	HF/HCL04/HN03/HCL	6HRS	0.2 -20%	DC PLASMA
K	%	0.5	HF/HCL04/HN03/HCL	6HRS	0.2 -20%	DC PLASMA
CA	%	0.5	HF/HCL04/HN03/HCL	6HRS	0.02-20%	DC PLASMA
SR	PPM	0.5	HF/HCL04/HN03/HCL	6HRS	10-2000	DC PLASMA
MG	%	0.5	HF/HCL04/HN03/HCL	6HRS	0.2-20%	DC PLASMA
SN	PPM	1.0	NH4I FUSION	15MIN	5-500	A.A. SOLVENT EXTRACT.
PT	PPB	25.0	FIRE ASSAY	45MIN	DL 10PPB	DC PLASMA
PD	PPB	25.0	FIRE ASSAY	45MIN	DL 5PPB	DC PLASMA
LOI	%	1.0	ASH 600 DEG C	2HRS	0.02-99%	WEIGH RESIDUE

GRID	SAMPLE	PROJECT	CU	ZN	PB	AG	AU1	
92H16	B/L00	12+00W	8436	30	430	40	0.5	NSS
92H16	B/L00	12+25W	8436	11	630	31	<0.2	<5
92H16	B/L00	12+50W	8436	100	790	41	1.3	<5
92H16	B/L00	12+75W	8436	9	250	18	<0.2	<5
92H16	B/L00	13+00W	8436	7	278	15	0.4	<5
92H16	B/L00	13+25W	8436	9	356	33	0.3	<5
92H16	B/L00	13+50W	8436	12	236	20	0.2	<5
92H16	B/L00	13+75W	8436	12	283	25	0.2	<5
92H16	B/L00	14+00W	8436	11	640	50	0.4	<5
test	STD P		8436	25	137	55	0.2	
92H16	L2+00W	7+00S	8436	11	204	15	<0.2	<5
92H16	L2+00W	7+25S	8436	23	140	20	0.2	10
92H16	L2+00W	7+50S	8436	15	302	14	<0.2	5
92H16	L2+00W	7+75S	8436	11	235	11	<0.2	<5
92H16	L2+00W	8+00S	8436	10	225	8	0.2	<5
92H16	L2+00W	8+25S	8436	9	178	10	0.2	<5
92H16	L2+00W	8+50S	8436	24	1800	24	0.4	60
92H16	L2+00W	8+75S	8436	72	0.33%	51	1.3	<5
92H16	L2+00W	9+00S	8436	10	70	12	<0.2	95
92H16	L2+00W	9+00S*	8436	9	69	11	<0.2	NSS
92H16	L2+00W	9+25S	8436	15	108	17	0.2	<5
92H16	L2+00W	9+50S	8436	14	87	16	<0.2	<5
92H16	L2+00W	9+75S	8436	12	81	15	<0.2	<5
92H16	L2+00W	10+00S	8436	7	190	19	<0.2	<5
92H16	L2+00W	10+25S	8436	9	100	14	<0.2	<5
92H16	L2+00W	10+50S	8436	12	182	12	0.2	<5
92H16	L2+00W	10+75S	8436	10	123	14	<0.2	<5
92H16	L2+00W	11+00S	8436	12	162	13	0.2	<5
92H16	L2+00W	11+25S	8436	13	130	14	0.3	<5
92H16	L2+00W	11+25S*	8436	13	130	14	0.3	<5
92H16	L2+00W	11+50S	8436	11	115	16	<0.2	<5
92H16	L2+00W	11+75S	8436	10	142	14	0.2	<5
92H16	L2+00W	12+00S	8436	8	166	14	0.2	<5
92H16	L2+00W	12+25S	8436	12	162	12	0.2	<5
92H16	L2+00W	12+50S	8436	8	140	11	<0.2	<5
92H16	L2+00W	12+75S	8436	7	94	10	<0.2	<5
92H16	L2+00W	13+00S	8436	8	164	14	0.3	<5
92H16	L2+00W	13+25S	8436	4	150	9	0.2	<5
92H16	L2+00W	13+50S	8436	4	88	9	<0.2	<5
92H16	L2+00W	13+50S*	8436	4	84	9	<0.2	<5
92H16	L2+00W	13+75S	8436	7	155	13	<0.2	<5
92H16	L2+00W	14+00S	8436	6	156	15	<0.2	<5
92H16	L2+00W	14+25S	8436	6	196	14	<0.2	<5
92H16	L2+00W	14+50S	8436	5	74	18	<0.2	<5
92H16	L2+00W	14+75S	8436	5	307	16	0.3	<5
92H16	L2+00W	15+00S	8436	7	400	20	<0.2	<5
92H16	L2+00W	15+25S	8436	7	194	17	<0.2	<5
92H16	L2+00W	15+50S	8436	12	190	19	0.2	<5
92H16	L2+00W	15+75S	8436	11	170	20	0.2	<5
92H16	L2+00W	16+00S	8436	11	184	19	0.3	<5
92H16	L2+00W	16+00S*	8436	11	184	19	0.3	<5
92H16	L2+00W	16+25S	8436	10	180	18	<0.2	<5
92H16	L2+00W	16+50S	8436	6	158	16	<0.2	<5
92H16	L2+00W	16+75S	8436	6	128	18	<0.2	<5
92H16	L2+00W	17+00S	8436	5	168	20	0.2	<5
92H16	L2+00W	17+25S	8436	4	102	19	<0.2	<5
92H16	L2+00W	17+50S	8436	4	64	13	<0.2	<5
92H16	L2+00W	17+75S	8436	5	86	16	<0.2	<5
92H16	L2+00W	18+00S	8436	6	150	21	0.2	<5
92H16	L2+00W	18+25S	8436	13	500	176	0.2	<5

GRID	SAMPLE	PROJECT	CU	ZN	PB	AG	AU1
test	STD P	8436	24	140	56	0.2	
92H16	L2+00W	18+50S	5	245	21	0.5	<5
92H16	L2+00W	18+75S	6	191	20	<0.2	<5
92H16	L2+00W	19+00S	8	81	32	<0.2	<5
92H16	L2+00W	19+25S	8	208	19	0.4	<5
92H16	L2+00W	19+50S	11	230	22	0.4	<5
92H16	L2+00W	19+75S	9	190	16	0.2	<5
92H16	L2+00W	20+00S	13	257	20	0.5	5
92H16	L6+00W	0+00N	15	174	70	<0.2	<5
92H16	L6+00W	0+25N	10	120	64	<0.2	<5
92H16	L6+00W	0+50N	13	176	20	0.2	<5
92H16	L6+00W	0+50N*	13	176	20	0.2	<5
92H16	L6+00W	0+75N	8	151	25	<0.2	<5
92H16	L6+00W	1+00N	4	128	10	<0.2	<5
92H16	L6+00W	1+25N	5	265	18	0.2	15
92H16	L6+00W	1+50N	10	266	15	0.2	5
92H16	L6+00W	1+75N	6	208	15	0.2	<5
92H16	L6+00W	2+00N	10	178	18	<0.2	<5
92H16	L6+00W	2+25N	6	145	12	0.3	<5
92H16	L6+00W	2+50N	8	235	17	0.2	<5
92H16	L6+00W	2+75N	8	224	15	0.3	<5
92H16	L6+00W	2+75N*	8	223	14	0.3	20
92H16	L6+00W	3+00N	12	250	16	0.5	<5
92H16	L6+00W	3+25N	9	185	19	0.3	<5
92H16	L6+00W	3+50N	13	230	16	0.4	<5
92H16	L6+00W	3+75N	15	230	14	0.4	<5
92H16	L6+00W	4+00N	11	260	17	0.3	<5
92H16	L6+00W	4+25N	10	240	25	0.3	<5
92H16	L6+00W	4+50N	7	260	18	0.3	<5
92H16	L6+00W	4+75N	7	250	15	0.4	<5
92H16	L6+00W	5+00N	9	240	16	0.4	<5
92H16	L6+00W	5+00N*	9	240	15	0.5	<5
92H16	L6+00W	5+25N	9	240	14	0.3	<5
92H16	L6+00W	5+50N	9	215	12	0.4	<5
92H16	L6+00W	5+75N	9	215	5	0.4	<5
92H16	L6+00W	6+00N	13	98	12	0.3	<5
92H16	L6+00W	6+25N	8	240	6	0.4	<5
92H16	L6+00W	6+50N	9	230	7	0.5	<5
92H16	L6+00W	6+75N	8	300	8	0.5	<5
92H16	L6+00W	2+00S	13	280	41	0.6	<5
92H16	L6+00W	2+25S	6	440	27	0.5	<5
92H16	L6+00W	2+25S*	6	420	26	0.4	<5
92H16	L6+00W	2+50S	5	300	11	0.3	<5
92H16	L6+00W	2+75S	10	380	19	0.4	<5
92H16	L6+00W	3+00S	10	320	16	0.4	<5
92H16	L6+00W	3+25S	12	310	21	0.6	<5
92H16	L6+00W	3+50S	9	220	22	0.4	<5
92H16	L6+00W	3+75S	17	250	17	1.0	<5
92H16	L6+00W	4+00S	12	330	30	0.7	<5
92H16	L6+00W	4+25S	13	240	47	0.5	<5
92H16	L6+00W	4+50S	13	260	47	0.5	<5
test	STD P	8436	26	131	52	0.3	
92H16	L6+00W	4+75S	13	290	48	0.4	<5
92H16	L6+00W	5+00S	10	290	26	0.5	<5
92H16	L6+00W	5+25S	9	240	26	0.4	<5
92H16	L6+00W	5+50S	17	600	32	0.8	<5
92H16	L6+00W	5+75S	14	1060	41	1.0	<5
92H16	L6+00W	6+00S	8	260	20	0.5	<5
92H16	L6+00W	6+25S	9	550	52	0.7	<5
92H16	L6+00W	6+50S	7	530	44	0.4	<5

GRID	SAMPLE	PROJECT	CU	ZN	PB	AG	AU1	
92H16	L6+00W	6+75S	8436	12	1340	47	2.5	<5
92H16	L6+00W	6+75S*	8436	13	1380	48	2.7	NSS
92H16	L6+00W	7+00S	8436	18	920	88	1.3	<5
92H16	L6+00W	7+25S	8436	15	320	36	0.4	<5
92H16	L6+00W	7+50S	8436	15	690	50	0.6	<5
92H16	L6+00W	7+75S	8436	10	720	31	0.5	<5
92H16	L6+00W	8+00S	8436	8	620	23	0.3	<5
92H16	L6+00W	8+25S	8436	11	740	30	0.6	<5
92H16	L6+00W	8+50S	8436	15	730	41	0.5	<5
92H16	L6+00W	8+75S	8436	11	550	38	0.3	<5
92H16	L6+00W	9+00S	8436	12	380	30	0.5	<5
92H16	L6+00W	9+00S*	8436	12	370	29	0.5	<5
92H16	L6+00W	9+25S	8436	12	480	70	0.5	<5
92H16	L6+00W	9+50S	8436	15	460	33	0.4	<5
92H16	L6+00W	9+75S	8436	11	660	43	0.3	<5
92H16	L6+00W	10+00S	8436	18	540	51	0.5	<5
92H16	L6+00W	10+25S	8436	12	204	13	0.2	<5
92H16	L6+00W	10+50S	8436	10	370	24	0.4	<5
92H16	L6+00W	10+75S	8436	18	330	39	0.3	<5
92H16	L6+00W	11+00S	8436	17	1050	33	1.0	<5
92H16	L6+00W	11+25S	8436	13	360	23	0.6	<5
92H16	L6+00W	11+25S*	8436	12	350	23	0.6	<5
92H16	L6+00W	11+50S	8436	14	380	20	0.4	<5
92H16	L6+00W	11+75S	8436	9	310	21	0.2	<5
92H16	L6+00W	12+00S	8436	16	300	22	0.4	<5
92H16	L6+00W	12+25S	8436	20	330	29	0.4	<5
92H16	L6+00W	12+50S	8436	29	630	20	0.6	<5
92H16	L6+00W	12+75S	8436	8	111	8	0.2	<5
92H16	L6+00W	13+00S	8436	16	188	12	0.3	<5
92H16	L6+00W	13+25S	8436	18	290	15	0.3	<5
92H16	L6+00W	13+50S	8436	26	143	21	<0.2	<5
92H16	L6+00W	13+50S*	8436	24	139	20	0.2	<5
92H16	L6+00W	13+75S	8436	16	84	12	0.2	<5
92H16	L6+00W	14+00S	8436	15	97	14	0.2	<5
92H16	L6+00W	14+25S	8436	11	189	30	0.3	<5
92H16	L6+00W	14+50S	8436	10	178	14	0.3	<5
92H16	L6+00W	14+75S	8436	7	156	12	0.2	<5
92H16	L6+00W	15+00S	8436	10	164	12	0.4	<5
92H16	L8+00W	0+25S	8436	8	191	20	0.2	<5
92H16	L8+00W	0+50S	8436	10	470	21	0.3	<5
92H16	L8+00W	0+75S	8436	7	288	9	0.3	<5
test	STD P		8436	26	131	52	0.3	
92H16	L8+00W	1+00S	8436	10	270	15	0.2	<5
92H16	L8+00W	1+25S	8436	11	240	13	0.3	<5
92H16	L8+00W	1+50S	8436	12	310	20	0.4	<5
92H16	L8+00W	1+75S	8436	10	310	27	0.5	<5
92H16	L8+00W	2+00S	8436	6	136	16	0.2	<5
92H16	L8+00W	2+25S	8436	13	240	18	0.3	<5
92H16	L8+00W	2+50S	8436	11	133	11	0.2	<5
92H16	L8+00W	2+75S	8436	10	188	8	0.3	<5
92H16	L8+00W	3+00S	8436	12	216	13	0.2	<5
test	STD P		8436	28	131	51	0.3	
92H16	L8+00W	3+25S	8436	13	181	14	0.4	<5
92H16	L8+00W	3+50S	8436	11	199	10	0.4	<5
92H16	L8+00W	3+75S	8436	12	240	12	0.3	<5
92H16	L8+00W	8+00S	8436	10	440	39	0.8	<5
92H16	L8+00W	8+25S	8436	9	670	89	0.7	<5
92H16	L8+00W	8+50S	8436	8	610	88	0.7	<5
92H16	L8+00W	8+75S	8436	8	520	38	0.6	<5
92H16	L8+00W	9+00S	8436	8	560	26	0.5	<5

GRID	SAMPLE	PROJECT	CU	ZN	PB	AG	AU1	
92H16	L8+00W	9+25S	8436	8	590	36	0.4	<5
92H16	L8+00W	9+25S*	8436	9	610	36	0.4	<5
92H16	L8+00W	9+50S	8436	31	1490	56	1.8	<5
92H16	L8+00W	9+75S	8436	12	710	32	0.8	<5
92H16	L8+00W	10+00S	8436	129	1080	64	4.2	<5
92H16	L8+00W	10+25S	8436	21	330	51	0.6	<5
92H16	L8+00W	10+50S	8436	14	630	98	0.7	<5
92H16	L8+00W	10+75S	8436	17	280	49	0.5	<5
92H16	L8+00W	11+00S	8436	12	280	30	0.4	<5
92H16	L8+00W	11+25S	8436	12	380	41	0.7	<5
92H16	L8+00W	11+50S	8436	15	310	35	0.3	<5
92H16	L8+00W	11+50S*	8436	15	300	36	0.3	<5
92H16	L8+00W	11+75S	8436	12	330	41	0.4	<5
92H16	L8+00W	12+00S	8436	13	370	37	0.5	<5
92H16	L8+00W	12+25S	8436	12	430	41	0.4	<5
92H16	L8+00W	12+50S	8436	11	400	37	0.4	<5
92H16	L8+00W	12+75S	8436	9	250	17	0.3	<5
92H16	L8+00W	13+00S	8436	22	260	24	0.6	<5
92H16	L8+00W	13+25S	8436	13	330	24	0.4	<5
92H16	L8+00W	13+50S	8436	12	320	21	0.3	<5
92H16	L8+00W	13+75S	8436	17	370	29	0.6	<5
92H16	L8+00W	13+75S*	8436	16	360	28	0.6	<5
92H16	L8+00W	14+00S	8436	6	550	20	<0.2	<5
92H16	L8+00W	14+25S	8436	14	480	30	<0.2	<5
92H16	L8+00W	14+50S	8436	8	100	17	0.2	<5
92H16	L8+00W	14+75S	8436	8	90	15	<0.2	<5
92H16	L8+00W	15+00S	8436	7	155	13	0.2	<5
92H16	L12+00W	0+25N	8436	9	550	28	0.2	<5
92H16	L12+00W	0+50N	8436	8	600	62	0.5	<5
92H16	L12+00W	0+75N	8436	10	1200	26	0.3	<5
92H16	L12+00W	1+00N	8436	8	420	23	<0.2	<5
92H16	L12+00W	1+00N*	8436	7	440	20	<0.2	<5
92H16	L12+00W	1+25N	8436	5	520	22	0.3	<5
92H16	L12+00W	1+50N	8436	9	640	26	0.6	<5
92H16	L12+00W	1+75N	8436	14	650	23	0.5	<5
92H16	L12+00W	2+00N	8436	9	590	17	0.4	<5
92H16	L14+00W	0+25N	8436	6	316	34	0.2	<5
92H16	L14+00W	0+50N	8436	7	273	16	0.2	<5
92H16	L14+00W	0+75N	8436	9	470	22	0.3	<5
92H16	L14+00W	1+00N	8436	17	600	24	0.4	<5
92H16	L14+00W	1+25N	8436	10	460	32	0.3	<5
test	STD P	8436	24	132	51	0.3		
92H16	L14+00W	1+50N	8436	5	610	11	<0.2	<5
92H16	L14+00W	1+75N	8436	7	840	18	0.2	<5
92H16	L14+00W	2+00N	8436	6	450	19	0.3	<5
92H16	L14+00W	2+25N	8436	10	420	31	0.3	<5
92H16	L14+00W	2+50N	8436	8	470	20	0.3	<5
92H16	L14+00W	2+75N	8436	3	307	10	0.2	<5
92H16	L14+00W	3+00N	8436	4	400	21	0.2	<5
92H16	L14+00W	3+25N	8436	8	268	31	<0.2	<5
92H16	L14+00W	3+50N	8436	9	570	51	<0.2	<5
92H16	L14+00W	3+50N*	8436	9	600	51	<0.2	<5
92H16	L14+00W	3+75N	8436	6	760	56	0.2	<5
92H16	L14+00W	4+00N	8436	8	620	34	<0.2	<5
92H16	L14+00W	4+25N	8436	9	227	17	0.2	<5
92H16	L14+00W	4+50N	8436	7	380	27	<0.2	<5
92H16	L14+00W	4+75N	8436	5	350	18	<0.2	<5
92H16	L14+00W	5+00N	8436	7	500	35	<0.2	<5
92H16	L14+00W	5+25N	8436	8	510	44	0.2	<5
92H16	L14+00W	5+50N	8436	48	1330	96	0.4	<5

GRID	SAMPLE	PROJECT	CU	ZN	PB	AG	AU1	
92H16	L14+00W	5+75N	8436	10	800	60	<0.2	<5
92H16	L14+00W	5+75N*	8436	10	750	58	<0.2	<5
92H16	L14+00W	6+00N	8436	16	1680	104	0.2	<5
92H16	L14+00W	6+25N	8436	8	540	13	0.2	<5
92H16	L14+00W	6+50N	8436	11	800	20	<0.2	<5
92H16	L14+00W	6+75N	8436	10	366	15	<0.2	<5
92H16	L14+00W	7+00N	8436	10	355	14	<0.2	<5
92H16	L14+00W	7+25N	8436	6	280	9	<0.2	<5
92H16	L14+00W	7+50N	8436	34	337	28	0.5	10
92H16	L14+00W	7+75N	8436	25	400	28	0.4	<5
92H16	L14+00W	8+00N	8436	10	270	15	0.2	<5
92H16	L14+00W	8+00N*	8436	9	270	15	0.2	<5
92H16	L14+00W	8+25N	8436	10	162	14	<0.2	<5
92H16	L14+00W	8+50N	8436	8	216	12	0.2	<5
92H16	L14+00W	8+75N	8436	14	156	10	0.2	<5
92H16	L14+00W	9+00N	8436	11	124	12	0.2	10
92H16	L14+00W	9+25N	8436	7	66	7	<0.2	10
92H16	L14+00W	9+50N	8436	7	170	15	<0.2	<5
92H16	L14+00W	9+75N	8436	14	70	13	<0.2	<5
92H16	L14+00W	10+00N	8436	10	115	25	<0.2	<5
92H16	L14+00W	10+25N	8436	14	52	8	<0.2	<5
92H16	L14+00W	10+25N*	8436	14	51	7	<0.2	<5
92H16	L14+00W	10+50N	8436	16	60	7	<0.2	<5
92H16	L14+00W	10+75N	8436	11	52	6	<0.2	<5
92H16	L14+00W	11+00N	8436	10	56	6	<0.2	<5
92H16	L14+00W	11+25N	8436	12	57	6	<0.2	<5
92H16	L14+00W	11+50N	8436	14	83	8	<0.2	<5
92H16	L14+00W	11+75N	8436	13	71	13	<0.2	<5
92H16	L14+00W	12+00N	8436	12	52	6	<0.2	<5
92H16	L14+00W	12+25N	8436	14	46	6	0.2	<5
92H16	L14+00W	12+50N	8436	12	40	6	0.2	<5
test	STD P	8436	25	130	50	0.2		
92H16	L14+00W	12+75N	8436	14	58	9	<0.2	<5
92H16	L14+00W	13+00N	8436	11	110	16	<0.2	<5
92H16	L14+00W	13+25N	8436	7	177	11	0.2	<5
92H16	L14+00W	13+50N	8436	14	51	6	0.2	<5
92H16	L14+00W	13+75N	8436	13	71	8	<0.2	<5
92H16	L14+00W	14+00N	8436	16	47	9	<0.2	<5
92H16	L14+00W	14+25N	8436	16	58	11	1.0	<5
92H16	L14+00W	14+50N	8436	10	67	8	<0.2	<5
92H16	L14+00W	14+75N	8436	17	104	9	<0.2	<5
92H16	L14+00W	14+75N*	8436	18	107	8	<0.2	<5
92H16	L14+00W	15+00N	8436	10	84	6	<0.2	<5
92H16	L14+00W	15+25N	8436	9	95	7	0.2	<5
92H16	L14+00W	15+50N	8436	9	178	7	<0.2	<5
92H16	L14+00W	15+75N	8436	10	85	10	<0.2	<5
92H16	L14+00W	16+00N	8436	8	158	12	0.3	5
92H16	L14+00W	16+25N	8436	13	155	11	0.4	<5
92H16	L14+00W	16+50N	8436	10	336	10	0.3	<5
92H16	L14+00W	16+75N	8436	11	55	5	<0.2	<5
92H16	L14+00W	17+00N	8436	9	46	4	<0.2	<5
92H16	L14+00W	17+00N*	8436	9	45	4	<0.2	<5
92H16	L14+00W	17+25N	8436	10	202	11	<0.2	<5
92H16	L14+00W	17+50N	8436	12	133	9	<0.2	<5
92H16	L14+00W	17+75N	8436	23	142	16	0.3	<5
92H16	L14+00W	18+00N	8436	9	240	30	<0.2	<5
92H16	L14+00W	18+25N	8436	6	60	6	<0.2	<5
92H16	L14+00W	18+50N	8436	16	90	13	0.2	<5
92H16	L14+00W	18+75N	8436	8	45	4	<0.2	<5
92H16	L14+00W	19+00N	8436	12	31	4	<0.2	<5

GRID	SAMPLE	PROJECT	CU	ZN	PB	AG	AU1	
92H16	L14+00W	19+25N	8436	10	70	5	<0.2	<5
92H16	L14+00W	19+25N*	8436	10	70	4	<0.2	<5
92H16	L14+00W	19+50N	8436	20	62	6	<0.2	<5
92H16	L14+00W	19+75N	8436	6	20	3	<0.2	<5
92H16	L14+00W	20+00N	8436	10	71	4	<0.2	<5
92H16	L14+00W	20+25N	8436	23	157	10	<0.2	<5
92H16	L14+00W	20+50N	8436	14	168	10	<0.2	<5
92H16	L14+00W	20+75N	8436	9	142	8	<0.2	<5
92H16	L14+00W	21+00N	8436	11	133	8	<0.2	<5
92H16	L14+00W	21+25N	8436	10	136	7	<0.2	<5
92H16	L14+00W	21+50N	8436	12	153	8	<0.2	<5
92H16	L14+00W	21+50N*	8436	11	147	7	<0.2	<5
92H16	L14+00W	21+75N	8436	14	194	7	<0.2	<5
92H16	L14+00W	22+00N	8436	13	112	5	<0.2	<5
92H16	L14+00W	22+25N	8436	14	121	7	<0.2	<5
92H16	L14+00W	22+50N	8436	21	108	6	<0.2	<5
92H16	L14+00W	22+75N	8436	16	113	5	<0.2	<5
92H16	L14+00W	23+00N	8436	17	84	5	<0.2	<5
92H16	L14+00W	23+25N	8436	16	104	5	<0.2	<5
92H16	L14+00W	23+50N	8436	20	64	13	<0.2	<5
92H16	L14+00W	23+75N	8436	17	88	6	<0.2	<5
test	STD P		8436	26	133	51	0.2	
92H16	L14+00W	24+00N	8436	15	98	7	<0.2	<5
92H16	L14+00W	24+25N	8436	17	130	7	<0.2	<5
92H16	L14+00W	24+50N	8436	21	144	9	<0.2	<5
92H16	L14+00W	24+75N	8436	9	74	6	<0.2	<5
92H16	L14+00W	25+00N	8436	10	74	6	<0.2	<5
92H16	L14+00W	25+25N	8436	12	63	6	<0.2	<5
92H16	L14+00W	25+50N	8436	15	73	6	<0.2	<5
92H16	L14+00W	25+75N	8436	12	102	8	<0.2	<5
92H16	L14+00W	26+00N	8436	20	100	6	<0.2	<5
test	STD P		8436	25	128	51	0.2	
92H16	L14+00W	26+25N	8436	11	31	4	<0.2	<5
92H16	L14+00W	27+25N	8436	14	59	5	<0.2	<5
92H16	L14+00W	27+50N	8436	18	75	5	<0.2	<5
92H16	L14+00W	27+75N	8436	13	36	4	<0.2	<5
92H16	L14+00W	28+00N	8436	17	54	6	<0.2	<5
92H16	L14+00W	28+25N	8436	16	57	7	<0.2	<5
92H16	L14+00W	28+50N	8436	14	55	5	<0.2	<5
92H16	L14+00W	28+75N	8436	16	93	8	<0.2	<5
92H16	L14+00W	29+00N	8436	14	72	7	<0.2	<5
92H16	L14+00W	29+00N*	8436	13	71	8	<0.2	<5
92H16	L14+00W	29+25N	8436	13	81	6	<0.2	<5
92H16	L14+00W	29+50N	8436	12	60	7	<0.2	<5
92H16	L14+00W	29+75N	8436	14	84	7	<0.2	<5
92H16	L14+00W	30+00N	8436	12	62	6	<0.2	<5
92H16	L14+00W	30+25N	8436	12	70	6	0.2	<5
92H16	L18+00W	15+75N	8436	9	50	7	<0.2	<5
92H16	L18+00W	16+00N	8436	10	54	7	<0.2	<5
92H16	L18+00W	16+25N	8436	15	118	9	0.2	<5
92H16	L18+00W	16+50N	8436	10	71	6	<0.2	45
92H16	L18+00W	16+50N*	8436	10	73	6	<0.2	<5
92H16	L18+00W	16+75N	8436	11	70	5	<0.2	<5
92H16	L18+00W	17+00N	8436	8	72	7	<0.2	5
92H16	L18+00W	17+25N	8436	9	75	7	<0.2	<5
92H16	L18+00W	17+50N	8436	9	90	16	<0.2	20
92H16	L18+00W	17+75N	8436	8	75	6	<0.2	<5
92H16	L18+00W	18+00N	8436	11	74	7	<0.2	<5
92H16	L18+00W	18+25N	8436	13	47	6	<0.2	<5
92H16	L18+00W	18+50N	8436	13	58	6	<0.2	<5

GRID	SAMPLE	PROJECT	CU	ZN	PB	AG	AU1	
92H16	L18+00W	18+75N	8436	12	88	7	0.2	<5
92H16	L18+00W	18+75N*	8436	12	88	7	0.2	<5
92H16	L18+00W	19+00N	8436	8	53	7	<0.2	<5
92H16	L18+00W	19+25N	8436	10	41	7	<0.2	<5
92H16	L18+00W	19+50N	8436	10	140	9	<0.2	<5
92H16	L18+00W	19+75N	8436	10	312	11	<0.2	5
92H16	L18+00W	20+00N	8436	8	76	8	<0.2	30
92H16	L18+00W	20+25N	8436	10	70	10	<0.2	20
92H16	L18+00W	20+50N	8436	9	92	7	<0.2	20
92H16	L18+00W	20+75N	8436	12	54	7	<0.2	<5
92H16	L18+00W	21+00N	8436	16	40	9	0.2	<5
92H16	L18+00W	21+00N*	8436	17	40	8	0.2	<5
92H16	L18+00W	21+25N	8436	7	54	8	<0.2	20
92H16	L18+00W	21+50N	8436	8	60	7	<0.2	<5
92H16	L18+00W	21+75N	8436	11	94	10	<0.2	<5
92H16	L18+00W	22+00N	8436	12	80	11	<0.2	<5
92H16	L18+00W	22+25N	8436	15	124	11	0.2	<5
92H16	L18+00W	22+50N	8436	16	102	11	0.2	<5
92H16	L18+00W	22+75N	8436	12	100	10	0.2	<5
92H16	L18+00W	23+00N	8436	15	130	11	0.2	<5
92H16	L18+00W	23+25N	8436	13	105	11	0.2	<5
test	STD P	8436	24	130	53	0.2		
92H16	L18+00W	23+50N	8436	12	85	10	<0.2	5
92H16	L18+00W	23+75N	8436	15	92	10	<0.2	<5
92H16	L18+00W	24+00N	8436	12	83	10	<0.2	<5
92H16	L18+00W	24+25N	8436	14	66	9	<0.2	<5
92H16	L18+00W	24+50N	8436	11	70	10	<0.2	<5
92H16	L18+00W	24+75N	8436	13	72	11	<0.2	5
92H16	L18+00W	25+00N	8436	12	73	9	0.2	15
92H16	L18+00W	25+25N	8436	11	54	9	<0.2	<5
92H16	L18+00W	25+50N	8436	10	43	9	<0.2	5
92H16	L18+00W	25+50N*	8436	10	42	9	<0.2	15
92H16	L18+00W	25+75N	8436	16	55	10	<0.2	<5
92H16	L18+00W	26+00N	8436	12	41	9	<0.2	<5
92H16	L18+00W	27+00N	8436	13	55	7	<0.2	<5
92H16	L18+00W	27+25N	8436	14	65	8	<0.2	<5
92H16	L18+00W	27+50N	8436	11	68	7	0.2	<5
92H16	L18+00W	27+75N	8436	12	51	8	<0.2	<5
92H16	L18+00W	28+00N	8436	13	52	9	<0.2	<5
92H16	L18+00W	28+25N	8436	26	101	11	0.3	<5
92H16	L18+00W	28+50N	8436	11	60	8	0.2	<5
92H16	L18+00W	28+50N*	8436	11	58	9	0.2	<5
92H16	L18+00W	28+75N	8436	12	46	6	<0.2	<5
92H16	L18+00W	29+00N	8436	12	49	8	<0.2	<5
92H16	L18+00W	29+25N	8436	10	46	8	<0.2	<5
92H16	L18+00W	29+50N	8436	15	49	8	<0.2	<5
92H16	L18+00W	29+75N	8436	13	45	8	0.2	10
92H16	L18+00W	30+00N	8436	11	58	8	<0.2	5
92H16	L18+00W	30+25N	8436	14	50	8	<0.2	<5
92H16	L18+00W	30+50N	8436	14	50	7	<0.2	<5
92H16	L18+00W	30+75N	8436	14	60	8	0.2	<5
92H16	L18+00W	30+75N*	8436	15	65	8	0.2	5
92H16	L18+00W	31+00N	8436	20	67	11	<0.2	<5
92H16	L18+00W	31+25N	8436	15	52	7	<0.2	<5
92H16	L18+00W	31+50N	8436	11	60	7	<0.2	<5
92H16	L18+00W	31+75N	8436	10	43	4	<0.2	15
92H16	L18+00W	32+00N	8436	7	33	4	<0.2	<5
92H16	L18+00W	32+25N	8436	14	72	6	<0.2	<5
92H16	L18+00W	32+50N	8436	16	56	6	<0.2	<5
92H16	L18+00W	32+75N	8436	9	52	6	<0.2	<5

GRID	SAMPLE	PROJECT		CU	ZN	PB	AG	AU1
92H16	L18+00W	33+00N	8436	66	106	13	0.5	<5
92H16	L18+00W	33+00N*	8436	64	102	13	0.5	<5
92H16	L18+00W	33+25N	8436	11	102	7	<0.2	<5
92H16	L18+00W	33+50N	8436	11	82	8	<0.2	<5
92H16	L18+00W	33+75N	8436	12	62	7	<0.2	<5
92H16	L18+00W	34+00N	8436	18	42	9	<0.2	<5
92H16	L18+00W	34+25N	8436	48	128	18	<0.2	<5
92H16	L18+00W	34+50N	8436	20	130	11	0.2	<5
92H16	L18+00W	34+75N	8436	12	91	15	<0.2	<5
92H16	L18+00W	35+00N	8436	15	195	12	0.2	<5
92H16	L18+00W	35+25N	8436	16	104	10	0.2	<5
test	STD P		8436	25	130	54	0.2	
92H16	L18+00W	35+50N	8436	9	84	9	<0.2	<5
92H16	L18+00W	35+75N	8436	9	90	9	<0.2	<5
92H16	L18+00W	36+00N	8436	11	130	8	<0.2	5
92H16	L18+00W	36+25N	8436	11	140	9	<0.2	<5
92H16	L18+00W	36+50N	8436	13	130	8	0.2	<5
92H16	L18+00W	36+75N	8436	15	123	9	<0.2	<5
92H16	L18+00W	37+00N	8436	10	110	7	0.2	<5
92H16	L20+00W	27+00N	8436	18	48	7	<0.2	<5
92H16	L20+00W	27+25N	8436	10	43	6	<0.2	<5
92H16	L20+00W	27+25N*	8436	11	46	6	<0.2	<5
92H16	L20+00W	27+50N	8436	10	43	6	<0.2	<5
92H16	L20+00W	27+75N	8436	5	21	5	<0.2	<5
92H16	L20+00W	28+00N	8436	10	34	5	<0.2	<5
92H16	L20+00W	28+25N	8436	10	47	6	<0.2	<5
92H16	L20+00W	28+50N	8436	9	70	6	<0.2	<5
92H16	L20+00W	28+75N	8436	13	64	8	<0.2	<5
92H16	L20+00W	29+00N	8436	7	42	6	<0.2	<5
92H16	L20+00W	29+25N	8436	9	40	7	<0.2	<5
92H16	L20+00W	29+50N	8436	8	37	6	<0.2	<5
92H16	L20+00W	29+50N*	8436	7	37	5	<0.2	<5
92H16	L20+00W	29+75N	8436	7	50	7	<0.2	<5
92H16	L20+00W	30+00N	8436	8	43	8	<0.2	<5
92H16	L20+00W	30+25N	8436	8	45	6	<0.2	<5
92H16	L20+00W	30+50N	8436	16	80	13	<0.2	5
92H16	L20+00W	30+75N	8436	20	86	11	0.2	15
92H16	L20+00W	31+00N	8436	27	113	12	0.2	<5
92H16	L20+00W	31+25N	8436	41	123	17	0.3	<5
92H16	L20+00W	31+50N	8436	13	113	13	0.2	<5
92H16	L20+00W	31+75N	8436	10	136	14	<0.2	<5
92H16	L20+00W	31+75N*	8436	10	130	12	<0.2	<5
92H16	L20+00W	32+00N	8436	11	81	10	<0.2	<5
92H16	L20+00W	32+25N	8436	10	41	7	<0.2	30
92H16	L20+00W	32+50N	8436	9	46	6	<0.2	<5
92H16	L20+00W	32+75N	8436	15	116	8	<0.2	15
92H16	L20+00W	33+00N	8436	12	138	13	<0.2	<5
92H16	L20+00W	33+25N	8436	17	182	17	<0.2	20
92H16	L20+00W	33+50N	8436	12	136	11	<0.2	<5
92H16	L20+00W	33+75N	8436	13	183	10	<0.2	<5
92H16	L20+00W	34+00N	8436	18	95	11	<0.2	<5
92H16	L20+00W	34+00N*	8436	17	96	10	<0.2	<5
92H16	L20+00W	34+25N	8436	12	60	9	<0.2	<5
92H16	L20+00W	34+50N	8436	10	126	9	<0.2	<5
92H16	L20+00W	34+75N	8436	17	120	10	0.3	<5
92H16	L20+00W	35+00N	8436	20	126	16	0.2	<5
92H16	L20+00W	35+25N	8436	14	237	16	0.2	<5
92H16	L20+00W	35+50N	8436	44	163	25	0.2	<5
92H16	L20+00W	35+75N	8436	26	103	17	<0.2	<5
92H16	L20+00W	36+00N	8436	15	227	15	<0.2	<5

GRID	SAMPLE	PROJECT	CU	ZN	PB	AG	AU1
92H16	L20+00W 36+25N	8436	14	113	11	0.2	<5
test	STD P	8436	25	130	55	0.2	
92H16	L20+00W 36+50N	8436	11	123	12	<0.2	<5
92H16	L20+00W 36+75N	8436	11	150	10	0.2	<5
92H16	L20+00W 37+00N	8436	29	128	19	0.3	<5
92H16	TL27+00N 18+25W	8436	9	56	8	<0.2	<5
92H16	TL27+00N 18+50W	8436	26	42	14	<0.2	<5
92H16	TL27+00N 18+75W	8436	47	80	15	0.8	<5
92H16	TL27+00N 19+00W	8436	15	33	7	<0.2	<5
92H16	TL27+00N 19+25W	8436	10	35	7	<0.2	<5
92H16	TL27+00N 19+50W	8436	9	38	8	<0.2	<5
test	STD P	8436	24	130	52	0.2	
92H16	TL27+00N 19+75W	8436	9	41	10	<0.2	<5
92H16	TL27+00N 19+75W*	8436	8	40	8	<0.2	<5
test	STD AU1	8436					625
test	STD AU1	8436					620
test	STD AU1	8436					560
test	STD AU1	8436					575
test	STD AU1	8436					670
test	STD AU1	8436					600
test	STD AU1	8436					650
test	STD AU1	8436					520
test	STD AU1	8436					510
test	STD AU1	8436					600
test	STD AU1	8436					500
test	STD AU1	8436					500
test	STD AU1	8436					550

END OF LISTING - 507 RECORDS PRINTED
GCLIST RUN AT: 15:26:32

PLACER DEVELOPMENT LIMITED: GEOCHEM ASSAY SYSTEM

Following elements needed some values adjusted:

ELEMENT	NSS	LOW	HI	%	BLNK	NVAL
ZN	0	0	0	1	0	444
AG	0	221	0	0	0	444
AU1	1	411	0	0	0	443

63 records skipped: tests, duplicate analyses

SUMMARY OF GEOCHEM DATA: V232 SPRING

ITEM	# VALUES	MISSING	MINIMUM	MAXIMUM	AVERAGE	STD. DEV.
GRID	444	0	92H16	92H16		
SAMP	444	0	B/L00	TL27+00N		
PROJ	444	0	8436	8436		
AG	444	0	0.10	4.20	0.25	0.30
AU1	443	1	2.50	95.00	3.55	6.27
CU	444	0	3.00	129.00	12.83	9.77
PB	444	0	3.00	176.00	17.82	16.92
ZN	444	0	20.00	3300.00	234.53	281.05

END OF GCHSCAN: DATE: 88:12:07 time: 15:26:32 444 RECORDS PROCESSED