


Big Nic  
880812

Feb 9/08

## PACIFIC COAST NICKEL CORP. CLAIM HOLDINGS



PACIFIC COAST NICKEL CORP.  
CLAIM MAP



outline of pcnc claims feb. 2006 (904x1179x24b.bmp)

**PACIFIC COAST NICKEL CORP.**  
**ANALYTICAL RESULTS**

**BIG NIC PROJECT**

<b>SAMPLE DESCRIPTION</b>	<b>Au</b>	<b>Pt</b>	<b>Pd</b>	<b>Co %</b>	<b>Cu %</b>	<b>Ni %</b>	
<b>MS AREA</b>	<b>ppm</b>	<b>ppm</b>	<b>ppm</b>				
MS	0.004	-0.005	0.004	0.029	0.057	0.06	
MS	0.194	0.038	0.072	0.0667	1.75	0.5910	
MS	0.033	0.095	0.104	0.0794	1.49	0.7220	
MS	0.039	0.07	0.11	0.0939	1.92	0.8020	
MS	0.035	0.119	0.138	0.0883	0.531	0.8570	
MS	0.005	-0.005	0.002	0.0063	0.0159	0.0215	
MS	0.053	0.085	0.061	0.0467	0.567	0.3840	
MS	0.098	-0.005	0.023	0.0545	2.93	0.2450	
MS	0.047	0.083	0.097	0.0612	0.0579	0.6050	
MS				0.083	3.728	0.651	
	<b>Au</b>	<b>Pt</b>	<b>Pd</b>				
	(oz/t)	(g/t)	(g/t)				
MS(1)	0.006	<0.03	0.20	0.09	2.45	0.88	
	<b>Au</b>	<b>Pd</b>	<b>Pt</b>				
	(g/t)	(g/t)	(g/t)				
MS(2A)	<0.03	0.10	0.05	0.110	1.99	0.82	

<b>SAMPLE DESCRIPTION</b>				<b>Co %</b>	<b>Cu %</b>	<b>Ni %</b>	
<b>MS-2 AREA</b>	<b>Au</b>	<b>Pt</b>	<b>Pd</b>				
	(oz/t)	(oz/t)	(oz/t)				
MS-2	0.003	<0.001	0.006	0.08	2.36	0.77	
MS-2				0.1134	1.997	0.9298	
MS-2				0.0294	0.2109	0.2650	
MS-2 (PM04 25.9:2)				0.0859	1.4312	0.7729	

<b>SAMPLE</b>							
<b>DESCRIPTION</b>							
<b>MS-3 AREA</b>							
<b>MS-3(DPCR 1A)</b>	<b>0.03</b>	<b>&lt;0.03</b>	<b>0.09</b>	<b>0.075</b>	<b>0.82</b>	<b>0.62</b>	
<b>MS-3(DPCR 1B)</b>	<b>&lt;.03</b>	<b>0.09</b>	<b>0.1</b>	<b>0.072</b>	<b>0.62</b>	<b>0.63</b>	
<b>MS-3 (DPCR 2A)</b>	<b>0.05</b>	<b>0.1</b>	<b>0.13</b>	<b>0.075</b>	<b>1.14</b>	<b>0.67</b>	
<b>MS-3 (DPCR 2B)</b>	<b>0.03</b>	<b>0.04</b>	<b>0.09</b>	<b>0.08</b>	<b>0.88</b>	<b>0.65</b>	
<b>MS-3 (DPCR 2C)</b>	<b>0.04</b>	<b>&lt;0.03</b>	<b>&lt;0.03</b>	<b>0.02</b>	<b>0.29</b>	<b>0.12</b>	
<b>MS-3 (DPCR)</b>	<b>0.059</b>	<b>0.017</b>	<b>0.034</b>	<b>0.022</b>	<b>0.581</b>	<b>0.163</b>	
<b>MS-3 (DPCR)</b>	<b>0.497</b>	<b>0.006</b>	<b>0.059</b>	<b>0.0493</b>	<b>1.83</b>	<b>0.347</b>	
<b>MS-3 (DPCR)</b>	<b>0.03</b>	<b>0.006</b>	<b>0.014</b>	<b>0.0145</b>	<b>0.1635</b>	<b>0.0872</b>	
<b>MS-3 (DPCR)</b>				<b>0.018</b>	<b>0.2197</b>	<b>0.1412</b>	
<b>SAMPLE</b>	<b>Au</b>	<b>Pt</b>	<b>Pd</b>	<b>Co</b>	<b>Cu</b>	<b>Ni</b>	
<b>DESCRIPTION</b>	<b>ppm</b>	<b>ppm</b>	<b>ppm</b>	<b>%</b>	<b>%</b>	<b>%</b>	
<b>NMS</b>							
<b>AREA &amp;</b>							
<b>SULFRAC</b>							
<b>NMS 07/16/05A</b>	<b>0.11</b>	<b>&lt;0.03</b>	<b>&lt;0.03</b>	<b>0.023</b>	<b>1.02</b>	<b>0.15</b>	
<b>NMS 07/16/05B</b>	<b>0.51</b>	<b>0.03</b>	<b>0.07</b>	<b>0.06</b>	<b>0.92</b>	<b>0.55</b>	
<b>NMS 07/16/05C</b>	<b>0.24</b>	<b>&lt;0.03</b>	<b>&lt;0.03</b>	<b>0.028</b>	<b>0.96</b>	<b>0.22</b>	
<b>NMS</b>	<b>0.96</b>	<b>0.014</b>	<b>0.025</b>	<b>0.0301</b>	<b>3.76</b>	<b>0.1515</b>	
<b>NMS</b>	<b>0.428</b>	<b>0.017</b>	<b>0.036</b>	<b>0.0406</b>	<b>1.67</b>	<b>0.2620</b>	
<b>NMS</b>	<b>0.084</b>	<b>0.01</b>	<b>0.024</b>	<b>0.0242</b>	<b>1.22</b>	<b>0.1640</b>	
<b>NMS</b>	<b>0.018</b>	<b>-0.005</b>	<b>0.002</b>	<b>0.0086</b>	<b>0.084</b>	<b>0.0372</b>	
<b>NMS-A</b>	<b>0.112</b>	<b>&lt;0.005</b>	<b>0.038</b>	<b>0.0460</b>	<b>4.38</b>	<b>0.21</b>	
<b>NMS-B</b>	<b>0.027</b>	<b>0.029</b>	<b>0.043</b>	<b>0.0570</b>	<b>4.17</b>	<b>0.31</b>	
<b>NMS #1</b>	<b>0.948</b>	<b>&lt;0.005</b>	<b>0.021</b>	<b>0.0330</b>	<b>2.54</b>	<b>0.17</b>	
<b>SULFRAC</b>	<b>0.53</b>	<b>&lt;0.03</b>	<b>&lt;0.03</b>	<b>0.02</b>	<b>0.32</b>	<b>0.15</b>	
<b>SAMPLE</b>	<b>Pt</b>	<b>Pd</b>	<b>Ir</b>		<b>Ru</b>	<b>Os</b>	<b>Rh</b>
<b>DESCRIPTION</b>	<b>ppb</b>	<b>ppb</b>	<b>ppb</b>		<b>ppb</b>	<b>ppb</b>	<b>ppb</b>

<b>NMS AREA &amp; MSFLT</b>							
<b>NMS #1</b>	<b>8</b>	<b>22</b>	<b>&lt;2</b>	<b>&lt;2</b>	<b>2</b>	<b>&lt;2</b>	
<b>MSFLT</b>	<b>133</b>	<b>153</b>	<b>10</b>	<b>20</b>	<b>13</b>	<b>15</b>	
<b>SAMPLE DESCRIPTION</b>	<b>Au ppm</b>	<b>Pt ppm</b>	<b>Pd ppm</b>	<b>Co %</b>	<b>Cu %</b>	<b>Ni %</b>	
<b>MSFLT &amp; S1</b>							
<b>MSFLT</b>	<b>0.036</b>	<b>&lt;0.005</b>	<b>0.083</b>	<b>0.143</b>	<b>7.64</b>	<b>0.86</b>	
<b>S1</b>	<b>0.01</b>	<b>0.014</b>	<b>0.006</b>	<b>0.010</b>	<b>0.159</b>	<b>0.03</b>	

<b>SAMPLE DESCRIPTION</b>	Au	Pt	Pd	Co %	Cu %	Ni %	
<b>MS AREA</b>	ppm	ppm	ppm				
MS	0.004	-0.005	0.004	0.029	0.057	0.06	
MS	0.194	0.038	0.072	0.0667	1.75	0.5910	
MS	0.033	0.095	0.104	0.0794	1.49	0.7220	
MS	0.039	0.07	0.11	0.0939	1.92	0.8020	
MS	0.035	0.119	0.138	0.0883	0.531	0.8570	
MS	0.005	-0.005	0.002	0.0063	0.0159	0.0215	
MS	0.053	0.085	0.061	0.0467	0.567	0.3840	
MS	0.098	-0.005	0.023	0.0545	2.93	0.2450	
MS	0.047	0.083	0.097	0.0612	0.0579	0.6050	
MS				0.083	3.728	0.651	
	Au	Pt	Pd				
	(oz/t)	(g/t)	(g/t)				
MS(-1)	0.006	<0.03	0.20	0.09	2.45	0.88	
	Au	Pd	Pt				
	(g/t)	(g/t)	(g/t)				
MS(-2A)	<0.03	0.10	0.05	0.110	1.99	0.82	

<b>SAMPLE DESCRIPTION</b>				Co %	Cu %	Ni %	
<b>MS-2 AREA</b>	Au	Pt	Pd				
	(oz/t)	(oz/t)	(oz/t)				
MS-2	0.003	<0.001	0.006	0.08	2.36	0.77	
MS-2				0.1134	1.997	0.9298	
MS-2				0.0294	0.2109	0.2650	
MS-2 (PM04 25/9/2)				0.0859	1.4312	0.7729	
	<b>SAMPLE DESCRIPTION</b>						
	<b>MS-3 AREA</b>						
MS-3(DPCR 1A)	0.03	<0.03	0.09	0.075	0.82	0.62	
MS-3(DPCR 1B)	<.03	0.09	0.1	0.072	0.62	0.63	
MS-3 (DPCR 2A)	0.05	0.1	0.13	0.075	1.14	0.67	
MS-3 (DPCR 2B)	0.03	0.04	0.09	0.08	0.88	0.65	

<b>MS-3 (DPCR 2C)</b>	<b>0.04</b>	<b>&lt;0.03</b>	<b>&lt;0.03</b>	<b>0.02</b>	<b>0.29</b>	<b>0.12</b>	
<b>MS-3 (DPCR)</b>	<b>0.059</b>	<b>0.017</b>	<b>0.034</b>	<b>0.022</b>	<b>0.581</b>	<b>0.163</b>	
<b>MS-3 (DPCR)</b>	<b>0.497</b>	<b>0.006</b>	<b>0.059</b>	<b>0.0493</b>	<b>1.83</b>	<b>0.347</b>	
<b>MS-3 (DPCR)</b>	<b>0.03</b>	<b>0.006</b>	<b>0.014</b>	<b>0.0145</b>	<b>0.1635</b>	<b>0.0872</b>	
<b>MS-3 (DPCR)</b>				<b>0.018</b>	<b>0.2197</b>	<b>0.1412</b>	
<b>SAMPLE</b>	<b>Au</b>	<b>Pt</b>	<b>Pd</b>	<b>Co</b>	<b>Cu</b>	<b>Ni</b>	
<b>DESCRIPTION</b>	<b>ppm</b>	<b>ppm</b>	<b>ppm</b>	<b>%</b>	<b>%</b>	<b>%</b>	
<b>NMS AREA &amp; SULFRAC</b>							
<b>NMS 07/16/05A</b>	<b>0.11</b>	<b>&lt;0.03</b>	<b>&lt;0.03</b>	<b>0.023</b>	<b>1.02</b>	<b>0.15</b>	
<b>NMS 07/16/05B</b>	<b>0.51</b>	<b>0.03</b>	<b>0.07</b>	<b>0.06</b>	<b>0.92</b>	<b>0.55</b>	
<b>NMS 07/16/05C</b>	<b>0.24</b>	<b>&lt;0.03</b>	<b>&lt;0.03</b>	<b>0.028</b>	<b>0.96</b>	<b>0.22</b>	
<b>NMS</b>	<b>0.96</b>	<b>0.014</b>	<b>0.025</b>	<b>0.0301</b>	<b>3.76</b>	<b>0.1515</b>	
<b>NMS</b>	<b>0.428</b>	<b>0.017</b>	<b>0.036</b>	<b>0.0406</b>	<b>1.67</b>	<b>0.2620</b>	
<b>NMS</b>	<b>0.084</b>	<b>0.01</b>	<b>0.024</b>	<b>0.0242</b>	<b>1.22</b>	<b>0.1640</b>	
<b>NMS</b>	<b>0.018</b>	<b>-0.005</b>	<b>0.002</b>	<b>0.0086</b>	<b>0.084</b>	<b>0.0372</b>	
<b>NMS-A</b>	<b>0.112</b>	<b>&lt;0.005</b>	<b>0.038</b>	<b>0.0460</b>	<b>4.38</b>	<b>0.21</b>	
<b>NMS-B</b>	<b>0.027</b>	<b>0.029</b>	<b>0.043</b>	<b>0.0570</b>	<b>4.17</b>	<b>0.31</b>	
<b>NMS #1</b>	<b>0.948</b>	<b>&lt;0.005</b>	<b>0.021</b>	<b>0.0330</b>	<b>2.54</b>	<b>0.17</b>	
<b>SULFRAC</b>	<b>0.53</b>	<b>&lt;0.03</b>	<b>&lt;0.03</b>	<b>0.02</b>	<b>0.32</b>	<b>0.15</b>	
<b>SAMPLE DESCRIPTION</b>	<b>Pt ppb</b>	<b>Pd ppb</b>	<b>Ir ppb</b>		<b>Ru ppb</b>	<b>Os ppb</b>	<b>Rh ppb</b>
<b>NMS AREA &amp; MSFLT</b>							
<b>NMS #1</b>	<b>8</b>	<b>22</b>	<b>&lt;2</b>		<b>&lt;2</b>	<b>2</b>	<b>&lt;2</b>
<b>MSFLT</b>	<b>133</b>	<b>153</b>	<b>10</b>		<b>20</b>	<b>13</b>	<b>15</b>
<b>SAMPLE DESCRIPTION</b>	<b>Au ppm</b>	<b>Pt ppm</b>	<b>Pd ppm</b>	<b>Co %</b>	<b>Cu %</b>	<b>Ni %</b>	
<b>MSFLT &amp; S1</b>							
<b>MSFLT</b>	<b>0.036</b>	<b>&lt;0.005</b>	<b>0.083</b>	<b>0.143</b>	<b>7.64</b>	<b>0.86</b>	
<b>S1</b>	<b>0.01</b>	<b>0.014</b>	<b>0.006</b>	<b>0.010</b>	<b>0.159</b>	<b>0.03</b>	