

WSW

ENE

ELEV. 1320 m

ELEV. 1280 m

ELEV. 1240 m

ELEV. 1200 m

ELEV. 1160 m

ELEV. 1120 m

1 + 50 W


1 + 50 W

0 + 50 W

0 + 50 E

1 + 00 E

1 + 50 E



ASSAY TABLE: RC 88-17

From (m)	To (m)	Width (m)	Au oz/t	Ag ppm	Interval (weighted oz/t Au)
16.75	18.30	1.55	0.084	4.4	7.65m @ .224 oz/t
18.30	19.80	1.50	0.036	1.9	
19.80	21.35	1.55	0.569	10.8	
21.35	22.85	1.50	0.370	9.0	
22.85	24.40	1.55	0.063	4.9	
24.40	25.90	1.50	0.003	3.5	
32.00	33.55	1.55	0.027	1.3	
33.55	35.05	1.50	0.023	4.2	
36.60	38.10	1.50	0.082	0.9	
39.60	41.15	1.55	0.024	0.8	
71.65	73.15	1.50	0.034	0.9	
74.70	76.20	1.50	0.045	1.0	
82.30	83.80	1.50	0.024	1.2	
83.80	85.35	1.55	0.047	1.6	
85.35	86.85	1.50	0.068	8.3	4.55m @ .046 oz/t
86.85	88.40	1.55	0.010	3.4	
114.30	115.80	1.50	0.025	3.6	
115.80	117.35	1.55	0.067	4.2	
117.35	118.85	1.50	0.233	3.0	
118.85	120.40	1.55	0.216	3.4	
120.40	121.90	1.50	1.280	13.5	
121.90	123.45	1.55	0.138	2.3	
123.45	124.95	1.50	0.072	3.6	9.15m @ .335 oz/t
124.95	126.50	1.55	0.020	8.7	
126.50	128.00	1.50	0.029	7.3	
128.00	129.55	1.55	0.025	4.0	

ASSAY TABLE: RC 88-25

From (m)	To (m)	Width (m)	Au oz/t	Ag ppm	Interval (weighted oz/t Au)
22.85	24.40	1.55	0.003	5.3	7.65m @ .050 oz/t
28.95	30.50	1.55	0.007	9.3	
30.50	32.00	1.50	0.001	3.7	
33.55	35.05	1.50	0.004	5.6	
67.05	68.60	1.55	0.023	1.2	
70.10	71.65	1.55	0.024	1.1	
71.65	73.15	1.50	0.024	2.1	
74.70	76.20	1.50	0.110	5.1	
86.85	88.40	1.55	0.003	3.6	
96.00	97.55	1.55	0.019	6.5	
97.55	99.05	1.50	0.010	6.7	
99.05	100.60	1.55	0.043	4.1	
100.60	102.10	1.50	0.075	4.4	
102.10	103.65	1.55	0.048	5.8	
103.65	105.15	1.50	0.047	3.4	
105.15	106.70	1.55	0.035	3.6	
106.70	108.20	1.50	0.011	5.1	
108.20	109.75	1.55	0.052	4.6	
109.75	111.25	1.50	0.020	3.3	

ASSAY TABLE: RC 88-31

From (m)	To (m)	Width (m)	Au oz/t	Ag ppm	Interval (weighted oz/t Au)
18.90	19.80	0.90	0.041	1.8	11.60m @ .058 oz/t
19.80	21.35	1.55	0.053	1.9	
21.35	22.85	1.50	0.026	3.5	
22.85	24.40	1.55	0.076	1.8	
24.40	25.90	1.50	0.024	1.1	
25.90	27.45	1.55	0.030	2.6	
27.45	28.95	1.50	0.117	3.2	
28.95	30.50	1.55	0.087	3.0	
36.60	38.10	1.50	0.024	1.4	
38.10	39.60	1.50	0.058	11.5	

LEGEND

ASSAY CATEGORIES

- 1: < .001 oz./ton GOLD
- 2: .001 to .009 oz./ton GOLD
- 3: .010 to .049 oz./ton GOLD
- 4: .050 to .099 oz./ton GOLD
- 5: .100 to .199 oz./ton GOLD
- 6: > .200 oz./ton GOLD

* Sample has been screened and found to contain coarse gold.

LITHOLOGY

- 4: FELDSPAR PORPHYRY DIKE
- 3: SHEAR ZONE
- 2: ANDESITE FLOWS, MINOR BASALT
- 1: TUFF, FINE (LOCALLY BEDDED) TO COARSE GRAINED
- ~: SHEAR / FRACTURE

Main Shear Zone

HUNTINGTON RESOURCES INC. / CORONA CORP.

BRETT CLAIMS SECTION 8+20N (RC)

VERNON MINING DIVISION, BRITISH COLUMBIA

TECHNICAL WORK BY: GEOQUEST CONSULTING LTD. SCALE: 1:500

DRAWN BY: DBM TECHNICAL SERVICES DATE: DEC., 1988

REVISION: FIG. NO.: 881399

