

ASSAY CERTIFICATE

B.C. Ministry of Employment (Van) File # A004264

301 - 865 Hornby St., Vancouver BC V6Z 2G3

883070

FOX



SAMPLE#	Cu %	Pb %	Zn %	Ag** gm/mt	Au** gm/mt	Ba* %	As ppm	Sb ppm	Hg ppb	Se ppm
TS-FOX-1	.007	.05	.03	<.3	<.01	.37				
TS-FOX-2	1.742	.69	20.34	42.9	.29	4.03	7.4	18.60	34322	21.5
TS-FOX-3	.145	2.72	3.71	58.6	.46	19.15	5.8	2.76	33930	65.6
TS-FOX-4	.564	.05	9.83	46.2	.55	.07	65.0	5.71	40354	13.4
TS-FOX-5	2.393	1.00	31.18	124.4	.73	8.20	42.2	67.43	33753	35.4
TS-FOX-6	.223	1.15	1.81	79.5	.66	11.14	8.3	1.54	14373	43.4
TS-FOX-7	.008	.01	.07	1.9	.04	2.06				
TS-FOX-8	.177	.02	4.40	9.5	.33	.05				
TS-FOX-9	1.839	1.08	27.12	75.6	.78	7.44	10.0	22.29	39205	24.3
TS-FOX-10	2.235	.07	7.42	139.3	1.07	.41	89.2	28.62	18131	11.7
TS-FOX-11	.007	<.01	.03	<.3	.03	.03				
TS-FOX-12	.419	.04	13.77	64.9	.70	.02	55.6	4.95	55935	18.3
RE TS-FOX-12	.420	.04	13.80	65.1	.70	.02	57.6	4.74	56020	21.6
TS-FOX-13	3.520	.96	33.03	146.7	.82	8.13	32.2	49.69	34694	40.4
TS-FOX-14	4.066	.85	34.39	141.5	.55	9.60	27.7	52.90	35833	39.5
TS-FOX-15	.082	.03	.14	102.6	.52	5.03	84.0	2.35	1258	6.7
TS-FOX-16	4.167	.73	35.10	142.1	.44	8.18	18.7	28.78	35776	42.4
TS-FOX-17	.003	<.01	.05	<.3	<.01	.03				
STANDARD R-1/AU-1/SO-15	.842	1.30	2.23	98.4	3.50	.20				

GROUP 7AR - 1.000 GM SAMPLE, AQUA - REGIA (HCL-HNO3-H2O) DIGESTION TO 100 ML, ANALYSED BY ICP-ES.  
 - SAMPLE TYPE: ROCK R150 60C AG\*\* & AU\*\* BY FIRE ASSAY FROM 1 A.T. SAMPLE.  
 BA\* BY FUSION, ANALYSIS BY WHOLE ROCK ICP ASSAY.  
 Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 23 2000

DATE REPORT MAILED: Nov 7/00  
Jan. 19/01

SIGNED BY: *C. Leong* D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

NOTE Jan. 19  
 Rock sample:  
 anomalous > 25 ppm Se  
 Concentrate:  
 'problem' > 100 ppm Se

*Tom Schwelt*  
 Nov. 20, 2000  
 Jan. 19, 2001

up to 56 ppm Hg



GEOCHEMICAL ANALYSIS CERTIFICATE



B.C. Ministry of Employment (Van) File # A004264R

301 - 865 Hornby St., Vancouver BC V6Z 2G3 Submitted by: Tom G. Schroeter

SAMPLE#	As ppm	Sb ppm	Hg ppb	Se ppm
TS-FOX-2	7.4	18.60	34322	21.5
TS-FOX-3	5.8	2.76	33930	65.6
TS-FOX-4	65.0	5.71	40354	13.4
TS-FOX-5	42.2	67.43	33753	35.4
TS-FOX-6	8.3	1.54	14373	43.4
TS-FOX-9	10.0	22.29	39205	24.3
TS-FOX-10	89.2	28.62	18131	11.7
TS-FOX-12	55.6	4.95	55935	18.3
RE TS-FOX-12	57.6	4.74	56020	21.6
TS-FOX-13	32.2	49.69	34694	40.4
TS-FOX-14	27.7	52.90	35833	39.5
TS-FOX-15	84.0	2.35	1258	6.7
TS-FOX-16	18.7	28.78	35776	42.4
STANDARD DS2	56.0	8.95	258	2.2

GROUP 1F1 - 1.00 GM SAMPLE, 6 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 20 ML, ANALYSIS BY ICP/ES & MS.  
- SAMPLE TYPE: ROCK PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JAN 2 2001 DATE REPORT MAILED: *Jan 19/01* SIGNED BY: *C. Leong* D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

ASSAY CERTIFICATE



B.C. Ministry of Employment (Van) File # A004264

301 - 865 Hornby St., Vancouver BC V6Z 2G3

SAMPLE#	Cu %	Pb %	Zn %	Ag** gm/mt	Au** gm/mt	Ba* %
TS-FOX-1	.007	.05	.03	<.3	<.01	.37
TS-FOX-2	1.742	.69	20.34	42.9	.29	4.03
TS-FOX-3	.145	2.72	3.71	58.6	.46	19.15
TS-FOX-4	.564	.05	9.83	46.2	.55	.07
TS-FOX-5	2.393	1.00	31.18	124.4	.73	8.20
TS-FOX-6	.223	1.15	1.81	79.5	.66	11.14
TS-FOX-7	.008	.01	.07	1.9	.04	2.06
TS-FOX-8	.177	.02	4.40	9.5	.33	.05
TS-FOX-9	1.839	1.08	27.12	75.6	.78	7.44
TS-FOX-10	2.235	.07	7.42	139.3	1.07	.41
TS-FOX-11	.007	<.01	.03	<.3	.03	.03
TS-FOX-12	.419	.04	13.77	64.9	.70	.02
RE TS-FOX-12	.420	.04	13.80	65.1	.70	.02
TS-FOX-13	3.520	.96	33.03	146.7	.82	8.13
TS-FOX-14	4.066	.85	34.39	141.5	.55	9.60
TS-FOX-15	.082	.03	.14	102.6	.52	5.03
TS-FOX-16	4.167	.73	35.10	142.1	.44	8.18
TS-FOX-17	.003	<.01	.05	<.3	<.01	.03
STANDARD R-1/AU-1/SO-15	.842	1.30	2.23	98.4	3.50	.20

GROUP 7AR - 1.000 GM SAMPLE, AQUA - REGIA (HCL-HNO3-H2O) DIGESTION TO 100 ML, ANALYSED BY ICP-ES.  
 - SAMPLE TYPE: ROCK R150 60C AG\*\* & AU\*\* BY FIRE ASSAY FROM 1 A.T. SAMPLE.  
 BA\* BY FUSION, ANALYSIS BY WHOLE ROCK ICP ASSAY.  
Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 23 2000 DATE REPORT MAILED: *Nov 7/00* SIGNED BY: *C. Leong* .D. TOYE, C.LEONG, J. WANG; CERTIFIED B.C. ASSAYERS



ASSAY CERTIFICATE



B.C. Ministry of Employment (Van) File # A004264

301 - 865 Hornby St., Vancouver BC V6Z 2G3

SAMPLE#	Cu %	Pb %	Zn %	Ag** gm/mt	Au** gm/mt	Ea* %	As ppm	Sb ppm	Hg ppb	Se ppm
TS-FOX-1	.007	.05	.03	<.3	<.01	.37				
TS-FOX-2	1.742	.69	20.34	42.9	.29	4.03	7.4	18.60	34322	21.5
TS-FOX-3	.145	2.72	3.71	58.6	.46	19.15	5.8	2.76	33930	65.6
TS-FOX-4	.564	.05	9.83	46.2	.55	.07	65.0	5.71	40354	13.4
TS-FOX-5	2.393	1.00	31.18	124.4	.73	8.20	42.2	67.43	33753	35.4
TS-FOX-6	.223	1.15	1.81	79.5	.66	11.14	8.3	1.54	14373	43.4
TS-FOX-7	.008	.01	.07	1.9	.04	2.06				
TS-FOX-8	.177	.02	4.40	9.5	.33	.05				
TS-FOX-9	1.839	1.08	27.12	75.6	.78	7.44	10.0	22.29	39205	24.3
TS-FOX-10	2.235	.07	7.42	139.3	1.07	.41	89.2	28.62	18131	11.7
TS-FOX-11	.007	<.01	.03	<.3	.03	.03				
TS-FOX-12	.419	.04	13.77	64.9	.70	.02	55.6	4.95	55935	18.3
RE TS-FOX-12	.420	.04	13.80	65.1	.70	.02	57.6	4.74	56020	21.6
TS-FOX-13	3.520	.96	33.03	146.7	.82	8.13	32.2	49.69	34694	40.4
TS-FOX-14	4.065	.85	34.39	141.5	.55	9.50	27.7	52.90	35833	39.5
TS-FOX-15	.082	.03	.14	102.6	.52	5.03	84.0	2.35	1258	6.7
TS-FOX-16	4.167	.73	35.10	142.1	.44	8.18	18.7	28.78	35776	42.4
TS-FOX-17	.003	<.01	.05	<.3	<.01	.03				
STANDARD R-1/AU-1/SO-15	.842	1.30	2.23	98.4	3.50	.20				

GROUP 7AR - 1.000 GM SAMPLE, AQUA - REGIA (HCL-HN(3-H2O) DIGESTION TO 100 ML, ANALYSED BY ICP-ES.  
 - SAMPLE TYPE: ROCK R150 60C AG\*\* & AU\*\* BY FIRE ASSAY FROM 1 A.T. SAMPLE.  
 BA\* BY FUSION, ANALYSIS BY WHOLE ROCK ICP ASSAY.  
 Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: OCT 23 2000

DATE REPORT MAILED: Nov 7/00  
Jan. 19/01

SIGNED BY: *C. Leong* D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

*Tom Schweltz*  
Nov. 20, 2000  
Jan. 19, 2001

GEOCHEMICAL ANALYSIS CERTIFICATE

B.C. Ministry of Employment (Van) File # A004264R  
301 - 865 Hornby St., Vancouver BC V6Z 2G3 Submitted by: Tom G. Schroeter



P. 02

FAX NO. 6042531716

JAN-19-2001 FRI 02:12 PM ACME ANALYTICAL LAB

SAMPLE#	As ppm	Sb ppm	Hg ppb	Se ppm
TS-FOX-2	7.4	18.60	34322	21.5
TS-FOX-3	5.8	2.76	33930	65.6
TS-FOX-4	65.0	5.71	40354	13.4
TS-FOX-5	42.2	67.43	33753	35.4
TS-FOX-6	8.3	1.54	14373	43.4
TS-FOX-9	10.0	22.29	39205	24.3
✓ TS-FOX-10	89.2	28.62	18131	11.7
TS-FOX-12	55.6	4.95	55935	18.3
✓ RE TS-FOX-12	57.6	4.74	56020	21.6
TS-FOX-13	32.2	49.69	34694	40.4
✓ TS-FOX-14	27.7	52.90	35833	39.5
TS-FOX-15	84.0	2.35	1258	6.7
✓ TS-FOX-16	18.7	28.78	35776	42.4
STANDARD DS2	56.0	8.95	258	2.2

GROUP 1F1 - 1.00 GM SAMPLE, 6 ML 2-2-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 20 ML, ANALYSIS BY ICP/ES & MS.  
- SAMPLE TYPE: ROCK PULP Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: JAN 2 2001 . DATE REPORT MAILED: *Jan 19/01* SIGNED BY: *C. Toy* D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

*up to 56 ppm Hg*