



BONDAR CLEGG



Geochemical Lab Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
REPORT: V00-02065.0 (COMPLETE)

DATE RECEIVED: 03-NOV-00 DATE PRINTED: 6-NOV-00 PAGE 1 OF 3 PROJECT: NONE GIVEN2

| SAMPLE NUMBER | ELEMENT UNITS | Ag PPM | Cu PPM | Pb PPM | Zn PPM | Mo PPM | Ni PPM | Co PPM | Cd PPM | Bi PPM | As PPM | Sb PPM | Fe PPM | Tot PCT | Mn PPM | Te PPM | Ba PPM | Cr PPM | V PPM | Sn PPM | W PPM | La PPM | Al PCT | Mg PCT | Ca PCT | Na PCT | K PCT | Sr PPM | Y PPM | Ga PPM | Li PPM | Nb PPM | Sc PPM | Ta PPM | Ti PCT | Zr PPM | S PCT |
|---------------|---------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|---------|--------|--------|--------|--------|-------|--------|-------|--------|--------|--------|--------|--------|-------|--------|-------|--------|--------|--------|--------|--------|--------|--------|-------|
| TS-GM-1 | | 2.1 | 17383 | 2 | 167 | 5 | >20000 | 801 | 1.6 | <5 | <5 | <5 | >10.00 | 1020 | <25 | <5 | 1310 | 82 | <20 | <20 | <5 | 0.77 | >10.00 | 2.91 | 0.11 | 0.03 | 12 | <5 | <10 | <2 | <5 | 17 | 8 | 0.08 | <5 | >10.00 | |
| TS-GM-2 | | 1.1 | 1262 | 104 | 113 | 4 | 2005 | 105 | <1.0 | <5 | <5 | <5 | >10.00 | 1257 | <25 | 82 | 828 | 583 | <20 | <20 | <5 | 5.72 | 9.90 | 5.49 | 1.01 | 0.25 | 243 | 13 | <10 | 5 | 52 | 43 | 5 | 0.70 | 13 | 1.622 | |
| TS-GM-3 | | 5.3 | >20000 | <2 | 168 | 5 | 10259 | 418 | <1.0 | <5 | <5 | <5 | >10.00 | 1066 | <25 | <5 | 2024 | 91 | <20 | 20 | <5 | 1.01 | >10.00 | 2.62 | 0.11 | 0.02 | 15 | <5 | <10 | <2 | <5 | 18 | 12 | 0.09 | <5 | >10.00 | |
| TS-GM-4 | | <.5 | 1032 | <2 | 127 | 4 | 3182 | 210 | <1.0 | <5 | <5 | <5 | >10.00 | 1387 | <25 | 8 | 3203 | 82 | <20 | <20 | <5 | 1.24 | >10.00 | 0.76 | 0.11 | 0.02 | 24 | <5 | <10 | 3 | <5 | 9 | <5 | 0.08 | <5 | 2.139 | |
| TS-GM-5 | | <.5 | 291 | 16 | 106 | 3 | 958 | 155 | <1.0 | <5 | <5 | <5 | >10.00 | 1396 | <25 | 7 | 2746 | 95 | <20 | <20 | <5 | 1.02 | >10.00 | 0.72 | 0.15 | 0.02 | 16 | <5 | <10 | 3 | <5 | 11 | 7 | 0.08 | <5 | 1.398 | |
| TS-GM-6 | | 1.1 | 7268 | <2 | 213 | 4 | 16257 | 554 | <1.0 | <5 | <5 | <5 | >10.00 | 1201 | <25 | <5 | 3432 | 34 | <20 | <20 | <5 | 0.22 | >10.00 | 0.13 | 0.02 | 0.01 | <1 | <5 | <10 | <2 | <5 | <5 | 13 | 0.02 | <5 | 8.774 | |
| TS-GM-7 | | 0.5 | 4597 | <2 | 143 | 5 | 7218 | 392 | <1.0 | <5 | <5 | <5 | >10.00 | 1456 | <25 | 28 | 4914 | 499 | <20 | <20 | <5 | 2.85 | 9.49 | 3.75 | 0.48 | 0.09 | 98 | 7 | <10 | 4 | 41 | 31 | <5 | 0.42 | <5 | 7.147 | |
| TS-GM-8 | | 1.0 | 5756 | 4 | 178 | 5 | >20000 | 1216 | <1.0 | <5 | <5 | <5 | >10.00 | 788 | <25 | <5 | 1372 | 54 | <20 | <20 | <5 | 0.41 | 9.84 | 1.49 | 0.07 | 0.02 | 6 | <5 | <10 | <2 | <5 | 10 | 17 | 0.05 | <5 | >10.00 | |
| TS-GM-9 | | 3.8 | >20000 | <2 | 199 | 5 | >20000 | 1038 | <1.0 | <5 | <5 | <5 | >10.00 | 911 | <25 | <5 | 1656 | 69 | <20 | 24 | <5 | 0.65 | >10.00 | 1.99 | 0.07 | 0.01 | 12 | <5 | <10 | <2 | <5 | 14 | <5 | 0.06 | <5 | >10.00 | |

"GIANT MASCOT"

Tom Schueler
Nov. 20/00

Feb. 1/01
TGS requested over telephone
to Rick McCaffrey:
'precise' amts. for Cu, Ni
(w/ YH) -> sign, i.e. 1, 3, 8, 9)
- RM started for sample # TS-GM-10
Also - Feb. 2 - gave RM sample # TS-GM-10
FA-36: 'low level' H, Ad, Au
GA-50: Ni & Cu

Giant Mascot
883257



BONDAR CLEGG



Geochemical Lab Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
REPORT: V00-02065.0 (COMPLETE)

DATE RECEIVED: 03-NOV-00

DATE PRINTED: 6-NOV-00

PROJECT: NONE GIVEN2
PAGE 2 OF 3

Table with columns: STANDARD NAME, ELEMENT UNITS, and various elements (Ag, Cu, Pb, Zn, Mo, Ni, Co, Cd, Bi, As, Sb, Fe, Tot, Mn, Te, Ba, Cr, V, Sn, W, La, Al, Mg, Ca, Na, K, Sr, Y, Ga, Li, Nb, Sc, Ta, Ti, Zr, S) with their respective values in PPM or PCT.



BONDAR CLEGG



Geochemical Lab Report

REPORT: V00-02065.0 (COMPLETE)

REFERENCE:

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY

SUBMITTED BY: T. SCHROETER

PROJECT: NONE GIVEN2

DATE RECEIVED: 03-NOV-00 DATE PRINTED: 6-NOV-00

| DATE APPROVED | ELEMENT | NUMBER OF ANALYSES | LOWER DETECTION | EXTRACTION | METHOD |
|---------------|-----------|--------------------|-----------------|-------------------|---------------------|
| 001104 | 1 Ag | 9 | 0.5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 2 Cu | 9 | 1 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 3 Pb | 9 | 2 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 4 Zn | 9 | 2 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 5 Mo | 9 | 1 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 6 Ni | 9 | 1 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 7 Co | 9 | 1 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 8 Cd | 9 | 1.0 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 9 Bi | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 10 As | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 11 Sb | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 12 Fe Tot | 9 | 0.01 PCT | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 13 Mn | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 14 Te | 9 | 25 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 15 Ba | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 16 Cr | 9 | 2 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 17 V | 9 | 2 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 18 Sn | 9 | 20 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 19 W | 9 | 20 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 20 La | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 21 Al | 9 | 0.01 PCT | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 22 Mg | 9 | 0.01 PCT | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 23 Ca | 9 | 0.01 PCT | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 24 Na | 9 | 0.01 PCT | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 25 K | 9 | 0.01 PCT | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 26 Sr | 9 | 1 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 27 Y | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 28 Ga | 9 | 10 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 29 Li | 9 | 2 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 30 Nb | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 31 Sc | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 32 Ta | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 33 Ti | 9 | 0.01 PCT | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 34 Zr | 9 | 5 PPM | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |
| 001104 | 35 S | 9 | 0.002 PCT | HF-HNO3-HClO4-HCL | INDUC. COUP. PLASMA |

| SAMPLE TYPES | NUMBER | SIZE FRACTIONS | NUMBER | SAMPLE PREPARATIONS | NUMBER |
|--------------|--------|----------------|--------|---------------------|--------|
| R ROCK | 9 | 2 -150 | 9 | CRUSH/SPLIT & PULV. | 9 |

REMARKS: Please note that carryover to the blanks and standards due to high level of some elements in the samples. 11/4 geng

REPORT COPIES TO: MR. TOM G. SCHROETER

INVOICE TO: MR. TOM G. SCHROETER

 This report must not be reproduced except in full. The data presented in this report is specific to those samples identified under "Sample Number" and is applicable only to the samples as received expressed on a dry basis unless otherwise indicated



BONDAR CLEGG



Geochemical Lab Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
REPORT: V00-02065.0 (COMPLETE)

DATE RECEIVED: 03-NOV-00

DATE PRINTED: 6-NOV-00

PAGE 3 OF 3

PROJECT: NONE GIVEN2

| SAMPLE NUMBER | ELEMENT UNITS | Ag PPM | Cu PPM | Pb PPM | Zn PPM | Mo PPM | Ni PPM | Co PPM | Cd PPM | Bi PPM | As PPM | Sb PPM | Fe PCT | Tot PCT | Mn PPM | Te PPM | Ba PPM | Cr PPM | V PPM | Sn PPM | W PPM | La PPM | Al PCT | Mg PCT | Ca PCT | Na PCT | K PCT | Sr PPM | Y PPM | Ga PPM | Li PPM | Nb PPM | Sc PPM | Ta PPM | Ti PCT | Zr PPM | S PCT |
|---------------|---------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|---------|--------|--------|--------|--------|-------|--------|-------|--------|--------|--------|--------|--------|-------|--------|-------|--------|--------|--------|--------|--------|--------|--------|-------|
| TS-GM-6 | 1.1 | 7268 | <2 | 213 | 4 | 16257 | 554 | <1.0 | <5 | <5 | <5 | >10.00 | 1201 | <25 | <5 | 3432 | 34 | <20 | <20 | <5 | 0.22 | >10.00 | 0.13 | 0.02 | 0.01 | <1 | <5 | <10 | <2 | <5 | <5 | 13 | 0.02 | <5 | 8.774 | | |
| Duplicate | 1.5 | 7266 | <2 | 212 | 6 | 16108 | 556 | <1.0 | <5 | <5 | <5 | >10.00 | 1212 | <25 | <5 | 3386 | 34 | <20 | <20 | <5 | 0.22 | >10.00 | 0.13 | 0.03 | 0.01 | <1 | <5 | <10 | <2 | <5 | <5 | 14 | 0.02 | <5 | 8.875 | | |



BONDAR CLEGG



Geochemical
Lab
Report

BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
MR. TOM G. SCHROETER
MINERAL DEVELOP. OFFICE
300 - 865 HORNBY STREET
VANCOUVER, BC V6Z 2G3

+ + + +

Bondar Clegg Canada Limited, 130 Pemberton Avenue, North Vancouver, BC, V7P 2R5, (604) 985-0681



BONDAR CLEGG

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY

PROJECT: NONE GIVEN2

REPORT: V00-02065.2 (COMPLETE)

DATE RECEIVED: 01-FEB-01

DATE PRINTED: 2-FEB-01

PAGE 1 OF 1

| SAMPLE NUMBER | ELEMENT UNITS | Cu PCT | Ni PCT |
|------------------|------------------|-----------|-----------|
| R2 TS-GM-1 | | | 2.294 |
| R2 TS-GM-3 | | 3.63 | |
| R2 TS-GM-8 | | | 3.727 |
| R2 TS-GM-9 | | 3.05 | 2.999 |



BONDAR CLEGG

Vancouver, B.C. Canada

" U R G E N T & C O N F I D E N T I A L "

To: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
 Attention : Mr. Tom G. Schroeter
 Reference :
 Submitter : T. SCHROETER

Our Fax No: (604) 985-1071
 Your Fax No: 775-0313
 Number of Pages : 2 including this page.

Report : V00-02065.2 Status : COMPLETE Total number of samples: 4

| Element Method | Totl | Element Method | Totl | Element Method | Totl |
|------------------------|------|------------------------|------|----------------|------|
| Cu AAS LOW LEVEL ASSAY | 2 | Ni AAS LOW LEVEL ASSAY | 3 | | |

| Sample Preparations | Totl | Sample Type | Totl | Size Fraction | Totl | Remarks |
|----------------------|------|-------------|------|---------------|------|---------|
| SAMPLES FROM STORAGE | 4 | ROCK | 4 | -150 | 4 | |

Notes:

If you do not receive the entire transmission in legible form, please call us at (604) 985-0681.

TITLE 02-02-01 22:55:02 V00-02065.2 T. SCHROETER 01/02/01
 CLIENT BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
 PROJECT NONE GIVEN2 #SAMPLES: 4
 SPECIAL VALUES

IS Insufficient Sample
 -9 No Value Recorded

Values above the upper limit are shown as +uplimit
 Values below the lower limit are shown as -lolmt (ie not detected)

DETERMINATIONS

ELNAME METHO ECO UNI #SAM LOLMT UPLIMIT COMMENTS
 01 Cu AA-LL EA5 PCT 2 0.01 15.00 Results Reported
 02 Ni AA-LL EA5 PCT 3 0.005 15.000 Results Reported

SAMPLE PREPS

40 SAMPLE TYPE=R ROCK
 41 P80= 4 SAMPLES FROM STORAGE

FORMAT (1X,A8,3X,A1,3X,A1,3X,A20,1X,2(1X,A7,2X,A1,1X))

| BEGIN | Type | Frac | Sample ID | Cu | Ni |
|----------|------|------|-----------|------|-------|
| 20650001 | R | | 2 TS-GM-1 | -9 | 2.294 |
| 20650002 | R | | 2 TS-GM-3 | 3.63 | -9 |
| 20650003 | R | | 2 TS-GM-8 | -9 | 3.727 |
| 20650004 | R | | 2 TS-GM-9 | 3.05 | 2.999 |

END



BONDAR CLEGG



Geochemical
Lab
Report

BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
MR. TOM G. SCHROETER
MINERAL DEVELOP. OFFICE
300 - 865 HORNBY STREET
VANCOUVER, BC V6Z 2G3

+ + + + +



BONDAR CLEGG



Geochemical Lab Report

REPORT: V00-02065.2 (COMPLETE)

REFERENCE:

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
PROJECT: NONE GIVEN2

DATE RECEIVED: 01-FEB-01

SUBMITTED BY: T. SCHROETER
DATE PRINTED: 3-FEB-01

Table with columns: DATE APPROVED, ORDER, ELEMENT, NUMBER OF ANALYSES, LOWER DETECTION LIMIT, EXTRACTION, METHOD. Rows include data for Copper and Nickel.

Table with columns: SAMPLE TYPES, NUMBER, SIZE FRACTIONS, NUMBER, SAMPLE PREPARATIONS, NUMBER. Row includes data for R ROCK.

REPORT COPIES TO: MR. TOM G. SCHROETER

INVOICE TO: MR. TOM G. SCHROETER

This report must not be reproduced except in full. The data presented in this report is specific to those samples identified under "Sample Number" and is applicable only to the samples as received expressed on a dry basis unless otherwise indicated.



BONDAR CLEGG



Geochemical
Lab
Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY

PROJECT: NONE GIVEN2

REPORT: V00-02065.2 (COMPLETE)

DATE RECEIVED: 01-FEB-01

DATE PRINTED: 3-FEB-01

PAGE 1 OF 3

| SAMPLE NUMBER | ELEMENT UNITS | Cu PCT | Ni PCT |
|---------------|---------------|--------|--------|
| R2 TS-GM-1 | | | 2.294 |
| R2 TS-GM-3 | | 3.63 | |
| R2 TS-GM-8 | | | 3.727 |
| R2 TS-GM-9 | | 3.05 | 2.999 |



BONDAR CLEGG



Geochemical Lab Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY

PROJECT: NONE GIVEN2

REPORT: V00-02065.2 (COMPLETE)

DATE RECEIVED: 01-FEB-01

DATE PRINTED: 3-FEB-01

PAGE 2 OF 3

| STANDARD NAME | ELEMENT UNITS | Cu PCT | Ni PCT |
|--------------------|---------------|--------|--------|
| SU-1A | | 0.94 | 1.232 |
| Number of Analyses | | 1 | 1 |
| Mean Value | | 0.940 | 1.2321 |
| Standard Deviation | | - | - |
| Accepted Value | | 0.97 | 1.233 |



BONDAR CLEGG



Geochemical
Lab
Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY

PROJECT: NONE GIVEN2

REPORT: V00-02065.2 (COMPLETE)

DATE RECEIVED: 01-FEB-01

DATE PRINTED: 3-FEB-01

PAGE 3 OF 3

| SAMPLE NUMBER | ELEMENT UNITS | Cu PCT | Ni PCT |
|---------------|---------------|--------|--------|
| TS-GM-1 | | | 2.294 |
| Duplicate | | | 2.291 |



BONDAR CLEGG



Geochemical
Lab
Report

BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
MR. TOM G. SCHROETER
MINERAL DEVELOP. OFFICE
300 - 865 HORNBY STREET
VANCOUVER, BC V6Z 2G3

+ + + + +



BONDAR CLEGG



Geochemical Lab Report

REPORT: V00-02065.1 (COMPLETE)

REFERENCE:

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
PROJECT: NONE GIVEN2

SUBMITTED BY: T. SCHROETER
DATE RECEIVED: 27-DEC-00
DATE PRINTED: 9-FEB-01

Table with columns: DATE APPROVED, ORDER, ELEMENT, NUMBER OF ANALYSES, LOWER DETECTION LIMIT, EXTRACTION, METHOD. Rows include Au, Pt, Pd, Rh, Os, Ir, Ru with various detection limits and extraction methods.

Table with columns: SAMPLE TYPES, NUMBER, SIZE FRACTIONS, NUMBER, SAMPLE PREPARATIONS, NUMBER. Row: R ROCK, 2, 2 -150, 2, SAMPLES FROM STORAGE, 2.

REMARKS: Samples have elevated detection limits due to high Cu. Feb 8/01 WAY

REPORT COPIES TO: MR. TOM G. SCHROETER

INVOICE TO: MR. TOM G. SCHROETER

This report must not be reproduced except in full. The data presented in this report is specific to those samples identified under "Sample Number" and is applicable only to the samples as received expressed on a dry basis unless otherwise indicated



BONDAR CLEGG



Geochemical Lab Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY

PROJECT: NONE GIVEN2

REPORT: V00-02065.1 (COMPLETE)

DATE RECEIVED: 27-DEC-00

DATE PRINTED: 9-FEB-01

PAGE 1 OF 1

| SAMPLE NUMBER | ELEMENT UNITS | Au PPB | Pt PPB | Pd PPB | Rh PPB | Os PPB | Ir PPB | Ru PPB |
|---------------|---------------|--------|--------|--------|--------|--------|--------|--------|
| R2 TS-GM-7 | | 53 | <46 | 48 | <5 | <10 | 2 | <50 |
| R2 TS-GM-9 | | 28 | <210 | 580 | 29 | <28 | 24 | <150 |



BONDAR CLEGG



Geochemical
Lab
Report

TGS

BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
MR. TOM G. SCHROETER
MINERAL DEVELOP. OFFICE
300 - 865 HORNBY STREET
VANCOUVER, BC V6Z 2G3

+ + + + +

WJ



BONDAR CLEGG



Geochemical Lab Report

REPORT: V01-00162.0 (COMPLETE)

REFERENCE:

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY
PROJECT: NONE GIVEN2

SUBMITTED BY: T. SCHROETER
DATE RECEIVED: 05-FEB-01
DATE PRINTED: 12-FEB-01

Table with columns: DATE APPROVED, ORDER, ELEMENT, NUMBER OF ANALYSES, LOWER DETECTION LIMIT, EXTRACTION, METHOD. Rows include Au, Gold, Pt, Pd, Cu, Ni.

Table with columns: SAMPLE TYPES, NUMBER, SIZE FRACTIONS, NUMBER, SAMPLE PREPARATIONS, NUMBER. Row: R ROCK, 1, 2 -150, 1, CRUSH/SPLIT & PULV., 1

REMARKS: Please note: Weight was reduced for AUD, PTd, and Pd because of high Ni to facilitate fusion quality.

REPORT COPIES TO: MR. TOM G. SCHROETER

INVOICE TO: MR. TOM G. SCHROETER

This report must not be reproduced except in full. The data presented in this report is specific to those samples identified under "Sample Number" and is applicable only to the samples as received expressed on a dry basis unless otherwise indicated



BONDAR CLEGG



Geochemical
Lab
Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY

PROJECT: NONE GIVEN2

REPORT: V01-00162.0 (COMPLETE)

DATE RECEIVED: 05-FEB-01

DATE PRINTED: 12-FEB-01

PAGE 1 OF 3

| SAMPLE NUMBER | ELEMENT UNITS | Au Wt1 GM | AU PPB | PT PPB | PD PPB | Cu PCT | Ni PCT |
|------------------|------------------|--------------|-----------|-----------|-----------|-----------|-----------|
| R2 TS-GM-10 | | 15.08 | 18 | 148 | 155 | 1.54 | 3.035 |



BONDAR CLEGG



Geochemical Lab Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY

PROJECT: NONE GIVEN2

REPORT: V01-00162.0 (COMPLETE)

DATE RECEIVED: 05-FEB-01

DATE PRINTED: 12-FEB-01

PAGE 2 OF 3

| STANDARD NAME | ELEMENT UNITS | Au Wt1 GM | AU PPB | PT PPB | PD PPB | Cu PCT | Ni PCT |
|--------------------|---------------|-----------|--------|--------|--------|--------|--------|
| SU-1A | | - | - | - | - | 0.94 | 1.248 |
| Number of Analyses | | - | - | - | - | 1 | 1 |
| Mean Value | | - | - | - | - | 0.936 | 1.2480 |
| Standard Deviation | | - | - | - | - | - | - |
| Accepted Value | | - | - | - | - | 0.97 | 1.233 |
| ANALYTICAL BLANK | | - | 1 | <5 | <1 | - | - |
| Number of Analyses | | - | 1 | 1 | 1 | - | - |
| Mean Value | | - | 1.0 | 2.5 | 0.5 | - | - |
| Standard Deviation | | - | - | - | - | - | - |
| Accepted Value | | <0.01 | 5 | 5 | 5 | <0.01 | <0.001 |
| ST 260 | | - | 800 | 2118 | 1455 | - | - |
| Number of Analyses | | - | 1 | 1 | 1 | - | - |
| Mean Value | | - | 800.0 | 2118.0 | 1455.0 | - | - |
| Standard Deviation | | - | - | - | - | - | - |
| Accepted Value | | - | 880 | 2230 | 1510 | - | - |



BONDAR CLEGG



Geochemical
Lab
Report

CLIENT: BC MINISTRY OF ENERGY AND MINES-GEOLOGICAL SURVEY

PROJECT: NONE GIVEN2

REPORT: V01-00162.0 (COMPLETE)

DATE RECEIVED: 05-FEB-01

DATE PRINTED: 12-FEB-01

PAGE 3 OF 3

| SAMPLE NUMBER | ELEMENT UNITS | Au Wt1 GM | AU PPB | PT PPB | PD PPB | Cu PCT | Ni PCT |
|------------------|------------------|--------------|-----------|-----------|-----------|-----------|-----------|
| TS-GM-10 | | 15.08 | 18 | 148 | 155 | 1.54 | 3.035 |
| Duplicate | | | | | | 1.53 | 3.056 |

Schroeter, Tom EM:EX

From: Schroeter, Tom EM:EX
Sent: Thursday, October 18, 2001 9:58 AM
To: 'cmansfield@bondarclegg.com'
Cc: Pinsent, Robert EM:EX; Nixon, Graham EM:EX
Subject: Sample Disposals

Further to your recent e-mail, please DISPOSE of samples TS-GM-1 to TS-GM-9, incl. (Report # VOO-02065.0) . Tom.

B.C. MINISTRY OF ENERGY, MINES AND
PETROLEUM RESOURCES

To: Graham Nixon Date: Nov. 21/00
From: Tom Schroeter

- For your approval.
- For your information.
- For necessary action.
- Send me copy of reply.
- For your comments.
- Prepare reply for my signature.
- Prepare draft of reply.
- Return to me.
- File.
- For signature.
- Wish to discuss.

Re: from Grant Mascot

→ samples for you, plus
prelim. assays
[Note: waiting for PGE analyses]

TS-GM-6
TS-GM-9

Tom.

M28-1737

B.C. MINISTRY OF ENERGY, MINES AND
PETROLEUM RESOURCES

To: Jacques Houle Date: Nov. 21/00
From: Tom Schroeter

- For your approval.
- For your information.
- For necessary action.
- Send me copy of reply.
- For your comments.
- Prepare reply for my signature.
- Prepare draft of reply.
- Return to me.
- File.
- For signature.
- Wish to discuss.

Re: from Grant Mascot

→ samples for you, plus
prelim. assays
[Note: waiting for PGE analyses]

TS-GM-6
TS-GM-9

Tom.

M28-1737

NOV. 2/00

Bondar Clegg
130 Pemberton Ave.
North Vancouver, B.C.
V7P 2R5

Re: SAMPLES FOR ANALYSES

TS-GM-1 to TS-GM-9, inclusive

Request: All element (34) - IC-30

Nov. 1/00 'chat' with
Rick McCaffrey (tel. 985-0681)
* 1) All element (34) [IC-30] pkg. ~ \$10.80/sa. GSB(MEM) gets 20% discount = \$9.25/sa.
2) 5-element pkg. [IC-30] eg. Ni, Cu, Co, Cr, As = \$1.85/sa
3) Au, Pt, Pd, Ir, Os, Ru, Rh [FA-70] = \$1.85/sa
4) Au, Pt, Pd (FA-36) ~~4~~

Thanks,
Tom Schraeter, P. Eng./P. Ge.
Senior Regional Geologist

Feb. 2/01

Bandar Clegg
130 Pemberton Ave.
North Vancouver, BC
V7P 2A5

ATTN: Rick McCaffrey

Re: SAMPLE FOR ANALYSIS

IS-GM-10

REQUEST: a) FA-36 : 'low level' Au, Pt, Pd
b) GA-50: Ni (up to 4%)
Cu (up to 6%)

Tan Schmitt