





Boulder Bowl Sample No.	Gold oz/ton	Silver oz/ton	Copper %	Lead %	Zinc %
11514	0.182	11.81	0.08	17.40	6.73
11515	0.006	1.46	0.01	2.04	3.34
11516	0.153	4.78	0.15	8.22	11.25
11517	0.001	0.12	-	0.06	0.07
11518	0.015	1.34	0.03	2.26	1.16
11519	0.039	2.65	0.02	3.94	6.65
11520	0.005	0.75	0.60	0.87	1.61
11521	0.069	6.71	0.79	9.86	11.50
11522	0.018	2.06	0.04	4.03	7.90
11523	0.056	4.64	0.13	7.98	7.95
11524	0.142	3.62	0.61	5.00	4.89
11525	0.085	3.88	0.27	6.65	6.78
11526	0.038	3.94	0.08	6.17	10.60
11527	0.027	1.57	0.03	1.96	4.24
11528	0.014	1.46	0.02	2.06	4.26
11553	0.062	3.24	0.14	3.57	9.20
11554	0.053	2.63	0.04	3.85	10.60
11555	0.047	3.79	0.01	6.02	15.40
Avg 18 Samples	0.056	3.36	.17	5.10	6.90

