

Polaris Taku

886117

Table 1
MINE PRODUCTION 1938 - 1951

Year	Tons Mined	Tons Milled	Ozs Gold (net)	Av. Gold Grade (oz/t)	Ozs Silver (net)	Av. Silver Grade (oz/t)
1938	52,678	58,759	12,765	0.22	495	0.008
1939	69,044	68,967	16,995	0.25	874	0.012
1940	80,320	80,364	22,954	0.29	1371	0.017
1941	89,684	89,609	19,091	0.21	1212	0.014
1942	30,966	31,335	17,506	0.56	1175	0.037
1946	25,724	25,724	3,267	0.13	486	0.019
1947	92,039	92,039	22,714	0.25	1589	0.017
1948	102,622	102,622	29,156	0.28	1311	0.013
1949	93,806	93,806	39,345	0.42	1384	0.015
1950	95,666	95,666	33,228	0.35	1182	0.012
1951	20,700	20,700	14,583	0.70	681	0.033
	—————	—————	—————	—————	—————	—————
	753,249	759,600	231,604	0.30	11,760	0.015