



Victoria
889350

DEPT. OF MINES
AND PETROLEUM RESOURCES

Rec'd AUG 11 1975

DEPARTMENT OF MINES AND PETROLEUM RESOURCES
VICTORIA

SMITHERS, B. C.

SAMPLE RECEIVED FROM T. SCHROETER

ADDRESS P. O. Box 877, Smithers, B. C.

LABORATORY No.	SUBMITTER'S MARK	LABORATORY REPORT					
		oz/T <u>Au</u>	oz/T <u>Ag</u>	% <u>Ni</u>	% <u>Co</u>	% <u>As</u>	% <u>U₃₋₈</u>
		VICTORIA					
15546M	V-1 No. 00	7.11	Tr	0.99	3.93	29.6	0.032
15547M	V-2 talus	0.02	Tr	Tr	0.01	<0.01	N.D.
15548M	V-3 "crest"	0.02	Tr	0.01	0.09	0.46	N.D.
15549M	V-4 No. 1	10.34	2.1	0.21	7.75	33.81	0.002
15550M	TL-1	Tr	Tr	prospector - Telkwa			

THIS DOCUMENT, OR ANY PART THEREOF, MAY NOT BE REPRODUCED
FOR PROMOTIONAL OR ADVERTISING PURPOSES.

DATE August 6, 1975

W. M. Johnson
CHIEF ANALYST AND ASSAYER.



DEPT. OF MINES
AND PETROLEUM RESOURCES
Rec'd AUG 11 1975
SMITHERS, B. C.

DEPARTMENT OF MINES AND PETROLEUM RESOURCES
VICTORIA

SAMPLE RECEIVED FROM J. Schroeter

ADDRESS P.O. Box 877, Smithers, B.C. VICTORIA

SEMI QUANTITATIVE SPECTROGRAPHIC ANALYSIS

Laboratory No.	ISS46M	ISS47M	ISS48M	ISS49M	ISS50M	
Submitter's No.	V-1	V-2	V-3	V-4	TL-1	
Si	>10.0	>10.0	>10.0	>10.0	>10.0	
Mn	0.15	0.05	0.15	0.07	0.04	
Al	2.0	10.0	1.5	0.6	1.0	
Mg	1.0	0.1	1.5	0.75	0.07	
Pb	TL	-	-	-	0.05	
Ca	1.5	2.0	5.5	1.0	<0.1	Prospector Telkwa
Fe	10.0	0.85	6.0	3.5	4.0	
V	T	T	0.02	T	TL	
Cu	T	T	T	0.01	0.02	
Ag	T	-	-	TA	TL	
Zn	-	-	-	-	0.015	
Na	0.05	>3.0	0.75	-	0.25	
K	0.75	0.75	0.5	-	0.5	
Ti	0.04	0.04	0.05	0.03	0.03	
Zr	T		T	T	T	
Ni	0.55	T	0.01	0.16	T	
Co	>1.0	0.01	0.06	>2.0	T	
Sr	T	T	T	T	T	
Cr	T	T	T	T	T	
Ba	T	T	T	T	0.03	
Traces:		Bi		Ge		
As	>5.0	As - N.D.	As - 0.2	As >7.0	Mo - 0.025	

Bi 0.5
Mo 0.02
U N.D.

THIS DOCUMENT, OR ANY PART THEREOF, MAY NOT BE REPRODUCED FOR PROMOTIONAL OR ADVERTISING PURPOSES.

Mo - 0.025
U - N.D.
Mo - 0.15
U - N.D.

Bi - 0.03
Ca - 0.25
Ce - 0.14
Nd - 0.04

DATE August 6/75

W. M. Johnson
CHIEF ANALYST AND ASSAYER