

0.112(1992)  
JUNE 10, 1992

*George Cross News Letter*  
"Reliable Reporting"

CREW NATURAL RESOURCES LTD. (CWT-V)

METALLURGICAL RESULTS RECEIVED - Dr. G. Wright, P.Eng.,  
reports Crew Natural

Resources Ltd. has received preliminary results of the metallurgical program, conducted by Beattie Consultants Ltd., on representative samples from the 100%-owned Red Dog copper/gold project located near Port Hardy on northern Vancouver Island, B.C. The initial testwork was directed at rougher flotation with a view to maximizing the recoveries of copper and gold. Testwork was completed on three composite samples of Red Dog drill core; results are listed below:

COMPOSITE SAMPLE ASSAYS

| SAMPLE NO.  | COPPER % | IRON % | MOLYBDENUM % | GOLD OZ/T | SILVER OZ/TON |
|-------------|----------|--------|--------------|-----------|---------------|
| Composite 1 | 0.42     | 8.80   | 0.018        | 0.025     | 0.024         |
| Composite 2 | .59      | 8.10   | .015         | .021      | .016          |
| Composite 3 | .46      | 9.00   | .012         | .022      | .011          |

Samples were ground to give 70% passing 200 mesh which gave the following rougher recoveries, based on a flotation time of 12 minutes:

Copper rougher recovery - 93.7-95.4%

Gold rougher recovery - 78.5-81.1%

Ongoing testwork is directed toward cleaning copper concentrates, testing blends of Red Dog o that from a nearby existing mining operation, scavenging of copper from the pyrite rougher concentrate and recovery of gold from the pyrite concentrate. (SEE GCNL No.48, 9Mar92, P.2 FOR PREVIOUS PROJECT INFORMATION)

92L 200