




Province of
British Columbia

Ministry of
Energy, Mines and
Petroleum Resources

1A, 3411 Shenton Road
Nanaimo
British Columbia
V9T 2H1

Double Registered

June 13, 1989



827416

LARA

92B/13

File: 14675-55-04\LAR

14745-30

Abermin Corporation
1500-1075 West Georgia Street
Vancouver, B. C.
V6E 3C9

Attention: J. S. Kinney, Vice President

Dear Sir:

Re: 10,000 Bulk Sample - Lara Property

Further to your request for the return of the \$30,000.00 bond for Permit MX-8-43, a request for the bond to be replaced was made of Minnova Incorporated. It would appear that Minnova is reluctant to replace the bond at the present time.

An order has been given for the ore stockpiled on the surface to be removed, see letter attached to Laramide Resources Ltd. dated May 8, 1989.

As you were the operator involved at the time, you are requested to fulfill the obligation imposed by Part 5 of the Permit #MX-8-43 by June 30, 1989.

Failure to comply with the request will result in the bond for \$30,000.00 being confiscated and used to carry out the work under the direction of the Ministry of Energy, Mines and Petroleum Resources.

Yours truly,

R. Bone, P.Eng.,
Inspector of Mines and
Resident Engineer

RB\gp

c.c. Laramide Resources Ltd.
A. F. Reeve
Reclamation: Carol Howel

→ JTL

NR



Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: HAIFIELD CONSULTANTS LTD.

201-1571 BELLEVUE AVENUE
WEST VANCOUVER, B.C.
V7V 3R6

Project:

Comments: ATTN: JOHN VILLAMERE

Page No. : 1
Tot. Pages: 1
Date : 29-JUN-89
Invoice #: I-8918565
P.O. #: NONE

CERTIFICATE OF ANALYSIS A8918565

SAMPLE DESCRIPTION	PREP CODE	S % (Leco)	MAX POT ACID **	Neutral Poten**	PASTE pH					
LOW GRADE 1	208	2.85	89	44	45	8.3	waste pile			
LOW GRADE 2	208	2.63	82	48	34	8.5				
LOW GRADE 3	208	3.02	94	58	36	8.8				
HIGH GRADE 1	208	3.73	117	78	39	8.4				
HIGH GRADE 2	208	16.80	525	103	422	8.0				
HIGH GRADE 3	208	8.90	278	58	220	8.2	ore piles			
HIGH GRADE 4	208	6.31	197	78	189	8.2				
HIGH GRADE 5	208	5.13	160	79	81	8.2				
HIGH GRADE 6	208	5.53	173	86	87	8.0				

246-2224

92B/LAR
41
Blwantes

NOTE: ** UNITS = TONS CaCO₃ EQUIVALENT PER THOUSAND TONS MATERIAL
ALL ASSAY DETERMINATIONS ARE PERFORMED OR SUPERVISED BY B.C. CERTIFIED ASSAYERS

CERTIFICATION :

230 182

HAIFIELD 926:3089

JUL 10 '89 13:17