

BOLIDEN - WESTMIN CANADA LTD
Myra Falls Operation
January 2004 Ore Reserves

830735

Quality Control (January 2004)


A quality control (QA-QC) program on sample analyses recommenced during the fall of 2003 after a hiatus during 2002. A bulk ore muck sample was taken from the H147 mining area of the Battle mine. This ore material represents muck from the Upper zones as well as the Battle Main zone. Additional andesite waste samples were collected from the Battle mine. Each month a sample was mixed with approximately 0.5 kg of material from the ore and andesite bulk samples. The ore sample was then divided into 5 splits with random tags assigned to each split. The andesite waste sample was not split. Only the geologist and buckerman know which samples are part of the test program. The assay lab did not. The sample was divided into five portions as shown on the following flow chart. It is planned to keep this mechanism for quality control in place during subsequent years.

In general there were insignificant differences between all of the assays. The only significant difference is that of Au in the first batch of samples (BG44952, BG44577, BG44777, BG44227 and BG46877). The pulp of the high grade sample, BG44952, was analyzed four more times. Three of the results showed low Au similar to the other samples. The fourth returned a value similar to BG44952. This would indicate a very high nugget effect for the material. See the following "MFO assay QA/QC - January 2004 Table" for results.

Due to a low volume of drill core samples, the typical backlog of analyses for precious metals and barite is currently not a concern. It is expected that contract geologists, assayers and buckerman may be required on a temporary basis to deal with peak demands.

The issue of full screen metallic vs. conventional fire assay was investigated during 2002. The results are attached. The findings appear inconclusive but it appears in a general sense that we may be understating the gold content of the ore by a small percentage. Work was to continue in 2003 but a lack of manpower precluded this from happening.

BOLIDEN - WESTMIN CANADA LTD
Myra Falls Operation
January 2004 Ore Reserves



BOLIDEN - WESTMIN CANADA LTD
Myra Falls Operation
January 2004 Ore Reserves

MFO Assay Quality Assurance and Quality Control Program (January 2004)										
Sep-03	type	sample	number	au	ag	cu	pb	zn	ba	fe
				g/t	g/t	%	%	%	%	%
MFO Lab	Ore pulp split a	split 1	BG44952	11.10	93.00	1.20	0.50	15.00	8.90	6.70
	Ore pulp split b	split 2	BG44577	1.10	94.90	1.20	0.40	14.40	8.50	6.95
	Ore riffle split a	split 3	BG44777	0.50	92.40	1.20	0.45	14.70	9.30	6.90
	Ore riffle split b	split 4	BG44227	0.50	101.20	1.20	0.55	14.90	9.30	7.10
	MFO Lab	Mean		3.30	95.38	1.20	0.48	14.75	9.00	6.91
		Stan. Dev		5.21	4.03	0.00	0.06	0.26	0.38	0.17
MFO vs Outside Lab	Outside Lab	split 5	BG46877	0.66	84.00	1.13	0.50	15.16	8.34	8.32
	MFO minus Outside	** Difference		2.64	11.38	0.07	-0.03	-0.41	0.66	-1.41
Oct-03	type	sample	number	au	ag	cu	pb	zn	ba	fe
				g/t	g/t	%	%	%	%	%
MFO Lab	Ore pulp split a	split 1	BG44951	0.50	184.70	1.75	0.35	15.80	4.70	11.50
	Ore pulp split b	split 2	BG44776	0.40	192.10	1.75	0.40	16.30	4.70	11.60
	Ore riffle split a	split 3	BG44226	0.40	169.80	1.75	0.35	16.70	4.90	11.10
	Ore riffle split b	split 4	BG44576	0.60	176.40	1.75	0.40	16.20	4.80	11.50
	MFO Lab	Mean		0.48	180.75	1.75	0.38	16.25	4.78	11.43
		Stan. Dev		0.10	9.72	0.00	0.03	0.37	0.10	0.22
MFO vs Outside Lab	Outside Lab	split 5	BG44876	0.39	165.90	1.75	0.38	16.05	4.62	12.75
	MFO minus Outside	** Difference		0.09	14.85	0.00	-0.01	0.20	0.16	-1.33
Nov-03	type	sample	number	au	ag	cu	pb	zn	ba	fe
				g/t	g/t	%	%	%	%	%
MFO Lab	Ore pulp split a	split 1	BG41417	0.40	40.00	0.25	0.15	5.30	2.00	2.35
	Ore pulp split b	split 2	BG41435	0.30	38.20	0.25	0.15	5.55	2.10	2.10
	Ore riffle split a	split 3	BG41367	0.60	40.60	0.25	0.15	5.60	2.10	2.15
	Ore riffle split b	split 4	BG41390	0.30	40.20	0.25	0.15	5.60	2.20	2.25
	MFO Lab	Mean		0.40	39.75	0.25	0.15	5.51	2.10	2.21
		Stan. Dev		0.14	1.06	0.00	0.00	0.14	0.08	0.11
MFO vs Outside Lab	Outside Lab	split 5	BG41637	0.12	38.20	0.27	0.16	5.66	2.06	2.96
	Mean minus Outside	** Difference		0.28	1.55	-0.02	-0.01	-0.15	0.04	-0.75
Months	type	sample	number	au	ag	cu	pb	zn	ba	fe
				g/t	g/t	%	%	%	%	%
MFO Lab	barren andesite	Sep-03	BG43700	0.00	0.00	0.00	0.00	0.10	0.10	3.50
	barren andesite	Oct-03	BG43800	0.00	0.80	0.00	0.00	0.00	0.30	1.10
	barren andesite	Nov-03	BG43900	0.00	2.20	0.00	0.00	0.10	na	2.25
	MFO Lab	Average		0.00	1.00	0.00	0.00	0.07	0.20	2.28
		Stan. Dev		0.00	1.11	0.00	0.00	0.06	0.14	1.20

BOLIDEN - WESTMIN CANADA LTD
Myra Falls Operation
January 2004 Ore Reserves

(MFO QA/QC Program continued)

COMMENTS: Ore and barren andesite samples are from the H147 Upper Zone stoping area of the Battle mine.
These results are based on only 3 ore samples and 3 barren samples.
More data is required for better statistical results.

MFO Lab Au Assays: September values for Au are highly variable ranging between 0.5 g/t and 11.1 g/t.
The standard deviation is greater than 100% of the mean value.
Therefore, a nugget effect is interpreted for the September 2003 QA / QC ore sample.
Au assays: October and November Au values have standard deviation values up to 0.14 g/t.
Ag assays: For all months, Ag standard deviation values ranged between 1.06 g/t up to 9.72 g/t.
Cu assays: For all months, Cu standard deviation values were consistently 0%.
Zn assays: For all months, Zn standard deviation values ranged between 0.14% and 0.37%

MFO vs Outside Lab:

Mean Au values for October-November by the MFO laboratory are up to 0.28 g/t Au higher than outside lab value.
Mean Ag values for October-November by the MFO laboratory are up to 14.8 g/t higher than the outside lab value.
Mean Cu values by the MFO laboratory are consistent with the outside laboratory values for all months assessed.
Mean Zn values by the MFO laboratory varies between -0.41% and +0.20% relative to outside laboratory values.

BOLIDEN - WESTMIN CANADA LTD
Myra Falls Operation
January 2004 Ore Reserves

Communication from Rob Eastman, MFO Sr. Assayer: Re: 2003 QA/QC

To: Albert Chong

From: Rob Eastman

Re: Analytical Error of the Boliden-Westmin (Can) Assay Lab up to June 21, 2004

Hello Albert

Our QA/QC program consists of a two pronged approach. The first part consists of data collected from Copper and Zinc Concentrate Quarterly samples that are prepared by myself and exchanged with SGS Labs. The samples are analyzed by all the Assayers and an in house standard deviation and accuracy is calculated. The data consists of results dating back to Oct. 1994.

The second part consists of "blind" samples submitted to the Buckerman who in turn prepares the raw sample. A series of splits are taken and one of the splits is sent to Chemex Labs for analysis while the others are submitted into the regular work load "blind". The comparison of the data is a measure of the complete variability of the entire process. The database for this part is relatively small at the present time.

Explanation of Abbreviations and Terms

BOL = Boliden

SGS = General Testing Laboratories

CMX = Chemex Laboratories

STDEV = Standard Deviation

$\% \text{ Accuracy} = (\text{BOL Assay}) - (\text{SGS or CMX Assay}) / (\text{SGS or CMX Assay}) \times 100$

$\% \text{ STDEV} = (\text{Average STDEV of BOL Assays}) / (\text{Assay SGS or CMX}) \times 100$

BOLIDEN - WESTMIN CANADA LTD
Myra Falls Operation
January 2004 Ore Reserves

(Communication from Rob Eastman, MFO Sr. Assayer: Re: 2003 QA/QC continued):

Note:

1. The term "Accuracy" is the comparison of Boliden's assay to an independent commercial lab assay and not to the "correct value". Variations in assays do occur from one commercial lab to another.
2. When comparing the data presented here one must consider the detection limit of the assay being studied. An example would be a Au assay of 0.5 g/MT +/- 0.1 g/MT. This would give a possible assay variation of +/- 20 % which seems large but more than acceptable by our assay standards and methods.
3. Samples containing free gold will yield "Flyer" assays that in turn significantly skew the average of a small population of assays (as in the case of the "blind" data set).

Results

Cu / Zn Conc. Exchange Samples with SGS Labs

Cu Conc. Accuracy	Zn Conc. Accuracy	Average Accuracy
Au -0.7 % +/- 2.1 %	Au -4.0 % +/- 4.2 %	Au -2.4 % +/- 3.2 %
Ag 2.3 % +/- 1.3 %	Ag -2.1 % +/- 1.8 %	Ag 0.1 % +/- 1.6 %
Cu 0.0 % +/- 0.5 %	Cu -1.5 % +/- 1.6 %	Cu -0.8 % +/- 1.1 %
Pb -2.5 % +/- 1.0 %	Pb -0.1 % +/- 1.4 %	Pb -1.3 % +/- 1.2 %
Zn -0.5 % +/- 1.3 %	Zn 0.2 % +/- 0.4 %	Zn -0.2 % +/- 0.9 %
Fe 1.5 % +/- 0.7 %	Fe 0.6 % +/- 1.7 %	Fe 1.1 % +/- 1.2 %
As -11.4 % +/- 7.3 %	As -23.4 % +/- 7.4 %	As -17.4 % +/- 7.4 %
Sb -20.5 % +/- 10.0 %	Sb 1.3 % +/- 1.4 %	Sb -9.6 % +/- 5.7 %

BOLIDEN - WESTMIN CANADA LTD
Myra Falls Operation
January 2004 Ore Reserves

(Communication from Rob Eastman, MFO Sr. Assayer: Re: 2003 QA/QC; continued):

QA/QC "Blind Samples" Exchange with Chemex Labs (As per previous MFO Assay QA/QC Program Table)

Accuracy

Au 179.9 % +/- 330.9 %
Ag 8.0 % +/- 4.0 %
Cu 0.3 % +/- 0.5 %
Pb -3.3 % +/- 6.2 %
Zn -2.1 % +/- 1.9 %
Fe -15.7 % +/- 1.8 %
Ba 0.7 % +/- 4.6 %

Accuracy Without Flyer

Au 25.2 % +/- 39.8 %

If you have any questions please phone me @ 215.

Rob Eastman
Senior Assayer
Boliden-Westmin (Can.) Ltd.

BOLIDEN - WESTMIN CANADA LTD
Myra Falls Operation
January 2004 Ore Reserves
Standard Precious Metal Assays Vs Full Screen Metallics (2002 data)

AU NORMAL	J METALUCS	% DIF (NO-MT)	AG NORMAL	AG METALLICS	% DIF (NO-MT)	AU NORMAL	AU METALLICS	% DIF (NO-MT)	AG NORMAL	AG METALLICS	% DIF (NO-MT)
0.3	0.3		16.1	18.9	(14.81)	2.8	2.6	7.69	145.0	128.1	13.97
18.8	17.3	867	282.7	266.9	(1.57)	3.3	2.6	26.92	63.8	63.9	(0.16)
1.8	2.3	(21.74)	236.4	241.3	(2.03)	0.9	2.6	(65.38)	174.0	164.8	5.53
1.5	1.3	15.38	55.4	58.7	(5.62)	1.5	1.2	25.00	59.8	53.9	10.95
1.3	2.3	(43.48)	58.4	59.0	(102)	1.3	1.3		110.9	107.1	3.55
1.2	1.4	(1429)	278.4	282.4	(142)	1.9	1.8	5.56	161.6	155.9	3.66
4.8	8.5	(43.53)	228.9	231.3	(1.04)	1.2	1.1	9.09	50.7	45.8	10.70
0.8	1.4	(42.865)	294.4	291.2	1.10	0.9	0.8	12.50	42.5	39.5	6.84
1.4	1.4	(22.22)	212.6	215.1	(1.16)	1.5	1.4	7.14	145.0	132.6	9.35
1.5	1.5	(6.25)	350.4	353.0	(2.40)	0.6	0.6		26.6	38.6	(31.091)
1.3	1.3	8.33	127.1	133.1	(4.51)	1.3	1.2	8.33	89.8	80.2	11.97
1.6	1.5	(36.00)	137.8	144.2	(4.44)	5.1	5.2	(1.92)	667.9	662.2	0.86
1.1	0.8	37.50	166.4	171.7	(3.09)	3.9	3.0	30.00	235.8	235.7	0.04
9.2	1.1	736.36	427.4	426.1	0.31	10.1	10.9	(7.34)	253.3	260.7	(2.84)
81.3	4.7	1,629.79	978.3	951.0	2.87	0.9	0.8	12.50	47.4	45.6	3.95
0.5	0.5	155.3	153.9	153.9	0.91	1.9	2.5	(24.00)	704.7	703.6	0.16
0.8	2.0	(69.23)	237.0	234.9	0.89	65.8	80.3	(18.06)	221.1	215.4	2.65
0.8	0.7	14.29	146.8	154.3	(4.86)	6.8	7.0	(2.86)	619.1	621.8	(0.43)
0.8	0.8	269.8	269.8	271.9	(0.85)	3.5	3.2	9.37	226.5	217.0	4.38
2.1	0.5	320.00	75.0	75.7	(0.92)	23	3.7	(37.84)	285.5	265.1	7.67
1.1	0.7	57.14	107.2	120.5	(11.04)	1.1	1.1		20.6	11.7	74.58
0.0	0.8	(100.00)	57.2	60.2	(4.98)	0.9	1.5	(40.00)	72.7	59.1	23.01
0.4	0.5	(20.00)	79.2	77.6	2.06	23	2.0	15.00	140.4	135.6	18.38
0.9	0.9	11.8	12.8	12.8	(7.81)	18	1.7	5.88	34.9	23.5	48.51
0.7	0.8	(12.50)	80.9	78.6	2.93	0.9	1.0	(10.00)	16.5	8	91.86
1.1	1.4	(21.43)	479.8	476.7	0.65	1.1	1.1		12.0	10.8	11.11
1.9	1.4	35.71	237.3	236.6	0.55	1.3	1.4	(7.14)	19.0	17.3	9.83
0.1	1.0	(90.00)	68.3	35.7	2.40	0.9	0.6	50.00	10.5	6.9	52.17
0.4	0.9	(55.56)	86.2	90.2	(4.43)	1.2	2.0	(40.00)	211.8	206.7	2.47
1.5	1.6	(16.25)	45.0	44.6	0.90	0.9	0.9		79.5	74.7	6.43
5.6	4.2	33.33	119.4	118.0	1.19	1.4	2.4	(41.67)	629.4	827.6	0.29
11.9	9.5	25.26	3115.4	3152.9	(1.19)	2.1	2.5	(16.00)	64.8	66.5	(2.56)
3.9	3.9	1724.0	1728.0	1728.0	(0.23)	1130.4	5457.7	(79.29)	2556.3	5378.7	(5247)
1.2	1.7	(29.41)	56.9	57.4	(0.87)	1.5	6.8	(77.94)	426.7	432.3	1141
5.1	9.2	(44.57)	406.8	407.4	(0.15)	2.2	4.4	(50.00)	536.4	555.5	(3.49)
0.0	0.8	(100.00)	73.6	72.1	2.08	205	9.3	120.43	329.8	332.2	(0.72)
3.4	2.3	47.83	312.3	319.8	(2.35)	12.0	16.3	(26.35)	455.4	458.8	10.74
2.8	2.2	27.27	201.0	207.6	(3.18)	2.9	1.3	123.08	101.5	99.7	1.81
6.7	5.3	26.42	192.0	200.6	(4.29)	0.0	0.6	(100.00)	0.0	34	(100.00)
12.8	5.7	124.56	70.5	61.8	14.08	140	1.4	900.00	194.9	209.5	(6.97)
4.0	6.1	(34.43)	199.8	193.6	3.20	1.0	0.9	11.11	34.3	36.6	(6.28)
3.5	11.1	(6547)	280.9	262.8	6.89	0.0	0.3	(100.00)	0.0	5.3	(100.00)
2.6	2.5	4.00	165.1	161.3	2.36	0.4	0.4		19.5	19.4	0.52
1.1	1.3	(15.38)	87.4	85.5	2.22	2.3	2.5	(8.00)	32.3	29.3	10.24
2.0	6.0	(66.67)	137.8	128.2	7.49	2.8	3.2	(12.50)	54.5	53.1	2.64
4.5	5.3	(15.09)	1294	123.9	4.44	2.0	1.9	5.26	30.5	26.4	15.53
4.4	4.4	1948	189.8	189.8	2.63	0.9	1.0	(10.00)	16.3	14.4	13.19
4.8	6.9	(30.43)	94.4	86.5	9.13	1.5	1.4	7.14	24.8	25.3	(1.98)
1.3	1.7	(23.53)	199.1	188.6	5.57	0.9	0.8	12.50	19.5	20.8	(6.25)
0.5	1.5	(73.68)	34.9	182	91.76	0.9	0.3		12.1	14.4	(15.97)
5.4	3.9	3846	211.0	171.8	22.82	0.5	1.3	(61.54)	24.4	26.6	(8.27)
7.3	5.5	32.73	306.5	274.3	11.74	1.1	0.8	37.50	12.1	11.6	4.31
9.3	8.2	13.41	353.9	330.5	7.08	1.1	0.4	175.00	7.8	9.2	(1522)
5.3	3.1	(34.57)	104.0	95.4	9.01	0.5	0.8	(37.50)	13.8	13.5	2.22
2.6	3.5	(25.71)	81.3	81.2	0.12	0.7	0.7		6.7	6.9	(2.90)
2.9	2.4	20.83	47.2	45.7	3.28	1.5	1.5		89.7	844	6.28
3.9	3.6	8.33	100.7	90.3	11.52	2.5	2.7		527.5	494.8	6.61