

# ECO-TECH LABORATORIES LTD.

ASSAYING - ENVIRONMENTAL TESTING

10041 East Trans Canada Hwy., Kamloops, B.C. V2C 2J3 (604) 573-5700 Fax 573-4557

861127  
Shear

APRIL 16 , 1992

## CERTIFICATE OF ASSAY ETK 92-138


PLACER DOME INC.  
1440 HUGH ALLEN DRIVE  
KAMLOOPS, B.C.  
V1S 1L8

ATTENTION: RON WELLS / BRUNO BARDE

SAMPLE DESCRIPTION: 27 ROCK SAMPLES RECEIVED APRIL 10, 1992  
----- PROJECT: 304

ET#	DESCRIPTION	Ag (g/t)	Ag (oz/t)	Cu (%)
4 -	25504	-	-	5.66
9 -	25509	32.6	.95	1.38

SC92/PLACER1

  
-----  
ECO-TECH LABORATORIES LTD.  
FRANK J. PEZZOTTI, A.Sc.T.  
B.C. CERTIFIED ASSAYER

ECO-TECH LABORATORIES LTD.  
 10041 EAST TRANS CANADA HWY.  
 KAMLOOPS, B.C. V2C 2J3  
 PHONE - 604-573-5700  
 FAX - 604-573-4557

PLACER DOME INC. ETK 92-138  
 1440 HUGH ALLEN DRIVE  
 KAMLOOPS, B.C.  
 VIS 1L8

APRIL 16, 1992


PROJECT: 304  
 27 ROCK SAMPLES RECEIVED APRIL 10, 1992

VALUES IN PPM UNLESS OTHERWISE REPORTED

ET#	DESCRIPTION	AU(ppb)	AG	AL(%)	AS	B	BA	BI	CA(%)	CD	CO	CR	CU	FE(%)	K(%)	LA	MG(%)	MN	MO	NA(%)	NI	P	PB	SB	SN	SR	TI(%)	U	V	W	Y	ZN
1 -	25501	20	<.2	1.88	25	54	40	<5	3.34	<1	34	47	379	3.75	.03	<10	2.43	1886	2	.01	11	1560	2	15	<20	109	.18	<10	138	<10	9	162
2 -	25502	20	3.4	1.87	5	14	60	15	2.98	<1	38	28	6460	3.40	.01	<10	2.60	1985	<1	<.01	10	1520	2	15	<20	71	.15	<10	110	<10	7	228
3 -	25503	10	<.2	1.80	10	12	35	<5	3.12	<1	38	42	316	4.29	.01	<10	2.55	1679	2	.01	12	1610	2	20	<20	80	.17	<10	121	<10	7	178
4 -	25504	25	22.6	1.88	<5	10	65	170	6.82	<1	28	18	>10000	3.53	.08	<10	2.24	2253	1	<.01	7	2260	2	15	<20	100	.10	<10	145	30	5	237
5 -	25505	5	.6	1.76	<5	14	180	<5	6.44	<1	29	22	2100	4.27	.25	<10	1.84	1894	<1	<.01	8	1620	6	15	<20	113	.02	<10	106	<10	3	155
6 -	25506	10	<.2	1.63	15	18	140	<5	2.58	<1	37	35	82	3.64	.01	<10	2.51	1614	1	.01	11	1590	4	15	<20	59	.15	<10	136	<10	8	237
7 -	25507	5	.6	1.59	10	12	65	<5	1.42	<1	33	31	16	4.54	.07	<10	2.00	1275	1	<.01	9	1770	4	15	<20	42	.14	10	129	<10	6	267
8 -	25508	10	<.2	1.63	5	12	75	<5	1.61	<1	30	34	14	3.95	.05	<10	1.75	1182	1	<.01	8	1730	4	10	<20	34	.13	<10	111	<10	5	199
9 -	25509	105	>30.0	1.33	10	14	190	45	1.45	<1	29	40	>10000	4.01	.03	<10	1.81	807	1	.01	9	1530	2	15	<20	66	.25	<10	146	<10	12	244
10-	25510	15	1.6	1.69	15	12	35	<5	1.70	<1	35	36	419	3.60	.02	<10	2.22	1080	1	.01	10	1710	2	15	<20	104	.18	<10	114	<10	9	171
11-	25511	5	<.2	1.66	15	12	40	<5	1.97	<1	33	36	29	3.44	<.01	<10	2.29	1709	2	.01	10	1660	2	15	<20	70	.15	<10	99	<10	5	178
12-	25512	5	4.0	1.79	10	12	85	15	1.91	<1	33	32	6100	4.04	.03	<10	2.19	1280	<1	.01	8	1660	2	15	<20	82	.19	<10	121	<10	8	146
13-	25513	10	2.4	1.70	10	36	350	5	4.24	<1	34	38	1960	4.51	.03	<10	1.95	1289	1	<.01	9	1550	2	15	<20	156	.22	10	150	<10	10	198
14-	25514	5	<.2	1.43	15	12	55	<5	2.59	<1	25	29	30	3.57	.03	<10	1.77	1033	<1	<.01	8	1570	4	15	<20	80	.17	<10	119	<10	7	120
15-	25515	5	2.2	1.82	10	12	100	5	1.81	<1	33	33	3016	4.11	.03	<10	2.40	1388	1	.01	9	1690	2	20	<20	64	.19	10	128	<10	8	162
16-	25516	150	7.8	2.38	55	10	205	20	4.05	5	33	18	8657	5.83	.15	<10	2.26	1509	8	<.01	7	1470	16	60	<20	66	.02	<10	145	<10	3	245
17-	25517	10	10.6	2.26	5	18	115	5	3.34	3	35	31	5217	5.95	.11	<10	2.28	1311	2	.01	9	1610	34	20	<20	57	.17	10	202	<10	8	168
18-	25551	5	<.2	1.47	10	24	30	<5	1.70	<1	30	67	155	4.50	.17	<10	1.98	463	<1	.01	28	1430	2	15	<20	48	.16	10	121	<10	3	29
19-	25552	5	<.2	1.83	5	18	25	<5	2.23	<1	33	79	11	5.11	.18	<10	2.63	626	<1	.01	35	1360	2	15	<20	42	.15	10	114	<10	1	35
20-	25553	5	<.2	1.92	5	8	25	<5	4.35	<1	28	33	13	4.61	.19	<10	2.32	735	<1	.01	14	1280	2	15	<20	70	.13	<10	100	<10	2	44
21-	25554	10	<.2	1.71	5	8	25	<5	3.75	<1	32	68	140	4.64	.14	<10	2.53	680	1	.01	22	1290	2	15	<20	77	.15	10	112	<10	3	42
22-	25555	40	<.2	1.06	10	8	25	<5	2.30	<1	21	23	427	5.11	.05	<10	1.22	420	2	.01	6	1510	2	10	<20	44	.18	10	120	<10	1	34
23-	25556	45	<.2	1.38	10	176	40	<5	1.96	<1	34	93	592	4.39	.06	<10	1.73	376	3	.01	20	1540	2	10	<20	50	.16	10	113	<10	5	26
24-	25557	40	<.2	2.01	5	14	35	<5	1.74	<1	46	53	455	5.01	.14	<10	2.41	485	1	.01	18	1450	2	20	<20	53	.20	<10	120	<10	5	37
25-	25558	100	<.2	2.19	10	12	30	<5	2.47	<1	54	60	486	6.09	.22	<10	2.67	649	4	.02	18	1380	2	20	<20	50	.20	10	159	<10	4	46
26-	25559	15	<.2	2.10	10	10	25	<5	3.60	<1	32	47	176	4.92	.11	<10	2.56	719	1	.01	15	1340	2	20	<20	61	.16	10	111	<10	3	44
27-	25560	30	<.2	1.60	10	10	30	<5	3.41	<1	27	61	196	4.78	.1	<10	1.83	621	4	.01	14	1460	2	15	<20	64	.14	<10	114	<10	4	43

NOTE: < = LESS THAN

SC92/PLACER1

  
 ECO-TECH LABORATORIES LTD.  
 Per FRANK J. PEZZOTTI, A.Sc.T.  
 B.C. CERTIFIED ASSAYER